

NIH Public Access

Author Manuscript

Chem Mater. Author manuscript; available in PMC 2012 March 8.

Published in final edited form as:

Chem Mater. 2011 March 8; 23(5): 1130–1135. doi:10.1021/cm1024487.

Catechol Redox Induced Formation of Metal Core-Polymer Shell Nanoparticles

Kvar C.L. Black^{1,4}, Zhonggiang Liu^{1,4}, and Phillip B. Messersmith^{1,2,3,4,5,6}

¹ Biomedical Engineering Department, Northwestern University, Evanston, Illinois 60208

² Materials Science and Engineering Department, Northwestern University, Evanston, Illinois 60208

³ Chemical and Biological Engineering Department, Northwestern University, Evanston, Illinois 60208

⁴ Chemistry of Life Processes Institute, Northwestern University, Evanston, Illinois 60208

⁵ Institute for Bionanotechnology in Medicine, Northwestern University, Evanston, Illinois 60208

⁶ Robert H. Lurie Comprehensive Cancer Center, Northwestern University, Evanston, Illinois 60208

Abstract

A novel strategy was developed to synthesize polymer-coated metal nanoparticles (NPs) through reduction of metal cations with 3,4-dihydroxyphenylalanine (DOPA)-containing polyethylene glycol (PEG) polymers. Catechol redox chemistry was used to both synthesize metal NPs and simultaneously form a cross-linked shell of PEG polymers on their surfaces. DOPA reduced gold and silver cations into neutral metal atoms, producing reactive quinones that covalently cross-linked the PEG molecules around the surface of the NP. Importantly, these PEG-functionalized metal NPs were stable in physiological ionic strengths and under centrifugation, and hold broad appeal since they absorb and scatter light in aqueous solutions.

Keywords

catechol; quinone; gold; silver; nanoparticle; plasmon; cross-link

Introduction

Catechol-containing molecules serve diverse functions in nature including surface adhesion^{1, 2}, photoprotection³, and neuromodulation ⁴, reflecting a chemical versatility that includes coordination of metal ions⁵ in solution, formation of π -electron⁶ and hydrogen bond⁷ interactions, and redox activity⁸. At solid interfaces, catechols employ one or more of these interactions to form robust adhesion. An example is given by 3,4-dihydroxyphenylalanine (DOPA), which plays a strong role in mussel foot protein adhesion^{9–12}. DOPA residues are believed to be essential in the solidification of the adhesive during attachment through oxidative cross-linking¹ and may also participate in

Contact Author: Phillip B. Messersmith, PhD, Biomedical Engineering Department, Northwestern University, 2145 Sheridan Road, Evanston, IL 60208, Phone (847)467-5273, Fax (847)491-4928, philm@northwestern.edu.

Supporting Information Available: Additional results including MALDI-TOF-MS, color images, optical spectroscopy, electron diffraction, cryo-TEM, and XPS of nanoparticle solutions are available in the supporting information file accompanying this manuscript (PDF). This information is available free of charge via the internet at http://pubs.acs.org.

interfacial adhesion¹³. This versatile chemical repertoire confers upon catechol-containing molecules the ability to adhere to almost any material of either organic or inorganic origin¹⁴.

Noble metal nanoparticles (NPs) composed of gold and silver hold broad appeal in optical applications due to their unique dielectric properties associated with the surface plasmon resonance that interacts strongly with electromagnetic radiation near the plasma frequency¹⁵. The optical properties can be tuned by size, shape, and composition of the metal at the nanoscale¹⁶, and metal NPs can be integrated into aqueous environments when functionalized with polymers such as polyethylene glycol (PEG)^{17–19}. Redox reactions are commonly used to form metal NPs in solution with reducing agents such as citric acid and ascorbic acid $^{20-22}$. Hydroxylated aromatics such as hydroquinone $^{23-26}$ and tyrosinecontaining peptides were used to form silver^{27, 28} and platinum²⁹ NPs and were selected in silver-binding phage display³⁰. Catechol-containing molecules form metal NPs^{31, 32}, and hold additional advantages in forming robust interfaces between metal surfaces and organic molecules compared to other structures, including the ability to coordinate strongly to metals through two adjacent hydroxyls and covalently cross-link when oxidized to quinones by Michael addition and Schiff base reactions. In this study, DOPA-containing PEG polymers induced spontaneous formation of PEG-coated gold and silver NPs from metal salts. A unique feature of the reported approach is the redox coupling of metal reduction with catechol oxidation and simultaneous polymerization to yield a stable cross-linked polymer shell on the NP surface.

Materials

Fmoc-DOPA(Acetonide)-OH and 2-chlorotrityl chloride resin were purchased from EMD Chemicals (Novabiochem, Gibbstown, NJ); methoxy-polyethylene glycol amine (mPEG-NH₂, $M_n = 1937$ g/mol) was purchased from Sunbio Corporation (Korea); N,Ndiisopropylethylamine (DIPEA), dichloromethane (DCM), methanol (MeOH), piperidine, N-methyl-2-pyrrolidone (NMP), Benzotriazol-1-yloxytris(dimethylamino)-phosphonium hexafluorophosphate (BOP), acetic anhydride (Ac₂O), triflouroacetic acid (TFA), toluene, dimethylformamide (DMF), gold chloride (HAuCl₄), silver nitrate (AgNO₃), sodium chloride (NaCl), 2,5-dihydroxybenzoic acid (DBA), sodium phosphate, glycine, and bicine were purchased from Sigma-Aldrich, Inc. (St. Louis, MO); TRIS hydrochloride was purchased from J.T. Baker (Phillipsburg, NJ); TRIS base was purchased from Thermo Fisher Scientific (Waltham, MA).

Methods

Synthesis of Ac-[DOPA(Acetonide)]₄-OH Peptide

The protected tetrapeptide acid was synthesized on 2-chlorotrityl chloride resin using a standard Fmoc-based solid phase peptide synthesis strategy. To introduce the first amino acid, Fmoc-DOPA(Acetonide)-OH (1 mmol) and DIPEA (4 mmol) were dissolved in 15 mL DCM and shaken with 2-chlorotrityl chloride resin (1.6 g, 1.6 mmol) for 4 h. After washing, the resin was capped with methanol using DCM/MeOH/DIPEA (17 : 2 : 1). Fmoc was removed by 20% piperidine in NMP. Subsequent amino acid additions were performed using Fmoc-DOPA(Acetonide)-OH/BOP/DIPEA (1.5 mmol each) in minimum amount of NMP. Ninhydrin test was performed after each amino acid addition to monitor the coupling result. After removal of the Fmoc group of the fourth amino acid, the tetrapeptide was capped with an acetyl group using Ac₂O/DIPEA/NMP (1 : 4 : 40). The protected peptide acid was cleaved from the resin using 2% TFA in DCM solution. MALDI-TOF (negative mode) yielded a monoisotopic mass [M-H]⁻ of 935.71, matching the theoretical mass of 935.37 (Figure S1a).

Synthesis of Ac-DOPA₄-mPEG

mPEG-NH₂ (0.44g) was azeotropically dried with toluene and stirred with Ac-[DOPA(Acetonide)]₄-OH (0.37 g), BOP (0.32 g), and DIPEA (0.136 mL) in dry DCM (3 mL) for two days. The polymer was precipitated with cold dry ethyl ether, dissolved in MeOH and precipitated again with ether. The precipitate was dissolved in water, centrifuged, and filtered. The clear filtrate was lyophilized into a white powder. MALDI-TOF (positive mode) revealed a group of peaks centered at 2865.84 m/z. The content of DOPA was determined using UV-Vis spectroscopy. Taking Ac-[DOPA(Acetonide)]₄-OH peptide as standard, a correlation was established between the concentrations of the peptide in DMF and the absorption intensities at 289 nm. The UV absorption of Ac-[DOPA(Acetonide)]₄-mPEG was measured and the degree of modification was calculated to be 93%. The synthesized Ac-[DOPA(Acetonide)]₄-mPEG (20 mg) was stirred in 2 mL of TFA/MeOH/Water/DCM (30 : 2.5 : 2.5 : 65) for 3 h to give Ac-DOPA₄-mPEG (Figure 1). The deprotected catechol structure was characterized with MALDI-TOF (positive mode); a group of peaks centered at 2705.93 was confirmed (Figure S1b).

Metal NP Synthesis

In one series of experiments, 1 mL aliquots of 370 μ M Ac-DOPA₄-mPEG in ultrapure deionized water were prepared, and pH was adjusted (6.0 – 9.0) with the addition of small volumes of 1 M NaOH. Then 107 μ M metal salt (HAuCl₄ or AgNO₃) was added to each aliquot. In another series, with and without the presence of 10 mM TRIS buffer, varying concentrations of metal salt solution (50 – 3000 μ M) were added to aliquots of 370 μ M Ac-DOPA₄-mPEG at pH 8.5 and mixed vigorously. Identical experiments were performed with 123 μ M Ac-DOPA₄-mPEG solutions.

Optical Spectroscopy

Time-dependent spectra of 123 μ M Ac-DOPA₄-mPEG solutions during gold and silver NP formation were acquired in a one beam Hewlett Packard (Palo Alto, CA) 8452A Diode Array Spectrophotometer over the 250 nm – 820 nm optical range, and compared to a water blank. Spectra were immediately and continually acquired for the duration of the reaction, and scan times ranged between 0.1 and 0.5 seconds.

Electron Microscopy (EM)

Metal NP samples were centrifuged at 9000 rpm for 10 minutes, and the supernatant solution was removed. $5-10 \ \mu$ L of the NP pellet was dropped onto an EM carbon grid (Electron Microscopy Sciences, Hatfield, PA) and allowed to dry overnight. For samples stained with phosphotungstic acid, grids with dried metal NPs were dipped in a 10% solution for 5 minutes, and then dipped in a solution of deionized water three times, soaked for 30 seconds, and allowed to dry. Transmission EM (TEM), Z-contrast (ZC) EM (a mode that provides bright contrast to high atomic number elements), secondary EM (SEM), and electron diffraction imaging were performed on a Hitachi HD-2300 Ultra High Resolution FE-STEM.

Results

Addition of gold chloride into a basic solution of Ac-DOPA₄-mPEG (Figure 1) induced a red color change in the solution that darkened over the span of a minute (Figures 2a inset and S2a). To characterize this color transformation, optical spectroscopy was performed before and after the addition of gold chloride into PEG solutions (Figure 2a). Before gold addition, a lone 280 nm DOPA absorption peak was detected. 10 seconds after addition of

HAuCl₄, a 390 nm peak and a 550 nm peak formed, and within 1 minute the 390 nm and 550 nm peak intensities stabilized.

A series of experiments were performed in which the concentration of gold chloride was varied (107 μ M – 1970 μ M) under constant polymer concentration (Table 1). A red color change occurred in samples with gold concentrations less than 1000 μ M, whose optical spectra contained both a transient 390 nm peak and a stable peak centered between 525–560 nm. The 525–560 nm peak broadened and the center wavelength red-shifted with increasing amounts of gold up to 1000 μ M. Importantly, when 1970 μ M gold chloride was added to 370 μ M polymer solutions, no red color change or absorbance at 525–560 nm were observed and the sample remained similar in appearance to the yellow color of pure gold chloride solution (Figure S2b). Experiments were also performed in the presence of TRIS buffer at 8.5 pH and yielded qualitatively similar color changes and optical spectra as their unbuffered counterparts (Figure S3).

In order to confirm the formation of gold NPs, samples were imaged with electron microscopy. In all samples with visible absorbance in the 525–560 nm range, sub-80 nm NPs were evident. Additionally, control over gold NP size between 10 nm and 70 nm was achieved by varying the concentration of gold chloride between 107 μ M – 625 μ M in 370 μ M polymeric solutions (1480 μ M catechol). Table 1 lists the polymer and metal ion concentrations and the resulting plasmon center wavelength and particle size. Micrographs of 70 nm gold NPs are shown in Figure 2. High resolution imaging under TE mode of a single NP provided evidence of a metal core and a less electron dense coating 9.4 nm thick (Figure 2b), SEM provided NP surface morphology of the metal core (Figure 2b inset), and EDS spectral imaging confirmed that gold was localized to the core (data not shown). Electron diffraction was performed on the gold core of single NPs (Figure S4), and gave evidence of polycrystalline features including twinning doublets and crystal orientation changes. Furthermore, multimode electron microscopy was performed on a group of gold NPs that appeared as closely packed spheres under SEM (Figure 2c). Under Z-contrast imaging (Figure 2d), the same cluster of NPs were observed to be separated from each other by up to 20 nm. When cryo-TEM was performed on a sample of gold NPs formed with the DOPA-containing PEG polymers to characterize their dispersion in suspension, welldispersed gold particles were observed (Figure S5).

In order to observe changes in polymer mass correlated to oxidation-induced polymerization, samples were plated at various times during the gold NP synthesis and MALDI-TOF-MS was performed (See Supporting Information for methods). Prior to the addition of HAuCl₄, a distribution of peaks centered at 2749 m/z with spacing of 44 (the weight of a PEG monomer unit) between peaks was detected in all pH conditions, representing individual Ac-DOPA₄-mPEG molecules. No peak distributions at higher masses were detected. Likewise, when gold was added at pH 6 (where NP formation did not occur as indicated by spectroscopic analysis), signal from the Ac-DOPA₄-mPEG molecule were detected. However under conditions where NP formation of peaks centered at twice the molecular weight of a single Ac-DOPA₄-mPEG molecule (5388 m/z) was detected (Figure S1c). XPS analysis of gold NPs revealed C1s and O1s peaks (Figure S6a), as well as weak peaks from Au 4f.

Similar results were obtained when silver nitrate was added to Ac-DOPA₄-mPEG using the same method as described with gold chloride. In basic conditions and excess catechol, a yellow color change (Figures 3a, S2c, and S3) resulting from a peak centered at ~410 nm occurred immediately after addition of AgNO₃, growing steadily for 1 minute. TEM imaging of NPs from a sample with a 403 nm absorption maximum revealed NPs of 17 nm

average size (Figure 3b), and XPS analysis of the same sample revealed C1s, O1s, Ag2s, and Ag₂O peaks (Figure S6b).

To investigate their stability in saline conditions, gold and silver NPs formed with Ac-DOPA₄-mPEG were incubated in 100 mM sodium chloride; control gold NPs with a 520 nm peak coated with citrate were also evaluated. In the case of gold, the peak in the 525–560 nm range from Ac-DOPA₄-mPEG-stabilized NPs did not shift or change shape when placed in 100 mM saline solution for 24 hours. In contrast, the peak of citrate-stabilized gold NPs broadened and red-shifted in 10 mM NaCl, further red-shifting and broadening with increasing concentrations of salt (Figures 4 and S7a). The silver NP suspensions formed with Ac-DOPA₄-mPEG were also stable in 100 mM sodium chloride (Figure S7b).

Discussion

Covalent reactions resulting from oxidation of DOPA are believed to play an important role in solidification and structural cohesion in mussel adhesive proteins² and sandcastle worm cement^{33–35}, and are believed to proceed via oxidation of DOPA to quinone^{9, 36} followed by their reaction to form covalent di-DOPA cross-links^{37, 38}. In this study, coupling of catechol oxidation with reduction of metal ions was demonstrated as a simple and convenient route for *in situ* formation of metal NPs while also ensuring a robust interface between the metal surface and surface grafted polymers.

The addition of gold and silver salts into Ac-DOPA₄-mPEG solutions led to rapid color change consistent with the formation of Au and Ag NPs with plasmon resonances centered at 525–560 nm and 400–430 nm, respectively. NP formation was clearly linked to the oxidation of DOPA in the Ac-DOPA₄-mPEG polymer, as peaks typical of DOPA-quinone (390 nm) and the plasmon resonance co-evolved during the reaction (Figure 2a). Control over particle size within the range 10–70 nm was achieved by manipulating the molar ratio of catechol to metal during reaction (Table 1). A general correlation between NP size and plasmon resonance was observed, with larger NPs giving rise to plasmon resonances at higher wavelengths, matching previous reports^{15, 16}. SEM analysis of 70 nm gold NPs provided evidence in support of clustering of smaller nanoparticles (Figure 2b, inset).

EM analysis of the NPs isolated from the reaction mixture showed that the reaction culminated in the formation of well-dispersed NPs (Figure S5) with a core-shell structure composed of a polycrystalline metal core (Figure S4) and an organic shell of thickness <10 nm (Figures 2 and 3). Once dried on an EM grid, SEM imaging that emphasizes the secondary electrons from the surface-bound PEG polymers revealed aggregates of NPs. However, Z-contrast imaging was used to accentuate the metal cores, revealing clear gaps between NP cores which presumably were occupied by Ac-DOPA₄-mPEG polymers comprising the NP shell. Metal core-polymer shell morphology was also detected by TEM with EDS spectral imaging (data not shown). The approximate thickness of the polymer shell (~ 9.4 nm) lies between the contour length (15.8 nm) and the dimensions of a tethered 2kDa PEG chain (4.8 nm)³⁹, implying an extended conformation⁴⁰, possibly due to dense polymer surface packing.

Evidence for covalent coupling of Ac-DOPA₄-mPEG was obtained through MALDI-MS analysis of the reaction mixture. Higher molecular weight species were observed shortly after mixing polymer and metal salt, confirming Ac-DOPA₄-mPEG polymerization during NP formation. Detection of the Ac-DOPA₄-mPEG dimer by MALDI only occurred upon the addition of metal salt at pH 8.7, providing further evidence that quinone-mediated cross-linking of Ac-DOPA₄-mPEG was concurrent with metal NP formation. The most likely explanation for these observations is that metal reduction led to catechol oxidation and

ultimately di-DOPA coupling of Ac-DOPA₄-mPEG polymers. Importantly, this study represents an alternative approach to previously reported methods^{41, 42} to form stable cross-linked polymer shells on NPs, one that is catalyzed by the same catechol redox reaction that causes the formation of the metal nanocrystals *in situ*.

Taken together, the presence of metal NP plasmon resonances, Au, Ag, ether C, and O peaks in XPS, as well as core-shell morphology evident in NPs under EM provide evidence of a PEG polymer coating on the metal NPs. The presence of a PEG shell should confer stability against aqueous aggregation of the NPs, particularly under high ionic strength conditions as would be observed in many biomedical applications of NPs. Indeed, Ac-DOPA₄-mPEG coated NPs were stable in high ionic strength solutions whereas citrate-stabilized Au NPs aggregated as evidenced by red shift of the surface plasmon absorbance (Figures 4 and S7). The covalent cross-linking of grafted Ac-DOPA₄-mPEG polymers within the polymer shell, as well as the robust adhesion afforded by DOPA at interfaces, should combine to create a robust core-shell NP, and in the future it may be possible to incorporate other DOPAcontaining molecules into more complex and multifunctional assemblies such as biodegradable plasmonic liposomes⁴³.

Our strategy builds upon recent work wherein catechol-containing molecules such as dopamine¹⁴ or DOPA peptides⁴⁴ were used to graft polymers and biomolecules onto surfaces, and represents an alternative approach to linking PEG and other polymers onto metal NP surfaces using polyamine¹⁷, thiol¹⁸, and thioctic acid¹⁹ anchors. In contrast to these previous approaches, the catechol group of DOPA serves as metal reductant, molecular anchor, and polymerizable cross-linker, simultaneously inducing *in situ* metal NP formation while also providing a cohesively cross-linked and robust adhesive interface between the metal NP and the PEG polymer shell (Figure 5). Gold NPs between 10 nm and 70 nm were formed and stabilized with this strategy, the larger particles characterized by a cluster morphology coated in PEG that should provide electromagnetic hotspots between metal crystals for surface enhanced Raman spectroscopy (SERS)^{45, 46}. Further, both gold and silver NPs were formed and stabilized, an important advantage for potential applications that use silver to either tune plasmonic absorption and scattering⁴⁷ or provide an antimicrobial therapeutic effect⁴⁸. Through its molecular design that contains four DOPA residues per molecule and aided by further polymerization during metal NP formation, Ac-DOPA₄-mPEG is expected to lead to multivalent attachment onto the NP surface, as is hypothesized in the case of mussel adhesive proteins that contain multiple DOPA residues¹¹, 49,50. Although we do not know the exact nature of the chemical interaction between DOPA and the metal NP surface, charge transfer and physisorption interactions from the aromatic side chain of DOPA⁶ and coordination through the catechol oxygen atoms⁵¹ have been hypothesized.

Conclusions

A catechol redox based strategy was employed to induce spontaneous *in situ* formation of polymer-coated gold and silver NPs from mixtures of a DOPA-containing polymer and noble metal salts. In this biomimetic strategy the catechol side chain of DOPA serves multiple roles: as a reducing agent for metal ions; as an anchoring chemistry for multivalent binding of the polymer onto the NP surface; and as a chemical precursor for cross-linking of the polymer shell. The resulting core-shell NPs exhibit plasmon resonance behavior characteristic of noble metal NPs and are stable toward aggregation in ionic aqueous media. Potentially, this biomimetic strategy can be used to produce surface derivatized metal NPs for diagnostic and therapeutic applications.

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The work was supported by National Institutes of Health (NIH) grant R37 DE014193. K.C.L.B. was partly supported by a NIH Health Ruth Kirschstein NRSA fellowship from the National Institute of Dental and Craniofacial Research (F31 DE019750). The content is solely the responsibility of the authors and does not necessarily represent the official views of the National Institute of Dental and Craniofacial Research or the National Institutes of Health. The authors also acknowledge the NUANCE, Keck II, and IMSERC facilities at Northwestern University for their TEM, UV-Vis, and MALDI-TOF-MS instruments, respectively, and Jinsong Wu of NUANCE for acquiring the cryo-TEM images.

References

- 1. Waite JH. Nature's underwater adhesive specialist. Int J Adhes Adhes. 1987; 7:9-14.
- 2. Waite JH. Adhesion a la Moule. Integr Comp Biol. 2002; 42:1172–1180.
- 3. Brenner M, Hearing VJ. The Protective Role of Melanin Against UV Damage in Human Skin. Photochem Photobiol. 2008; 84:539–549. [PubMed: 18435612]
- 4. Callier S, Snapyan M, Crom SL, Prou D, Vincent JD, Vernier P. Evolution and cell biology of dopamine receptors in vertebrates. Biol Cell. 2003; 95:489–502. [PubMed: 14597267]
- 5. Pierpont CG, Buchanan RM. Transition Metal Complexes of o-Benzoquinone, o-Semiquinone, and Catecholate Ligands. Coordin Chem Rev. 1981; 38:45–87.
- Weinhold M, Soubatch S, Temirov R, Rohlfing M, Jastorff B, Tautz FS, Doose C. Structure and Bonding of the Multifunctional Amino Acid L-DOPA on Au(110). J Phys Chem B. 2006; 110:23756–23769. [PubMed: 17125337]
- Burzio LA, Waite JH. Reactivity of peptidyl-tyrosine to hydroxylation and cross-linking. Protein Sci. 2001; 10:735–740. [PubMed: 11274464]
- Uchimiya M, Stone AT. Redox reactions between iron and quinones: Thermodynamic constraints. Geochim Cosmochim Ac. 2006; 70:1388–1401.
- Yu M, Hwang J, Deming TJ. Role of L-3,4-Dihydroxyphenylalanine in Mussel Adhesive Proteins. J Am Chem Soc. 1999; 121:5825–5826.
- 10. Suci PA, Geesey GG. Comparison of adsorption behavior of two Mytilus edulis foot proteins on three surfaces. Colloid Surface B. 2001; 22:159–168.
- Waite JH, Qin X. Polyphosphoprotein from the Adhesive Pads of Mytilus edulis. Biochemistry-US. 2001; 40:2887–2893.
- Waite JH. Evidence for a Repeating 3,4-Dihydroxyphenylalanine- and Hydroxyproline-containing Decapeptide in the Adhesive Protein of the Mussel, Mytilus edulis L. J Biol Chem. 1983; 258(5): 2911–2915. [PubMed: 6298211]
- Lee H, Scherer NF, Messersmith PB. Single-molecule mechanics of mussel adhesion. PNAS. 2006; 103(35):12999–13003. [PubMed: 16920796]
- Lee H, Dellatore SM, Miller WM, Messersmith PB. Mussel-Inspired Surface Chemistry for Multifunctional Coating. Science. 2007; 318:426–430. [PubMed: 17947576]
- 15. Simmons, JH.; Potter, KS. Optical Materials. Academic Press; San Diego: 2000.
- Jain PK, Lee KS, El-Sayed IH, El-Sayed MA. Calculated Absorption and Scattering Properties of Gold Nanoparticles of Different Size, Shape, and Composition: Application in Biological Imaging and Biomedicine. J Phys Chem B. 2006; 110:7238–7248. [PubMed: 16599493]
- Miyamoto D, Oishi M, Kojima K, Yoshimoto K, Nagasaki Y. Completely Dispersable PEGylated Gold Nanoparticles under Physiological Conditions: Modification of Gold Nanoparticles with Precisely Controlled PEG-b-polyamine. Langmuir. 2008; 24(9):5010–5017. [PubMed: 18386943]
- Duchesne L, Gentili D, Comes-Franchini M, Fernig DG. Robust Ligand Shells for Biological Applications of Gold Nanoparticles. Langmuir. 2008; 24:13572–13580. [PubMed: 18991409]
- 19. Zhang G, Yang Z, Lu W, Zhang R, Huang Q, Tian M, Li L, Liang D, Li C. Influence of anchoring ligands and particle size on the colloidal stability and in vivo biodistribution of polyethylene

glycol-coated gold nanoparticles in tumor-xenografted mice. Biomaterials. 2009; 30:1928–1936. [PubMed: 19131103]

- 20. Turkevich J, Stevenson PC, Hillier J. Discuss Faraday Soc. 1951; 11:55.
- Kimling J, Maier M, Okenve B, Kotaidis V, Ballot H, Plech A. Turkevich Method for Gold Nanoparticle Synthesis Revisited. J Phys Chem B. 2006; 110(32):15700–15707. [PubMed: 16898714]
- 22. Enustun BV, Turkevich J. J Am Chem Soc. 1963; 85:3317.
- 23. Yi HB, Diefenbach M, Choi YC, Lee EC, Lee HM, Hong BH, Kim KS. Interactions of Neutral and Cationic Transition Metals with the Redox System of Hydroquinone and Quinone: Theoretical Characterization of the Binding Topologies, and Implications for the Formation of Nanomaterials. Chem Eur J. 2006; 12:4885–4892.
- Perez MA, Moiraghi R, Coronado EA, Macagno VA. Hydroquinone Synthesis of Silver Nanoparticles: A Simple Model Reaction To Understand the Factors That Determine Their Nucleation and Growth. Cryst Growth Des. 2008; 8(4):1377–1383.
- Gentry ST, Fredericks SJ, Krchnavec R. Controlled Particle Growth of Silver Sols through the Use of Hydroquinone as a Selective Reducing Agent. Langmuir. 2009; 25:2613–2621. [PubMed: 19437745]
- Perrault SD, Chen WCW. Synthesis and Surface Modification of Highly Mondispersed, Spherical Gold Nanoparticles of 50–200 nm. J Am Chem Soc. 2009; 131:17042–17043. [PubMed: 19891442]
- Jacob JA, Mahal HS, Biswas N, Mukherjee T, Kapoor S. Role of phenol Derivatives in the Formation of Silver Nanoparticles. Langmuir. 2007; 24(2):528–533. [PubMed: 18095719]
- Xie J, Lee J-Y, Wang DIC, Ting YP. Silver Nanoplates: From Biological to Biomimetic Synthesis. ACS Nano. 2008; 1(5):429–439. [PubMed: 19206664]
- 29. Li Y, Whyburn G, Huang Y. Specific Peptide Regulated Synthesis of Ultrasmall Platinum Nanocrystals. J Am Chem Soc. 2009; 131(44):15998–15999. [PubMed: 19831348]
- Naik RR, Stringer SJ, Agarwal G, Jones SE, Stone MO. Biomimetic synthesis and patterning of silver nanoparticles. Nat Mater. 2002; 1:169–172. [PubMed: 12618805]
- Baron R, Zayats M, Willner I. Dopamine-, L-DOPA-, Adrenaline-, and Noradrenaline-Induced Growth of Au Nanoparticles: Assays for the Detection of Neurotransmitters and of Tyrosinase Activity. Anal Chem. 2005; 77:1566–1571. [PubMed: 15762558]
- 32. Begum N, Mondal S, Basu S, Laskar R, Mandal D. Biogenic synthesis of Au and Ag nanoparticles using aqueous solutions of Black Tea leaf extracts. Colloid Surface B. 2009; 71:113–118.
- 33. Stewart RJ, Weaver JC, Morse DE, Waite JH. The tube cement of Phragmatopoma californica: a solid foam. J Exp Biol. 2004; 207:4727–4734. [PubMed: 15579565]
- Endrizzi BJ, Huang G, Kiser PF, Stewart RJ. Specific Covalent Immobilization of Proteins through Dityrosine Cross-links. Langmuir. 2006; 22:11305–11310. [PubMed: 17154619]
- Shao H, Bachus KN, Stewart RJ. A Water-Borne Adhesive Modeled after the Sandcastle Glue of P. californica. Macromol Biosci. 2009; 9(5):464–471. [PubMed: 19040222]
- Burzio LA, Waite JH. Cross-linking in Adhesive Quinoproteins: Studies with Model Decapeptides. Biochemistry US. 2000; 39:11147–11153.
- 37. Schonhorn, H. Adhesion and adhesives: Interactions at interfaces. Plenum; New York: 1981.
- McDowell LM, Burzio LA, Waite JH, Schaefer J. Rotational echo double resonance detection of cross-links formed in mussel byssus under high-flow stress. J Biol Chem. 1999; 274(29):20293– 20295. [PubMed: 10400649]
- Moore NW, Kuhl TL. The Role of Flexible Tethers in Multiple Ligand-Receptor Bond Formation between Curved Surfaces. Biophys J. 2006; 91(5):1675–1687. [PubMed: 16751237]
- Jeppesen C, Wong JY, Kuhl TL, Israelachvili JN, Mullah N, Zalipsky S, Marques CM. Impact of Polymer Tether Length on Multiple Ligand-Receptor Bond Formation. Science. 2001; 293:465– 468. [PubMed: 11463908]
- Gittins DI, Caruso F. Multilayered Polymer Nanocapsules Derived from Gold Nanoparticle Templates. Adv Mater. 2000; 12(24):1947–1949.

Black et al.

- Joralemon MJ, O'Reilly RK, Hawker CJ, Wooley KL. Shell Click-Crosslinked (SCC) Nanoparticles: A New Methodology for Synthesis and Orthogonal Functionalization. J Am Chem Soc. 2005; 127:16892–16899. [PubMed: 16316235]
- Troutman TS, Barton JK, Romanowski M. Biodegradable Plasmon Resonant Nanoshells. Adv Mater. 2008; 20:2604–2608. [PubMed: 21494416]
- 44. Dalsin JL, Hu BH, Lee BP, Messersmith PB. Mussel Adhesive Protein Mimetic Polymers for the Preparation of Nonfouling Surfaces. J Am Chem Soc. 2003; 125:4253–4258. [PubMed: 12670247]
- 45. Moskovits M. Surface-enhanced Raman spectroscopy: a brief retrospective. J Raman Spectrosc. 2005; 36:485–496.
- 46. Camden JP, Dieringer JA, Wang Y, Masiello DJ, Marks LD, Schatz GC, Duyne RPV. Probing the Structure of Single-Molecule Surface Enhanced Raman Scattering Hotspots. J Am Chem Soc. 2008; 130:12616–12617. [PubMed: 18761451]
- Link S, Wang ZL, El-Sayed MA. Alloy Formation of Gold-Silver Nanoparticles and the Dependence of the Plasmon Absorption on Their Composition. J Phys Chem B. 1999; 103:3529– 3533.
- Rai M, Yadav A, Gade A. Silver nanoparticles as a new generation of antimicrobials. Biotechnol Adv. 2009; 27:76–83. [PubMed: 18854209]
- 49. Waite JH. Evidence for a Repeating 3,4-Dihydroxyphenylalanine- and Hydroxyproline-containing Decapeptide in the Adhesive Protein of the Mussel, Mytilus edulis L. THE JOURNAL OF BIOLOGICAL CHEMISTRY. 1983; 258(5):2911–2915. [PubMed: 6298211]
- Papov VV, Diamond TV, Biemann K, Waite JH. Hydroxyarginine-containing polyphenolic proteins in the adhesive plaques of the marine mussel Mytilus edulis. J Biol Chem. 1995; 270(34): 20183–20192. [PubMed: 7650037]
- Ooka AA, Garrell RL. Surface-Enhanced Raman Spectroscopy of DOPA-Containing Peptides Related to Adhesive Protein of Marine Mussel, Mytilus edulis. Biopolymers (Biospectroscopy). 2000; 57:92–102. [PubMed: 10766960]

Black et al.



Figure 1. Molecular structure of Ac-DOPA₄-mPEG polymer.



Figure 2.

Spontaneous formation of Ac-DOPA₄-mPEG-coated gold nanoparticles: (a) UV-Vis extinction curves at successive time points after mixing 102 μ M HAuCl₄ with 123 μ M Ac-DOPA₄-mPEG. The inset shows a photograph of the suspension after 1 hour. (b–d) EM of gold NPs formed with Ac-DOPA₄-mPEG: (b) TEM and SEM (inset) of a single gold NP, (c) SEM and (d) Z-Contrast EM of a cluster of gold NPs.



Figure 3.

Spontaneous formation of Ac-DOPA₄-mPEG-coated silver nanoparticles: (a) UV-Vis extinction curves at successive time points during the formation of silver NPs with Ac-DOPA₄-mPEG polymers. The inset shows a photograph of the suspension after 1 hour. (b) TEM microscopy of silver NPs formed with Ac-DOPA₄-mPEG.



Figure 4.

Plot of the visible extinction peak center wavelength from Ac-DOPA₄-mPEG-coated (white) and citrate-coated (black) gold nanoparticles as a function of sodium chloride concentration.



Figure 5.

Schematic representing the addition of Ac-DOPA₄-mPEG with gold or silver ions to form a metallic NP core with a DOPA interface and a PEG shell.

Table 1

Table representing the concentration of Ac-DOPA₄-mPEG and metal salt, the metal-DOPA ratio, the surface plasmon resonance (SPR) center wavelength, and the nanoparticle size determined by TEM of metal nanoparticle samples.

Black et al.

[Ac-DOPA4-mPEG] (μM)	[Au] (μ M)	[Ag] (µM)	[M]/[DOPA]	SPR λ (nm)	Size (nm)
370	107	0	0.0723	525	10.4 ± 6.7
370	427	0	0.289	547	38.7 ± 5.5
370	625	0	0.423	559	68 ± 18
370	1970	0	1.33	ΩN	N/A
370	0	107	0.0723	415	16.9 ± 2.4