

BZT: a soft pseudo-spin glass

David Sherrington*

*Rudolf Peierls Centre for Theoretical Physics, University of Oxford, 1 Keble Road, Oxford OX1 3NP, UK
Santa Fe Institute, 1399 Hyde Park Rd., Santa Fe, NM 87501*

(Dated: 24 Oct 2013)

In an attempt to understand the origin of relaxor ferroelectricity, it is shown that interesting behaviour of the onset of non-ergodicity and of precursor nanodomains, found in first principles simulations of the relaxor alloy $\text{Ba}(\text{Zr}_{1-x}\text{Ti}_x)\text{O}_3$, can easily be understood within a simple mapping to a soft pseudo-spin glass.

For several years there has been much interest in relaxor ferroelectric alloys based on the the generic pure ionic perovskite form ABO_3 , where A, B, O have charges +2, +4 and -2, but with the single B-type ion replaced by random mixtures of B' , B'' [1–3]. They exhibit (i) frequency-dependent peaks in their dielectric susceptibilities as a function of temperature but without any macroscopic polarization in the absence of applied fields and (ii) higher temperature manifestations of nano-scale polar domains [4]. They have proven to be of significant application value but there is no universally accepted understanding of the origin of their behavior. The present objective is to provide such understanding within the context of a recently recognised system, employing only minimal modeling and simple mappings and without the need to posit *a priori* random bonds or random fields.

The originally discovered [5] and most studied relaxor is $\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3$ (PMN). It exhibits the features mentioned above, as well as non-ergodicity [6, 7] beneath a temperature comparable with that of the finite-frequency susceptibility peaks. However, it is complicated by the fact that Mg and Nb are not isovalent, giving rise to perturbing extra charges and hence random fields. By contrast, in $\text{Ba}(\text{Zr}_{1-x}\text{Ti}_x)\text{O}_3$ (BZT) Zr and Ti are isovalent, of charge +4. Yet it still exhibits characteristic relaxor features [8–10] for a range of relative (Zr:Ti) concentrations.

A recent first principles and Monte Carlo computer simulation study of BZT [11] has demonstrated an ergodicity-breaking phase transition at which a separation onsets between dielectric susceptibilities measured under different protocols and also has exhibited nanodomains above this transition temperature. This communication provides a physical explanation of this transition as the onset of a soft spin glass-like state, extends the analogy to explain the more general phase structure of BZT and demonstrates an expected origin of the observed nano-domains.

BaZrO_3 and BaTiO_3 are ABO_3 ionic crystals with positive charges on the Ba, Zr and Ti ions and negative charges on the O ions. Their equilibrium structures correspond to minimizing their free energies under the resultant competing (spatially frustrated) interactions. At high temperatures both have simple perovskite structure

but at low temperature BaTiO_3 transforms to a ferroelectric through spontaneous coherent displacement of the Ti ions; BaZrO_3 remains paraelectric as the temperature is lowered. The particular current interest is in alloys in which the B sites are occupied randomly by Zr or Ti.

Akbarzadeh et al.[11] studied the alloy system with equal concentrations of Zr and Ti, allowing for displacements of all the ions (in a finite-size simulation) and using parameters obtained from first-principles computer modeling of small cells. They examined the susceptibilities measured (i) by directly observing the polarization when cooled in a small applied field and (ii) from the correlation function in the absence of an applied field, using the conventional equilibrium statistical physics relationship between response and correlation. These measurements increased with reducing temperature and roughly coincided above a characteristic temperature, T_f , but started to diverge significantly from one another at this temperature, with the directly evaluated susceptibility exhibiting a plateau beneath it while that determined from the correlations decreased, giving a cusp at T_f . This is precisely what is expected from mapping to a pseudo-spin glass.

As noted and utilised in [11], a crucial difference between systems with Zr or Ti at a B site lies in the strength of the effective local restoring forces associated with displacements of the ions from their positions in the pure matrix; these are weak for Ti, permitting the low-temperature ferroelectric distortion observed in BaTiO_3 , whereas in BaZrO_3 the Zr restoring force is much stronger and prevents macroscopic global distortion even to zero temperature.

Akbarzadeh et al. [12] modeled the alloy in terms of local mode variables centred on B-sites, including averaged inter-site interaction terms, simple local restoring-force terms of strengths corresponding to the appropriate local B-site occupation and associated random fields and random strains. However, they found that their results are essentially unaffected by the random field and random strain terms and hence these will be ignored from the outset here. For conceptual purposes the modeling can be simplified further by absorbing the effects of the Ba and O ions into an effective system involving only the B-site ions. Ignoring any local anisotropy for illustrative simplicity, one is then left with a model characterized by

an effective Hamiltonian

$$H = \sum_i \{ \kappa_i |\mathbf{u}_i|^2 + \lambda_i |\mathbf{u}_i|^4 \} + \sum_{ij} H_{int}^{avg}(\mathbf{u}_i, \mathbf{u}_j, \mathbf{R}_{ij}) \quad (1)$$

where the sites $\{i\}$ are occupied randomly by Ti or Zr according to the admixture concentration, with corresponding κ, λ . H_{int} represents interactions between $\{\mathbf{u}\}$ at different sites; the superscript $\{avg\}$ indicates that, as in [11], effects of the randomness are averaged and details of quenched randomness in H_{int} are ignored. The zero-temperature phase structure is given by minimising H with respect to the $\{\mathbf{u}_i\}$.

Considering first a pure system, the sign of κ determines whether this Hamiltonian can, in principle, exhibit displacive or order-disorder transitions, with positive κ being displacive and the true order-disorder limit corresponding to strongly negative κ , in each case with λ positive. Within mean field theory, in the order-disorder case there will always be a transition to an ordered phase as the temperature is lowered from the high temperature paramagnetic phase, whereas in the displacive case a minimal strength of bootstrapping binding energy gain from H_{int} , through self-consistent displacements, is needed to overcome the local penalty from the κ term. For BaTiO_3 κ^{Ti} is small enough to permit ferroelastic, and hence ferroelectric, order being favored in this case [13]. By contrast, κ^{Zr} is too large for self-consistent displacive order and only para-electricity $\{u_i = 0\}$ is possible at all temperatures for BaZrO_3 .

Turning now to the alloy and noting that the large κ^{Zr} implies that all the sites $\{i\}$ occupied by Zr atoms have $u_i = 0$ and hence may be ignored, one is left with the effective Hamiltonian

$$H_{eff} = \sum_{i(\text{Ti})} \{ \kappa^{\text{Ti}} |\mathbf{u}_i|^2 + \lambda^{\text{Ti}} |\mathbf{u}_i|^4 \} + \sum_{ij(\text{Ti})} H_{int}(\mathbf{u}_i, \mathbf{u}_j, \mathbf{R}_{ij}). \quad (2)$$

with sums now restricted to B-sites occupied by Ti ions.

The fact that experimentally the low temperature state of BaTiO_3 is ferroelectric shows that the dominant interaction in H_{int} is ferroelectric. However, there are both ferroelectric and anti-ferroelectric contributions at different separations [14] [15].

This model is now recognizable as a soft pseudo-spin analog of canonical experimental spin glass systems [16], such as $\text{Au}_{1-x}\text{Fe}_x$ or $\text{Eu}_x\text{Sr}_{(1-x)}\text{S}$, whose Hamiltonians may be written as

$$H = - \sum_{ij(\text{Mag})} J(\mathbf{R}_{ij}) \mathbf{S}_i \cdot \mathbf{S}_j \quad (3)$$

where the \mathbf{S}_i are hard spins [17], $J(\mathbf{R})$ is a translationally-invariant but spatially-frustrated exchange interaction and the sum is restricted to sites oc-

cupied by magnetic atoms [21]. For large x , high concentrations of magnetic atoms, these systems are periodically magnetically-ordered but for lower concentrations of magnetic atoms a non-periodic non-ergodic but still cooperative spin-glass phase results [22].

With this identification it becomes clear that within some intermediate concentration range $x_c > x > x_p$ of Ti on the B sites in the alloy $\text{BaZr}_{(1-x)}\text{Ti}_x\text{O}_3$, there will be a pseudo-spin glass transition at a critical temperature $T_g(x)$, marking the onset of non-ergodicity and preparation-dependence, the Zero-Field-Cooled (ZFC) susceptibility peaking and the Field-Cooled (FC) susceptibility ‘freezing’ [24]. Given that the FC susceptibility essentially measures a full Gibbs average over all pure states while the ZFC essentially measures the susceptibility restricted to a single pure macrostate [25] [26], this explains the corresponding observations of Akbarzadeh et al. [11], with their T_f identified as T_g , their $x = 0.5$ being within this relaxor/pseudo-spin-glass concentration range [8] and FC and ZFC corresponding to the two different susceptibility measurements they made [27].

For $x > x_c$ the transition is to ferroelectricity at a $T_c(x)$ that increases with x , reaching the pure BaTiO_3 value at $x = 1$. As x is decreased below x_c , T_g is expected also to decrease with x , but initially less quickly, until a further critical concentration x_p beyond which only paraelectricity exists as a thermodynamic phase; thus we have the sequence with increasing Ti concentration (x) paraelectric \rightarrow relaxor \rightarrow ferroelectric for $0 \leq x_p \leq x_c \leq 1$, [28], in accord with experiments [8, 9].

As noted earlier, the best known signature of relaxors is the feature of frequency-dependent peaks in the susceptibility as a function of temperature, with the peak temperature increasing with increasing frequency [5] [30]. It is observed experimentally for BZT [8–10]. A similar frequency-dependent peaking is also a well-known feature of spin glasses; see *e.g.* [31, 32]. In spin glasses it is also well-known that the peak temperature tends in the zero-frequency limit to that of the onset of non-ergodicity as measured by deviation of the FC and ZFC susceptibilities. Hence the mapping above would also lead one to expect this famous relaxor signature.

There has been much interest in the precursor observation (or interpretation) of ‘nano-domains’ in relaxors and these were also seen in the simulations of Akbarzadeh et al. [11], as well as in experiments [8]. They too can be understood from the above ‘induced-moment’ soft pseudo-spin modeling, as corresponding to longish-lived ‘local moments’ on statistically occurring clusters of Ti ions. To see this H and H_{eff} may be re-interpreted as Ginzburg-Landau free energies with their parameters renormalized as a function of temperature. The effective ‘local nano-domains’ are given by minimization with respect to the \mathbf{u}_i , yielding values given in simple mean field theory by

the self-consistent solution of

$$\tilde{\kappa}_i \mathbf{u}_i + 2\tilde{\lambda}_i \mathbf{u}_i |\mathbf{u}_i|^2 + \sum_j \partial \tilde{H}_{int}(\mathbf{u}_i, \mathbf{u}_j, \mathbf{R}_{ij}) / \partial \mathbf{u}_i = 0, \quad (4)$$

with all the terms effectively temperature-renormalized but with the most important conceptual feature that the $\{\tilde{\kappa}\}$ increase with increasing temperature relative to the interaction term. This equation is closely analogous to that for a mean field theory of cluster moment formation in transition metal alloys introduced in [20] and, similarly to that case, the formation of local nanodomains is relatable to an Anderson localization model [33, 34].

Simplifying for illustrative purposes to a simple scalar analog of eqn.(4) we consider

$$\tilde{\kappa}_i u_i + 2\tilde{\lambda}_i u_i^3 - \sum_j \tilde{J}_{ij} u_j = 0. \quad (5)$$

and compare it with an Anderson-type eigen-equation

$$\tilde{\kappa}_i \phi_i - \sum_j \tilde{J}_{ij} \phi_j = E \phi_i. \quad (6)$$

Non-zero u solutions to eqn.(5) correspond to solutions of eqn.(6) with $E < 0$. However, solutions to eqn. (6) with quenched κ -disorder can be either localized or extended; localized states at the extremities of the band of eigenstates separated from a region of extended states by lower $E_{mL}(x, T)$ and upper $E_{mU}(x, T)$ ‘mobility edges’. Note that the density of states and the mobility edges are temperature-dependent through the renormalization of the $\tilde{\lambda}$ and \tilde{J} , decreasing with decreasing T . Thus, the onset of mean-field ‘cluster moments’, observable on finite timescales as nano-domains, is given by the onset of solutions $E \leq 0$ to eqn.(6), while the true thermodynamic transition, which requires an extended state, occurs only when the mobility edge $E_{mL}(x, T)$ becomes zero.

While in the usual electronic Anderson situation the $\{\tilde{J}_{ij}\} \geq 0$ so that extended states are ferroelectric, in the present frustrated case with $\{\tilde{J}_{ij}\}$ of both signs the extended states can also be spin-glass-like [35] for finite x . This leads to the expectation of a true thermodynamic ferroelectric phase structure as temperature is lowered at high x , passing over to transition to a spin glass phase as x is reduced to a critical x_c and eventually beneath x_p exhibiting paraelectric behavior only, but also with higher temperature non-equilibrium nanodomain precursors for all $0 < x < 1$, the size of the precursor region reducing to zero as the pure limits are approached [36].

We might also note that in the Anderson analogy above quasi-frozen nano-regions need not necessarily be internally ferroelectric and indeed deviations from collinearity were observed in the simulations of [11].

The concept of polar nano-regions (PNRs) interacting among themselves and eventually freezing cooperatively macroscopically can, in principle, be given substance by defining nano-moments in terms of negative

eigenvalue eigenfunctions of eqn.(6), introducing them into an expanded partition function by adding them as variables with delta functions ensuring their identification and then integrating out the original variables [39].

Note that neither random fields nor random interactions were posited above [40, 41]. However, H_{eff} can be mapped into a random-bond model

$$H_{eff}^{EA} = \sum_l \kappa u_l^2 + \lambda u_l^4 + \sum_{lm} J_{lm} u_l u_m \quad (7)$$

where now the l are relabelled Ti sites, κ and λ are site-independent and all the randomness is in the $\{J_{lm}\}$. In a precise mapping the $\{J_{lm}\}$ code the spatial distribution of Ti ions. Following the conceptualization introduced by Edwards and Anderson [42] that the important physics of spin glasses is maintained as long as one retains frustration and quenched disorder, one would expect that a further assumption of independent randomness of $\{J_{lm}\}$ would maintain the crucial physics. However, to allow for the transition between ferroelectric and relaxor phases with x , the $\{J_{lm}\}$ distribution should have a tunable (x -dependent) mean [43, 44].

These analogies also suggest that, within the relevant intermediate range of x , BZT should exhibit other behaviors corresponding to those known for spin glasses, not only at the onset (where the susceptibility peaks), but also within the relaxor phase. Similar behavior and explanation might also be anticipated in other isovalent alloys of a frustrated displacive (or mixed displacive-weak order-disorder) ferroelectric (or antiferroelectric) and an appropriate paraelectric partner [45]. The corresponding analogy between hard dipolar (strong order-disorder) and other orientational glasses and hard spin glasses has long been recognised [46]; for reviews see [47] [48].

The modeling of eqn.(4) is of course only mean-field and so misses both thermal fluctuation effects and dynamics. However a similar extended simple modelling based on disorder only in local restoring terms and a spatially frustrated periodic interaction could in principle be extended to treat these.

Finally, it should be emphasised that the discussion above is minimal, a skeleton modeling to expose the physical core. More ‘flesh’ is needed for the whole body,

ACKNOWLEDGEMENTS

The author thanks Prof. Rasa Pirc for drawing his attention to [11] and for helpful comments on a first draft, Profs. Wolfgang Kleemann and Laurent Bellaiche for comments, information and references, and the Leverhulme Trust for the award of an Emeritus Fellowship.

-
- * D.Sherrington1@physics.ox.ac.uk
- [1] L.E.Cross. *Ferroelectrics* **76** 241 (1987)
 - [2] R.A.Cowley, S.N.Gvasaliya, S.G.Lushnikov, B.Roessli and G.M.Rotaru, *Adv.Phys.* **60** 229 (2011)
 - [3] In some cases A is also substitutionally alloyed.
 - [4] I.K. Jeong et al., *Phys.Rev.Lett* **94**, 147602 (2005)
 - [5] G.A.Smolenskii, V.A.Isupov, A.I.Agronayskaya and S.N.Popov, *Sov.Phys.Solid State* **2** 2584 (1961)
 - [6] V.Westphal, W.Kleemann and M.D.Glinchuk, *Phys.Rev.Lett.* **68**, 847 (1992), W.Kleemann and R.Lindner, *Ferroelectrics* **199** 1 (1997)
 - [7] A.Levstik, Z.Kutnjak, C.Filipić and R.Pirc, *Phys.Rev.B* **57**, 11204 (1998)
 - [8] T.Maiti, R.Guo and A.S.Bhalla, *J.Am.Cer.Soc.* **91**, 1769 (2008)
 - [9] V.V.Shvartsman, J.Zhai and W.Kleemann *Ferroelectrics* **379**, 77 (2009)
 - [10] W.Kleemann, S.Miga, J.Dec and J.Zai, *App.Phys.Lett.* **102**, 232907 (2013)
 - [11] A.R.Akbarzadeh, S.Prosandeev, E.J. Walter, A.Al-Barakaty and L.Bellaiche, *Phys.Rev.Lett.* **108**, 257601 (2012)
 - [12] See the supplemental material to [11]
 - [13] In fact, detailed theoretical/numerical studies of BaTiO₃ [14], of greater complexity than employed here, have exhibited a ferroelectric state that has features of both displacive and order-disorder type, as expected for an effective κ that is small and negative.
 - [14] W.Zhong, D.Vanderbilt and K.M.Rabe, *Phys.Rev.B* **52**, 6301 (1995)
 - [15] This is expected from the competing interactions in the ionic crystal, evidenced by the existence of ABO₃ antiferroelectrics, demonstrated in [14], and clearly needed for the spin-glass like behavior discussed here.
 - [16] J.A.Mydosh, *Spin Glasses: An Experimental Introduction* (Taylor and Francis 1993)
 - [17] This Hamiltonian can be re-expressed as $H = \sum_{i(Mag)} \{ \kappa |\mathbf{S}_i|^2 + \lambda |\mathbf{S}_i|^4 \} - \sum_{ij(Mag)} J(\mathbf{R}_{ij}) \mathbf{S}_i \cdot \mathbf{S}_j$ where for hard spins the limits $\kappa \rightarrow -\infty$, $\lambda \rightarrow \infty$ and $|\kappa|/\lambda \rightarrow \text{const.}$ are taken. A more general soft-spin formulation is commonly employed in theoretical studies of spin glasses, especially for dynamics [18]. A corresponding itinerant-electron (induced-moment/displacive) spin glass model - the Stoner glass - was studied in [19], while an equation analogous to eq.(1) with positive values of κ was earlier introduced in [20], in consideration of the magnetism of certain transition metal alloys.
 - [18] H.Sompolinsky and A.Zippelius *Phys.Rev.Lett.* **47**, 359 (1981)
 - [19] J.A.Hertz, *Phys.Rev.B* **19**, 4796 (1979)
 - [20] D.Sherrington and K.Mihill, *J.Physique Colloq.* **35**, C4-199 (1974); <http://dx.doi.org/10.1051/jphyscol:1974435>.
 - [21] In these alloys the Fe and Eu are the magnetic atoms.
 - [22] Note that the key necessary, but not automatically sufficient, ingredients for spin glass behavior are frustration and quenched disorder. In the case of metallic spin glasses, such as AuFe, the exchange interaction is long-ranged and oscillatory (RKKY) whereas for a semiconductor, such as EuSrS, the range is shorter and of different origin, but still greater than nearest neighbour and frustrated. For a brief theoretical perspective see [23].
 - [23] D.Sherrington, in *Spin Glasses*, eds. E.Bolthausen and A. Bovier, p 41-46, (Springer 2006)
 - [24] S.Nagata, P.H.Keesom and H.R.Harrison, *Phys.Rev.B* **19**, 1633 (1979)
 - [25] M.Mézard, G.Parisi and M.A.Virasoro, *Spin Glass Theory and Beyond* (World Scientific 1987)
 - [26] G.Parisi, in *Stealing the Gold*, eds. P.M.Goldbart, N.Goldenfeld and D.Sherrington, p 192-210, (Oxford University Press 2005)
 - [27] Note that the expression ‘relaxor’ is used both for a phase and also to label materials that exhibit this phase. Here the phase is being understood to be that in which ergodicity-breaking is observed, measured quantities depending on the protocol used to observe them.
 - [28] All three phases here warrant the qualifying adjective ‘displacive’ *c.f.* [29].
 - [29] A. R. Bishop et al., *Phys.Rev.B* **81**, 064106 (2010)
 - [30] These peaks mark the effective onset of non-ergodicity at the corresponding frequency.
 - [31] J.L.Tholence, *Physica B* **108**, 1287 (1981)
 - [32] G.V.Lecomte, H.von Löhneysen and E.F.Wassermann, *Z.Phys. B* **50**, 239 (1983)
 - [33] P.W.Anderson, *Phys.Rev.* **109**, 1492 (1958)
 - [34] P.W.Anderson, *Rev.Mod.Phys.* **50**, 191 (1978)
 - [35] Without any periodic order or macroscopic orientation.
 - [36] A similar picture of nanodomains as corresponding to localized states above the relaxor phase has been suggested before [37] but for quenched randomness in the $\{J_{ij}\}$ with $P(J_{ij}) = P(-J_{ij})$ and without the present simple mapping as the justification. As an example of the observation of quasi-localized nanodomains, corresponding to Anderson eigenstates below the mobility edge but without the explanation above, see [38].
 - [37] S.Nambu and K.Sugimoto, *Ferroelectrics* **198**, 11 (1997)
 - [38] I.Levin *et al.*, *Phys.Rev.B* **83**, 094122 (2011)
 - [39] One might note that these nano-moments need not necessarily all be internally collinear nor even have a finite overall polarization.
 - [40] We recall that [11] observed that turning off random field and random strain terms in their Hamiltonian does not significantly affect their results.
 - [41] This does not mean that random fields cannot be relevant, only that they are not needed for the present explanation.
 - [42] S.F.Edwards and P.W.Anderson, *J.Phys.F* **5**, 965 (1975)
 - [43] D.Sherrington and B.W.Southern, *J.Phys.F* **5**, L49 (1975)
 - [44] To emulate crudely the resultant interaction distribution and yield a transition sequence with increasing $x \in [0, 1]$ paraelectric→relaxor→ferroelectric one might take the mean $\overline{J_{ij}} = J_0 \sim x$ and the standard deviation $[(\overline{J_{ij}^2} - \overline{J_{ij}}^2)]^{1/2} = J \sim (x(1-x))^{1/2}$.
 - [45] The classic relaxor alloy PMN ($\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3$), however, is not isovalent and consequently has additional interactions, together with random fields, due to the excess charges of the Mg (-2) and Nb(+1), as compared with Ti in the ferroelectric template PbTiO_3 . Hence it requires further consideration.
 - [46] R. Brout, *Phys.. Rev. Lett.* **19**, 176 (1965)
 - [47] U.T.Hochli, K.Knorr and A.Loidl, *Adv.Phys.* **39**, 405 (1990)
 - [48] K.Binder and J.D.Reger, *Adv.Phys.* **41**, 547 (1992)