

AperTO - Archivio Istituzionale Open Access dell'Università di Torino

Effect of chemical composition and state of the surface on the toxic response to high aspect ratio nanomaterials (HARNS)

This is the author's manuscript

Original Citation:

Availability:

This version is available <http://hdl.handle.net/2318/90910> since 2016-11-30T09:39:10Z

Published version:

DOI:10.2217/nnm.11.80

Terms of use:

Open Access

Anyone can freely access the full text of works made available as "Open Access". Works made available under a Creative Commons license can be used according to the terms and conditions of said license. Use of all other works requires consent of the right holder (author or publisher) if not exempted from copyright protection by the applicable law.

(Article begins on next page)

"EFFECT OF CHEMICAL COMPOSITION AND STATE OF THE SURFACE ON THE TOXIC RESPONSE TO HIGH ASPECT RATIO NANOMATERIALS (HARNs)"

Summary

1 INTRODUCTION

1.1 Nanosized materials as a double sword

1.2 What makes a particle or a fiber toxic?

1.3 Why a specific study on HARNs

1.4 Not all fibers nor all HARNs are toxic

1.5 Materials considered

2 CARBON NANOTUBES

2.1 Carbon nanotubes: forms and chemical requirements for their applications.

2.2 Toxicity / biocompatibility of carbon nanotubes

2.3 Synthetic chrysotile asbestos nanotubes

2.4 Carbon Nanotubes vs. Asbestos

3 CARBON NANOFIBERS

4 METAL/OXIDE HARNs

4.1 Metal nanorods: the case of gold

4.2 Metal and oxide nanowires

5 Conclusions

6 Future Perspectives

7 Executive summary

FIGURES, CAPTIONS and TABLE

Bibliography

Summary

Nanomaterials often act as a double sword. On the one hand they offer new exceptional properties, on the other one show signs of toxicity. High Aspect Ratio Nanomaterials (HARNs) cause more concern than isometric nanoparticles because of their physical similarity with asbestos. Many compounds may be prepared in fibrous shape with nano-sized diameter differing one from the other in various ways. This review reports a comparative picture of the chemical features and related toxic responses to a variety of HARNs, namely carbon nanotubes, asbestos, carbon nanofibres, oxide and metal wires and rods. In spite of similarities in form, durability and several biological responses elicited in vitro and in vivo, carbon nanotubes, - opposite to asbestos - quench radicals, are hydrophobic and may be fully purified from metal impurities. Most of the other HARNs produced so far are metal or metal oxide compounds, less biopersistent than carbon nanotubes.

Key words: HARNs, Carbon Nanotubes, Carbon Wires, Asbestos, Gold Nanorods, Nanowires, Nano-Chrysotile, Free Radicals, Hydrophilicity/Hydrophobicity, Free Radical Generation, Free Radical Quenching, Nanotoxicology.

1 INTRODUCTION

1.1 Nanosized materials as a double sword

Nanotoxicology - the new discipline which parallels the enthusiastic development of nanotechnology - stems from the experience of different groups of scientists. When - about a decade ago - it became clear that appropriate methods in nanotechnology would have allowed the synthesis of nano particles in controlled shape and size, biomedical scientists were quite excited by the idea that such materials could become versatile devices for diagnostic, drug delivery or “intelligent” cancer cells killers. Beside medical applications several industries looked at the new materials such as carbon nanotubes as an excellent way to improve various productions by means of an extremely strong, nearly inert and light material.

In the mean time particle toxicologists and pathologists were alarmed by the possible exposure of workers and users to particles of unknown toxicity (which could be more pronounced on smaller particles than those traditionally studied), let alone the idea of a biopersistent particle being injected on purpose in the body [1-5]. On several occasions the media stressed the (potential) toxicity of nanoparticles but most unfortunately a general idea that any nanoparticle is hazardous just because of its size was retained, in spite of what reported in several books, reviews and experimental studies.

Information on the hazard associated to each kind of nanoparticles is much required in order to decide whether to develop its production, stop it, or at least provide sufficient precautionary procedures during production, use and disposal.

When it comes to nanomedicine only a correct balance between risks and benefits will allow to take sound decisions. For instance at the American Chemical Society Fall Meeting held in Boston in 2010 it was proposed to employ radioactive salts sealed inside carbon nanotubes for targeted radiotherapy. This is obtained by chemical modification of the surface of the tubes with sugar or other targeting molecules. The sugar could play a variety of roles, making the nanotubes soluble and stopping them from clumping together as well as providing a site for proteins to recognize. Sealed up carbon nanotubes with radioactive

salts inside would provide an excellent tool in targeted radiotherapy [6]. Under such circumstances any potential toxicity of the nanotube itself is not relevant, when compared to the benefit to reduce the tissue injury arising from traditional radiotherapy.

Clearly nano sized materials may act as a double sword as, on the one hand, they may fulfil several tasks never thought before, on the other one - because of several factors including their size - they may turn out to be a very hazardous material.

1.2 What makes a particle or a fibre toxic?

Particle and fibre toxicology is nowadays a relatively large field of toxicology involving several occupational and environmental issues. It is somehow an ancient discipline which has been deeply investigated in the last decades. Silicosis, the disease caused by crystalline silica dusts, is one of the most ancient occupational pathologies, reported by Hippocrates in 400 BC and by Plinio in 70 AD. Following a large number of studies the mechanism of action of silica at the molecular level has been partly clarified, even if some of the steps yielding the disease are still obscure or controversial because of the complexity of the physico-chemical features involved when the toxicant is in the solid state [7]. Beside silicosis several other particle or fibre associated pathologies are well known – e.g. asbestosis, mesothelioma, lung cancer, hard metal diseases - while there is not yet any medical evidence of “nanopathologies”, i.e. a pathology caused by a material because it is in nano-size.

Many signs of toxicity appear from in vitro and in vivo studies on some nanomaterials which suggest caution in their use, before they might damage human life and the environment. Traditional particle toxicology has clearly evidenced that the pathogenic response to an inhaled fibre does not concern a single step but is the sum of several subsequent events, each of which is determined by different physico-chemical features of the particle considered. Three major factors act together, namely the “form” of the particle, its crystal and surface composition and its biopersistence [8]. Form stands for fibrous vs isometric, nano vs. micron sized, smooth vs. indented, crystalline vs. amorphous particle. Biopersistence determines the time the particle remains unaffected into a given biological compartment, thus together with

the administered dose or the exposure determines the correct “dose”, meaning the extent of interaction of the body with that given material. Finally surface composition determines the nature of the contact of the particle with living matter, i.e. fluids cells and tissues. Surface reactivity, the potential to adsorb biomolecules, to disrupt cell membranes, to adhere to a given substrate are features derived from the chemical composition of a surface, which ultimately determine safety, biocompatibility or toxicity of a given kind of (nano) material.

1.3 Why a specific study on HARNs

HARNs is the term employed to indicate high aspect ratio - or fibre shaped – nanoparticles, a group of nanomaterials which deserve a specific approach [9]. They share with asbestos an elongated fibrous shape, one of the factors (associated to biopersistence and surface composition) which contributes to the high carcinogenic potential of asbestos.

The fibrous form has a specific role in toxicity as it is the cause of failed phagocytosis and of the translocation in various biological compartments, typically the parietal pleura. Macrophage clearance is one of the major route whereby the body defences get rid of unwanted foreign materials. Inhaled particles which do not damage the phagolysosome membrane may be easily engulfed by alveolar macrophages and transported to the lymphatics. When the material is in fibrous form the macrophage attempts often end up with frustrated phagocytosis and macrophage death, following the scheme reported in Figure 1, which may apply also to inflammatory reactions occurring in body compartments other than the lung. Long fibres cannot be phagocytosed, while the short ones are more easily uptaken and cleared, which explains the higher toxic potency of long vs. short fibres [9]. However beside fibre dimensions also surface reactivity determines the fate of the fibre and its ultimate toxicity [10] (Figure 1). In the case of isometric silica particles, for instance, surface reactivity determines reactions with the phagosome membrane and cell death [11].

There are nowadays several nanomaterials exhibiting one or two dimensions in the nanosize range - a typical example are respectively graphene sheets and carbon nanotubes - which make them different from “regular” isometric nanoparticles, having all three dimensions at the nanosize level.

Asbestos are the typical example of a material with exceptional properties, allowing an extremely large variety of employments (Figure 2), which turned out to be one of the greatest occupational tragedies of the XX century, still going on in the present days because of both, the latency of the asbestos associated diseases and the still increasing trade of this material worldwide (Russia, Canada, India, Brazil, China and other countries). In the case of HARNs no one would repeat what happened with asbestos, so that particular attention should be given to those HARNs who also share with them a high biopersistence and their other properties, including their surface reactivity.

The role of form and biopersistence in determining the pulmonary hazard of HARNs has been extensively reviewed by Donaldson et al. [9] and will here be just mentioned, while we will concentrate on the chemical aspects which may modulate the potential hazard of these materials caused by their shape.

It has to be pointed out that whilst in some cases materials non toxic at the micron size level may become toxic when synthesized at the nanolevel, there are few indications in the literature on what happens when well known solid toxicants are reduced from the micron size level to the nano-size one. In the case of crystalline silica only two studies have been performed so far, which indicate a lower toxicity of nanoquartz [12]. Titania nanorods turned out to be not more significantly toxic than isometric micron-sized particles [13].

In the case of asbestos there are no published studies; from an ongoing study in our laboratory we may anticipate that tests performed on natural chrysotile nanofibres indicate a reduction in toxic potency when passing from the micron to the nano size [unpublished results].

1.4 Not all fibres nor all HARNs are toxic

Some fibrous materials such as asbestos, the zeolite erionite, artificial ceramic fibres and others are highly toxic when micrometric fibres remain airborne and reach the lung alveoli and the pleura. Not all fibres however are equally toxic, some, e.g. wollastonite (CaSiO_3), are even inert [14]. A comparison of the toxicity of chrysotile asbestos with several other fibrous materials committed by WHO in 2005 [15] reported great differences in toxicity among the different materials. The available data on HARNs are still scarce to allow a similar study. In search of appropriate positive and negative controls for HARNs some of us have recently reported that imogolite, a hydrated alumino-silicate with the formula $(\text{OH})_3\text{Al}_2\text{O}_3\text{SiOH}$ [16] – opposite to carbon nanotubes - appears inactive in cell viability, NO production, and epithelial barrier permeability [17, 18].

1.5 Materials considered

We will report here what is known on most of the HARNs whose toxicity has been largely investigated: carbon based materials, such as carbon nanotubes (CNTs) and carbon nanofibers (CNFs) and metal / oxide based nanowires (NWs) and nanorods (NRs). CNTs, which are by far the most studied because of their potential applications on the one hand and of their close similarity to asbestos on the other one will be considered in detail. Because of a recent fear that CNTs might become the “asbestos” of the present century, we will compare physico-chemical features relatable to toxicity in CNTs and asbestos, highlighting not only similarities but also chemical differences.

Among the large variety of nanowires and rods prepared so far we will concentrate on the most investigated and applied ones - typically gold - and on a variety of metal/metal oxide compounds

The basic structures of the materials described are schematized in Figure 3 and their dimensional aspects depicted in Figure 4.

2 CARBON NANOTUBES

2.1 Carbon nanotubes: forms and chemical requirements for their applications.

CNTs are a form of elemental carbon. Like in fullerenes and graphite, carbon is organized in layers of hexagonal rings having conjugated double bonds (Figure 5A). Because of their high length/diameter ratio CNTs are comprised into the general term HARN. The discovery of CNTs is generally attributed to Iijima [19].

CNTs are made of one (single-walled SWCNT) or more (multi-walled MWCNT) graphene sheets rolled-up to form tubes. Depending upon the synthesis procedure CNTs may exhibit external diameters ranging between 1 to 200 nm. Their length may vary from nanometres to micrometers, depending upon the method of synthesis and may be modified by mechanical or chemical shortening. The graphene layers contain various amount and degree of defects [20] which may arise directly from the synthesis or may be introduced or eliminated *ad hoc*. After synthesis CNTs generally contain amorphous carbon, metals deriving from the catalyst used in their synthesis and inert materials (alumina or silica) used as support for the catalysts up to 20-30% w/w of the product. Only in extreme conditions a purification yields a 99% carbon content. Often metal ions remain on or within the carbon framework acting as a catalytic centre for free radical release or other reactions.

CNTs exhibit high thermal and mechanical resistance, electrical conductivity or semiconductivity. Such properties make CNTs interesting in a variety of industrial applications e.g. as component in electronics, energy-storage devices, solar cells, sensors, or in mechanical applications as filler in polymeric composites [21]. Their physico-chemical properties may be modulated by varying the method of synthesis and by applying post-synthesis treatments. Therefore a large variety of CNTs forms may be produced which exhibit different chemical reactivity one from the other.

The number of studies devoted to the production of new tailored forms of CNTs for the different industrial applications has exponentially increased, as shown in Figure 5B. Many forms of CNTs have shown

distinctive signs of toxicity, but the number of studies on their health effects compared in the histogram keeps well below that of their production.

The possibility to introduce functionalities at the surface of CNTs through radical reactions has attracted the interest of several scientists. Surface functionalization of CNTs in fact opens a wide range of applications [22, 23], e.g. by making CNTs compatible with aqueous media, by increasing their dispersion in polymeric matrixes, or by binding specific molecules to their surface.

MWCNTs find application mainly as components in high strength composites while SWCNTs are currently studied for their conducting/semiconducting properties in electronic devices, and as biosensors.

CNTs also attract a great interest for several applications in medicine [24-26]. CNTs rapidly cross the cell membranes like fullerenes, which makes them apt to act as nanovectors [27, 28]. In such application chemical modifications are required to impart hydrophilicity and bind drugs or biomolecules [29]. CNTs in bulk materials have been proposed as alternative artificial hard tissues [30], as tissue scaffold materials for bone formation [31], as microcatheters [32] or as substrates for neuronal growth in nervous system disorders [33, 34].

2.2 Toxicity / biocompatibility of carbon nanotubes

CNTs are currently object of a large debate on their toxicity/biocompatibility. Several extensive reviews on this topic have been published. We refer to them for a detailed discussion [35-40].

Overall a substantial consensus has not been reached yet, mainly because of controversial data obtained in the different studies. Such variability in the toxic effect elicited by CNTs has mostly to be ascribed to the differences in shape and chemical composition/modifications of CNTs employed in the different studies [17, 41-47].

It is generally accepted that physical and chemical properties modulate the cell responses toward CNTs. Differences in toxic responses have been observed to be related to length [28, 48], presence of metals [42], oxidation of the surface [49, 50], presence or absence of defects [50, 51], tube diameter di-

mensions [52, 53]. However very few studies have been designed to relate physico-chemical determinants to the toxic response to CNTs by testing a large set of samples differing for one single property at the time. This kind of approach allowed the assignment to defects - among other properties – of lung toxicity and genotoxicity [50, 51]. For the time being therefore toxicity needs to be assessed for each kind of nanotube employed and the clues to synthesize safe CNT materials have not yet been disclosed.

The major alarm raised on CNTs toxicity in the past decade concerns their physical similarity with asbestos, namely form and durability. Several studies have been devoted to assess whether CNTs are able to induce neoplastic transformations in mesothelial cells similarly to asbestos fibers. Conflicting data were obtained [54], as both ability to induce mesothelioma [45, 46] and absence of carcinogenic response [55] were reported. Such variable outcomes may be ascribed to different physical chemical properties among the examined specimens. The next two paragraphs are therefore devoted to describe synthetic asbestos and to a systematic comparison between asbestos and CNTs.

2.3 Synthetic chrysotile asbestos nanotubes

Stoichiometric chrysotile tubular nanocrystals have been recently, synthesized [56] as possible starting materials for applications in nanotechnology and as a standard reference sample for the investigation of the molecular interactions between chrysotile asbestos and biological systems. Each single nanocrystal of pure chrysotile has a tubular shape of about 49 nm in outer maximum diameter, a hollow core of about 7 nm and a length of the order of some microns. The presence of iron does not change the tubular shape of nanocrystals which appear just slightly longer than the iron free ones. Iron ions replace both Mg and Si into the octahedral and tetrahedral sheets [57].

Free radical generation and the effect of pure nano-chrysotile on human lung epithelial A549 cells have been compared to that elicited by a well known toxic natural chrysotile (UICC A, from Rhodesia). After a 24-h incubation, the natural, but not the synthetic form exerted a cytotoxic effect, detected as leakage of lactate dehydrogenase. Generation of carbon centred radicals in cell free tests and lipoperoxidation on lung epithelial cells took place in the presence of the natural, but not of the synthetic chrysotile. Anti-

oxidant systems were also affected differently. The pentose phosphate pathway and its regulatory enzyme glucose 6-phosphate dehydrogenase were markedly inhibited only by the natural specimen, which also caused a depletion of intracellular reduced glutathione in A549 cells [58]. Similarly, synthetic chrysotile nanofibers, devoid of iron, did not exert genotoxic and cytotoxic effects nor elicited oxidative stress in a murine alveolar macrophage cell line [59]. Briefly all the properties relatable to toxicity were absent in the synthetic form.

To gain direct experimental evidence of the chemical role of iron in asbestos reactivity a set of nanochrysotiles have also been synthesized with 0.6% and 0.9% (w/w) iron by means of the same procedure [60]. Even the lowest iron-loading induced DNA strand breaks, lipoperoxidation, inhibition of redox metabolism and alterations of cell integrity, i.e. the same toxic characteristics of natural chrysotile [59]. These results suggest that metal ions play a crucial role in the oxidative stress and genotoxic effects caused by chrysotile asbestos.

Accurate analysis over a set of iron loaded samples revealed that generation of hydroxyl radical and carbon centred radicals are catalyzed by iron ions in specific crystallographic sites [61]. Even the smallest iron contamination may impart radical reactivity. The most reactive surface sites in carbon centred radical generation are isolated iron ions in octahedral coordination in both axial and rhombic distortion. Conversely, the mechanism of OH^\bullet generation seems to be independent of the iron lattice distortion. Aggregated iron ions and/or extra-framework clustering are less reactive in both mechanisms. Moreover carbon centred radical generation requires iron in low oxidation state or iron in high oxidation state but easily reducible to iron(II) by endogenous reducing agents, e.g. ascorbic acid.

The studies above described constitute the first direct experimental confirm of the role played by isolated iron ions within the asbestos framework in free radical release and cell damage.

2.4 Carbon Nanotubes vs. Asbestos

Carbon nanotubes share with asbestos some relevant properties relatable to asbestos pathogenicity such as their “fibrous” habit and a high biopersistence (reviewed by Donaldson et al. [9]). The possibility

that carbon nanotubes would show asbestos-like behaviour in the human body was raised several years ago [62]. More recently, some experiments *in vivo* have been performed to evidence any asbestos-like pathogenic response, such as a persistent inflammation or the induction of mesothelioma, which is a disease only caused by asbestos and few other mineral fibres [45-47].

Poland and co-workers [47] showed that MWCNTs injected directly into the abdominal cavity of mice induce inflammation, formation of granulomas and early fibrosis or scarring in the mesothelial lining. Shorter nanotubes had much less of an effect, as did carbon black nanoparticles used as a non-fibrous reference material. Inflammation and granulomatous lesions elicited by long CNTs were similar to those induced by long fibres of amosite asbestos. Tagaki and co-workers [45] even showed that MWNTs injected, in a large volume, into the abdominal cavity of mice induce malignant mesotheliomas in p53+/- heterozygous mice — a common genetically engineered mouse model with an increased propensity to toxicity induced cancer. Mesothelioma induction was finally observed also after a single intrascrotal administration of multi-wall carbon nanotube in intact male Fischer 344 rats [46]. At the opposite Muller et al. [55] reported that crocidolite induced a clear carcinogenic response while MWCNT with or without structural defects did not induce any mesothelioma in male Wistar rats. It has to be pointed out that the above experiments were performed with CNT preparations differing in form, length and level of contaminants, which might account for the different outcomes.

Several reviews have recently been devoted to the comparison between CNT and asbestos [36, 39, 63-65]. They mostly consider the physical similarities such as shape and chemical stability in a physiological environment and report several outcomes in various cell systems and in *in vivo* rodent models. Few reviews [63, 64] also mention some chemical aspects - surface properties, presence of metal transition ions, adsorptive potential- in relation with the toxicological properties reported (cell derived ROS, cytotoxicity, DNA damage, physical interference with mitosis, stimulation of target cell proliferation and induction chronic inflammation). Other focus on activation of macrophages and injury on epithelial / mesothelial cells [65], and on the potential to activate signaling pathways modulating transcription factor activity, inducing apoptosis and DNA damage [39] without considering at all the differences in chemical properties.

Most comparisons of CNTs are made with crocidolite asbestos [39]. Interestingly Jaurand et al report that chrysotile is the asbestos form more close to CNTs. In fact most CNTs are curled and flexible in similar way to chrysotile, but different from amphiboles.

In conclusion while the CNTs - asbestos analogy was mainly raised because of some points of physical similarity, we will here give a detailed description of the chemical differences and similarities between the two entities. We recall here that in the case of isometric nanoparticles surface chemistry and particularly the formation of Reactive Oxygen Species (ROS) plays a crucial role in toxicity, thus by the same token, chemical aspects in HARNs behavior need to be considered in detail [4,8,13,17].

2.4.1 Chemical composition of CNTs and asbestos: differences and similarities

Asbestos are naturally occurring hydrated silicates. They belong to two mineralogical groups: serpentine (chrysotile) and amphiboles (actinolite, amosite, anthophyllite, crocidolite, and tremolite). The amphibole minerals are composed of octahedrally coordinated cations sandwiched between two double silicate layers. The oxygen atoms of the silicate chains coordinate both Si and other cations (Mg^{2+} , Fe^{2+} , Fe^{3+}). Chrysotile is composed of an octahedral magnesium hydroxide layer, the so-called brucitic layer, intercalated between silicate tetrahedral layers which form tightly rolled sheets [66].

CNTs are allotropes of carbon exhibiting a surface made up by a rolled hexagonal lattice of carbon atoms linked by σ and π covalent bonds.

Both CNTs and asbestos have a thin and elongated shape, compatible with a fibrous morphology according to the WHO definition. The CNTs diameter ranges from 0.4 to 3 nm for SWCNT and from 2 to 200 nm for MWCNT [2, 35, 67]. The diameter of single chrysotile fiber falls below 100 nm whereas in crocidolite and amosite (amphiboles) is about 200 nm [68].

One of the most prominent chemical difference between the two materials lies in their opposite degree of hydrophilicity /hydrophobicity. Asbestos are all very hydrophilic materials because of both the metal ions exposed (positive surface charges) and the silicon-oxygen bonds, giving rise to silanols (SiOH)

when exposed at the surface in presence of moisture. Silanols coordinate water molecule and establish strong H-bonding with several other molecules [69]. The presence of metal ions exposed to the surface creates an uneven distribution of charges, resulting in acid Lewis sites of variable strengths, which strongly attract polar molecules and constitute the active site where catalytic generation of free radicals might take place.

At the opposite CNTs, unless oxidized or functionalized, are highly hydrophobic therefore incompatible with water [51]. Few hydrophilic surface sites may originate from metal traces from the catalyst exposed at the surface or upon strong oxidation. As prepared CNTs are tightly bound in aggregates or bundles because of Van der Waals attractive forces among graphene sheets [70, 71]. In aqueous media they form large agglomerates [72]. Dispersion in water may be improved introducing a sufficient number of charged functionalities at the surface to generate repulsion among particles. In the past few years, *in vivo* bio-distribution studies have been carried out by a number of groups using different tracking methodologies [73]. As observed for molecular substances the hydrophilic character and the presence of charged functionalities modified the pharmacokinetic profile of nanoparticles. Additionally, for nanoparticles, diameter, length/diameter ratio and tendency to form aggregates are expected to play a role [74]. We recall here that protein adsorption, cell uptake and translocation depend upon the hydrophilic/hydrophobic degree [75].

2.4.2 Metal ions and surface generation vs. quenching of free radicals and ROS on asbestos and CNTs

Metals are considered important elements to account for fibre toxicity [76, 77]. All asbestos fibres contain iron, either structural (crocidolite, amosite), as a consistent part of the crystal framework, or as contaminant (chrysotile, tremolite) substituting e.g. Mg^{+2} ions, which share with Fe^{+2} size and charge. Iron in asbestos fibres can be present in both ferrous (Fe^{+2}) and ferric (Fe^{+3}) form within the asbestos crystal structure.

Depending on the method of production CNTs may also contain iron and other different redox active metals (e.g. Co, Ni, Mo) as a residue of the catalyst employed in their synthesis [35]. The amount is highly variable, and may reach 20% in unpurified CNTs [78]. Metals may be present in different oxidative states as ions, clusters or even organized in metal nanoparticles. Kim and co-workers analyzed some samples of CNTs in which iron was found as a mixture of $\alpha\text{-Fe}^0$, $\gamma\text{-Fe}^0$, and carbide phases [79]. The metal residues may be extracted from CNT, e.g. by an acidic treatment, but often few traces remain. A full elimination of any metal trace may be achieved by heating at extremely high temperatures where the metal vaporize. Such purified samples were successfully employed to distinguish the effect of metals or framework defects in causing lung toxicity and genotoxicity in vitro [50, 51].

Pioneer work by Pezerat and co-workers hypothesized more than two decades ago a crucial role for iron in asbestos toxicity [80, 81]. The role of iron in the induction of oxidative stress and toxicity upon exposure to asbestos fibres was confirmed by a number of studies [73, 82-84]. Iron ions involved in free radical generation are those present at the fibre surface in a poorly coordination state [85] [61, 86, 87] or those easily removable (bio-available) [76, 88]. Since iron sealed within the graphene layers cannot be released in the medium [89], the amount of bio-available iron in CNTs varies greatly from sample to sample and cannot be predicted from total iron content [78]. As a consequence of such variability, conflicting data are found with CNTs, as both ROS production [42, 90-92] and scavenging (see below) were described [51, 93, 94].

Fiber-derived free radicals contribute with cell-derived free radicals to the overall asbestos-induced oxidative stress. Asbestos have been shown to induce ROS generation in cell cultures [82, 95] as consequence of both highly reactive surface iron ions [84] and of frustrated phagocytosis [96, 97].

Several in vitro studies using different cell lines suggest that also CNTs may induce ROS generation and oxidative stress in cellular system models [42, 98-102]. Frustrated phagocytosis was observed by Brown and coworkers with CNT [103] but metal ions play the most important role in oxidative stress [42, 100]. In

fact when pure carbon nanotubes are administered to cultured cells, ROS generation did not occur [90, 94].

Oxygenated free radicals easily react with CNTs similarly to fullerenes. Such reactivity makes CNTs promising as antioxidant agents. Several studies report an antioxidant activity of CNTs in polymeric composites, which preserves the polymeric matrix from degradation [104]. Purified MWCNTs were reported by some of us to scavenge hydroxyl radicals and superoxide anion [105]. A decrease in reactive oxygen species found in vivo was assigned to the scavenging potential of purified MWCNTs [94]. Recent studies report an antioxidant activity of pristine and modified SWCNTs [106]. The antioxidant properties of CNTs could find applications in medicine. An antioxidant therapy may be suggested in several diseases where mitigation of oxidative stress is beneficial, e.g. cardiovascular diseases and neurodegenerative disorders [107]. To be employed in such way, however, CNTs need to be efficiently delivered to the organ/tissue of interest, then cleared when their function is over. Theoretical calculations reported that the scavenging activity of SWCNTs may be modulated by introducing defects [20] or by varying their diameter, length, and chirality [108-110]. Experimental studies are needed to confirm such hypothesis.

Conversely an uncontrolled antioxidant activity may damage cells. Reduction of the physiological free radical levels may in fact lead to impairment of the cellular physiological functions since free radicals have a key role in cellular proliferation and in host defence [111].

2.4.3 Biopersistence, biodistribution and translocation

Biopersistence may be related to the toxic potential of particulates. The longer a hazardous fiber or particle remains unaffected into a given biological compartment, the longer the biological response elicited might persist over time. Somehow biopersistence would thus enhance the “dose”, not the nature of the caused damage. Well-known particulate toxicants such as asbestos or quartz are characterized by a high biopersistence which exacerbates their toxic effects [8]. Biopersistence is also crucial for nanoparticles used in diagnosis and therapy. On the one hand a safe material should not be modified in the body,

on the other one, as a foreign body should be eliminated, as quickly as possible, once its task is completed. In this case a controlled pharmacokinetic profile is needed.

Note that at the opposite biopersistence is searched when nanomaterials are used as permanent prosthetic devices.

Biopersistence in the lung is the result of the clearance mechanisms and interactions with the biological medium, both related to the structure and chemistry of the material. For amosite and crocidolite estimated clearance half-times are measured in years to decades, whereas for chrysotile the majority of fibres are cleared within months, although some fibres may be sequestered and slowly cleared [112]. The brucitic layer makes the chrysotile acid-sensitive. Fibres that reach the lung can undergo focal fibre fragmentation [113, 114] in the acidic (pH 4.5) phagolysosome of macrophages [115]. Conversely, amphiboles exhibit a more complex chemical composition and a higher stability [116].

In vivo experiments showed that MWCNTs persist in the lung for some months [41, 44, 117]. Because of their graphitic structure CNTs are highly insoluble [118] and it has been suggested that they may be as biopersistent as amphiboles [64]. However, the CNT durability may vary depending to surface defects or functionalization, e.g. surface carboxylation reduced CNT durability [73]. Insertion of COO groups, in fact, causes collateral damage to the graphenic structure introducing active sites that provide points of attack for oxidative degradation. Oxidative degradation may take place in cellular compartments e.g. reactive oxygen species produced by alveolar macrophages following phagocytosis [73]. A possible degradation of SWCNT by myeloperoxidase, an enzyme involved in the generation of reactive oxygen species in neutrophils, was also reported [119]. However as the physiological oxidizing environment is not very harsh chemical degradation may require long times. Using an in vitro flow through assay with phagolysosomal simulated fluid at pH 4.5, SWCNTs have been shown to persist for several months [120]. Conversely, strong oxidants such as nitric acid or hydrogen peroxide may cause a partial degradation of CNTs and have been used for shortening processes [121]. If confirmed in vivo, these studies may open the door to a safe use of CNT in medicine. However, whether such degradation processes would be sufficient to prevent ad-

verse side effects of CNTs as well as the efficiency of the process on the various types of CNTs (SW vs. MW, short vs. long) remains to be clarified.

Asbestos fibres and CNTs are both subjected to macrophagic and lymphatic clearance [44, 122, 123]. Long asbestos fibres ($> 10 \mu\text{m}$) are slowly cleared as they cannot be easily enclosed by macrophages leading to frustrated phagocytosis. Frustrated phagocytosis was observed in cells engulfing long and well dispersed CNTs [47, 103]. Conversely, short CNTs or long CNTs in tangled forms do not pose a problem to macrophages [28]. Likewise, CNT aggregates are usually easily phagocytosed [28]. Note that single walled CNTs are more likely to tangle while multi walled ones tend to maintain a rigid shape.

Inhaled asbestos fibres are detected in lung, lymph nodes, pleura and peritoneum of the exposed peoples. The shorter fibres ($< 2\mu\text{m}$) were observed in the lymph nodes and in the pleural plaques [124].

Biodistribution of CNTs after deposition in the lung has been poorly investigated. As macrophage clearance, both translocation and biodistribution of CNTs are modulated by the aggregation state [43, 125-127]. Short MWCNTs were observed in the lung and in the lymph nodes after intratracheal instillation like short asbestos fibres [44]. No passage from the alveolar space to the systemic circulation and systemic organs (liver, spleen, and kidneys) was detected for CNTs [126].

One controversial point on CNTs toxicity is their ability to reach the pleura. Asbestos fibres are able to translocate to the pleural cavity, causing pleural effusion, fibrosis and mesothelioma. Ryman-Rasmussen [128] showed that MWCNTs reach the subpleura in mice after inhalation exposure. Mercier [129] and co-workers observed a distribution of MWCNTs into the subpleural tissue and the intrapleural space after pharyngeal aspiration.

Kane and co-workers [130] noted that long asbestos fibres accumulated preferentially at the peritoneal face of the diaphragm around the stomata (pore like structures less than $10 \mu\text{m}$ in diameter linking the peritoneal cavity to the underlying lymphatic capillaries). Retention of long fibres at the diaphragmatic mesothelial surface could initiate inflammation, proliferation and granuloma formation [131]. Poland [47]

showed that also long CNTs accumulate at the diaphragm, following instillation in the peritoneal cavity, which would suggest that they are too long or bulky to exit through the stomata [132].

2.4.4 Final remarks

In conclusion CNTs are a rapidly growing family of carbon based materials having large differences in their physico-chemical properties. Moreover most of their applications require surface modifications (covalent grafting, surface functionalization, coatings) which increase the variety of physico-chemical characteristics, by fully modifying surface properties. The relationship between the above mentioned physico-chemical features of CNTs and the toxic responses at the molecular level is still an area of large interest, being the basis of the possible design of CNT-based biocompatible materials.

As to CNTs similarity with asbestos the above data clearly show several differences at the chemical level, in spite of similar physical features which vary from one to the other CNT specimen considered. Table 1 compares asbestos and CNTs as far as the physico-chemical features most relevant to toxicity are concerned.

3 CARBON NANOFIBERS

Carbon nanofibers (CNFs) is a general term used to describe filaments comprised of graphene layers stacked at an angle to the fibre axis. They have lengths in the order of micrometers (up to 200 μm), and diameters ranging from some tens of nanometre up to ca. 200 nm. Graphene layers may be arranged as stacked cones, cups [133] or plates. In the last case three types of CNFs may be recognized, depending on the size and orientation of the graphene layers within their structure: platelet (alignment perpendicularly to the fibre axis), tubular (alignment parallel to the axis), and herringbone (alignment angled to the axis) [134, 135].

Excellent mechanical, electrical and surface properties make CNFs ideal candidates for a wide range of applications such as structural materials, field emission displays, hydrogen storage materials, tips for scanning probe microscopy, nanometre sized semiconductor devices and sensors. Several applications in

biomedical and regenerative medicine are known. The presence of many reactive sites allows selective functionalization to immobilize proteins, enzymes, and DNA, for biosensor preparation. CNFs have also been considered for hard (e.g., orthopaedic and dental) and soft (e.g., cartilage, tendon, vascular) tissue implants and they have been already used as regenerative scaffolds for neural and bone regeneration or as drug and gene delivery vehicles [136].

Adsorption, translocation, excretion of CNFs are expected to be close to what happens with CNTs [64]. Note that a high variability was observed for CNFs [103]. In a biological system, in fact, the absorption, distribution, metabolism, and toxicity of carbon nanomaterials depend on the inherent physical and chemical characteristics such as functionalization, coating, length, and agglomeration state which is influenced by external environmental conditions [137]. Exposure to CNFs could take place following biomedical applications or occupational exposure [136]. Airborne CNFs were found in several manufactures [138] and the exposure preferably occurs through inhalation, although dermal exposure cannot be excluded. To date, however, there is a lack of information on whether CNFs can be absorbed across the skin's stratum corneum barrier. Several reports indicate that carbon fibres may cause dermatitis [139, 140], suggesting that carbon nanomaterials may entry into the viable epidermis after topical exposure [141]. The stratum corneum is the outermost layer of the epidermis and consists of several layers of completely keratinized dead cells, which form a barrier between the "milieu interieur" and the outside environment. However, disease or occupational conditions that cause damage to the stratum corneum barrier (e.g. abrasion, solvent exposure) may abrogate these protective functions.

Because of their graphitic structure CNFs are highly insoluble thus highly biopersistent. Due to their strong chemical stability CNFs are not expected to be broken down when inhaled [142]. Nevertheless Yokoyama [143] studied a new hydrophilic type of carbon nanofiber for application to biomaterials. Such nanofibers, named hat-stacked CNFs, because of the novel arrangement where the singles carbon layer of the graphite structure are similar to stacked hats (graphene hats), implanted in the subcutaneous tissue of rats showed a shortening with time, likely due to delaminating of graphene layers. Delamination, which occurred in lysosomes and cytoplasm, could have originated from the intercalation of hydrophilic sub-

stances such as enzymes and proteins. Intercalations is possible because of the rich functional groups at the edges of the graphene hats [143].

CNFs may subjected to macrophagic clearance. Long CNFs may induce frustrated phagocytosis, escape clearance by normal mechanism and persist in the lung. Although they may exhibit different structure (Figure 3), CNFs usually show a strong tendency to agglomerate and form bundles in aqueous media mainly because of their hydrophobicity. Agglomerates of small dimension (few micrometers) might be easily engulfed by macrophage or other cells. Interestingly monocytic cells treated with CNFs entangled into aggregates of about ten microns in diameter do not exhibit signs of incomplete uptake, unlike monocytic cells treated with straight and well dispersed CNTs [103].

Several studies show that the cytotoxicity of CNFs is very low [144, 145] or even absent [103]. Cytotoxicity might be related to the presence of few dangling bonds - i.e. unpaired electrons in a free orbital arising from the homolytic rupture of the carbon-carbon bonds. As they may easily form new bonds they constitute highly reactive sites [146]. Analysis of the dose-dependent toxicity of different carbon based materials (CBN) in human lung-tumour cell lines revealed that the number of viable cells decreases as a function of dose for all CBN tested. The number of viable cells decreased in the sequence carbon black > CNFs > CNTs. Dangling bonds are present in carbon black with a high density, whereas in carbon nanotubes they preferentially occur at the lattice defects and at end caps [146]. CNFs exhibit more reactive sites than CNTs. In fact, they have more graphene edge planes, which are ledges of carbon that protrude from the surface at regular intervals, that could lead to easier physical bonding with other materials [147]. Surface modifications to improve dispersion in biological media, which results in adding carbonyl, carboxyl, and/or hydroxyl groups, increase CNF cytotoxicity [146].

CNFs did not significantly produce ROS in mouse keratinocytes [144], nor in acellular tests. A weak increase dose dependent of $O_2^{\bullet-}$ production was observed in monocyte cells by Brown and co-workers [103]. Dose response was higher for platelet CNFs than for a platelet/herringbone CNF mixed sample, suggesting implication of the graphene structure.

Metal impurities induce ROS generation by CNFs. Formation of OH[•] radicals was observed in macrophages after few minutes of exposure to CNF containing about 1% of iron. Radical release increased upon addition of H₂O₂ suggesting a metal-dependent Fenton reaction [148].

CNFs have a low inflammatory potential. Platelet and platelet/herringbone CNFs did not stimulate inflammatory cytokines such as TNF- α (tumour necrosis factor) in monocyte cells [103]. Hat stacked CNFs (H-CNFs), modified with carboxyl groups in order to improve their dispersion showed only a induction of TNF- α [30]. One week after implantation in the subcutaneous tissue of rats, H-CNFs caused granulomatous inflammatory change, but not an acute severe inflammatory reaction [30].

Lindberg and co-workers [145] compared the potential genotoxic of CNTs, containing < 5%wt of Co and Mo, and graphite nanofibers containing < 3% wt of Fe. Genotoxicity was assessed by the comet and the micronucleus assay in human bronchial epithelial cells. While CNTs induced a dose-dependent increase in DNA damage at all dose and treatment times, graphite nanofibers induced DNA strand breaks and chromosomal damage in human bronchial epithelial only after long time of treatment with no dose dependence.

Conversely CNFs containing iron impurities (<1.4% wt) showed a genotoxicity comparable with asbestos and stronger than SWCNT (Fe < 0.23%) [148]. The authors hypothesized that CNFs cause genotoxicity via two different mechanisms: i) by production of ROS, likely via Fenton reaction, which in turn react readily with DNA and ii) by physically interfering with DNA/chromosomes and/or the mitotic apparatus.

4 METAL/OXIDE HARNs

With the tremendous advances on the capacity to manipulate the unique physicochemical properties of nanoscaled systems with varied composition we may foresee that soon many metals and oxides will be prepared in form of HARNs for different applications, including diagnostic or therapeutic purposes [27]. An increasing number of nanorods and nanowires of several metals and metal oxides have now been studied and sometime already available to the market. Among the nanorods, we will report here only on

the most studied ones with intended applications in nanomedicine: i.e. gold nanorods. The paragraph devoted to nanowires has been more generally focused on the many studies dealing with metal and metal-oxide nanowires relevant in nanomedicine.

4.1 Metal nanorods: the case of gold

Gold nanostructures are often used as a model system since their physical and chemical properties can be easily manipulated [149]. Gold nanorods (Au NRs) are one kind of most promising and widely utilized materials owing to their biocompatibility and optical tunability [150]. Au NRs are usually synthesized with relative low aspect ratio but high aspect ratio (length/diameter > 11) have recently been prepared. Many applications of high aspect ratio Au NRs have been proposed [151] as useful object in nanomedicine: tools for cellular imaging, molecular diagnosis and targeted thermal therapy.

Wet chemical synthesis of gold nanorods is the most popular route to prepare these nanomaterials and it requires the use of cetyltrimethylammonium bromide (CTAB) as shape-directing surfactant, which forms a bilayer on the surfaces of gold nanorods [152, 153]. Au nanorods toxicity, uptake, circulation and distribution has been thoroughly investigated in different labs and from different points of view [154, 155]. Surface modification of cetyltrimethylammonium bromide (CTAB)-stabilized gold nanorods is primarily reported as a method to demote inherent toxicity of Au NRs [156]. CTAB is indeed a well-established agent promoting cellular toxicity of Au NRs, thus many studies claim to substitute it with other less toxic coatings [154, 157]. There is not a clear consensus, however, on the mechanism of CTAB-induced cytotoxicity, which can be due either to free CTAB in solution (Connor [157, 158], or to the simultaneous effect of CTAB molecules in solution and at the Au NRs surface [154]. Unfortunately the removal of the CTAB bilayer results in suspension instability and nanorod agglomeration. Some strategies - still to be found- are required to replace, stabilize CTAB or coating Au with other less toxic surfactants. A great attention has been devoted to the formation of specific chemical interfaces surroundings Au NRs. The modification of each of these interfaces provides strategies for altering nanorod properties such as stability against aggregation, toxicity, and ease of assembly. Murphy and co-workers [159] clarify that three interfaces are relevant in tailoring Au NRs properties: i) the gold-surfactant interface, ii) the hydrophobic

surfactant bilayer, and iii) the surfactant interface with bulk water. The last one - the solvent-accessible interface - dictates nanorod interactions with other particles, macromolecules, and living cells.

According to several authors, the effect of the Au NRs aspect ratio is relevant in terms of cellular uptake, rather than being the actual cause of cytotoxicity. In human breast adenocarcinoma cells (MCF-7) shorter Au NRs seem to be easier to internalize than longer ones [154]. This is believed to be a protein receptor mediated endocytosis process and appears to be energy dependent [160, 161]. A set of Au NRs with different aspect ratio and surface charge was tested on human colon cancer cell line (HT-29) [157]. The authors report that serum proteins from the culture media - most likely bovine serum albumin - adsorb to Au NRs leading to all nanorod samples bearing the same effective charge, regardless of the initial surface charge. This confirms that surface properties of nanomaterials change substantially after coming into contact with protein-rich solution media [162, 163]. A clear consensus has not yet been achieved about the role of surface charge in cellular uptake. Some studies report plays a significant role [154], while for others surface charge seems not to bear the expected importance in driving uptake and modulating toxicity [157, 164].

The promising synthesis of nanoscale hybrid HARNs, e.g. Au-nanorod/SWCNT/Au-nanorod [165], will make the assessment of molecular mechanism of toxicity of these nano-objects a further entangled maze.

4.2 Metal and oxide nanowires

Nanowires (NWs) are one dimensional nanostructures, with diameter constrained to tens of nanometres or less and an unconstrained length. The aspect ratio is usually very high and NWs with AR > 1000 are currently produced. Many chemically different types of nanowires exist: metallic (e.g., Ni, Pt, Au), semiconducting (e.g., Si, GaN) and oxides (e.g., SiO₂, TiO₂). NWs include single-crystalline homostructures as well as heterostructures of at least two single-crystalline materials having different chemical compositions. Generally, there are two basic morphologies in nanowire heterostructures: radial, such as core-shell nanowires, and axial heterostructures, comprising multisegment nanowires. The peculiar electrical properties due to their size make NWs suitable to build the next generation of computing devices.

578 NWs may also be readily functionalized with various biomolecules including enzymes, antibodies or nucle-
579 ic acids, thus being good candidates for several biomedical applications. NWs with different segments
580 along the length provide the opportunity to introduce multiple chemical functionalities by exploiting the
581 selective binding of different ligands to the various segments. Such functionalization imparts catalytic and
582 recognition/binding properties onto NWs, that can be used as nanosensors for detection of biological and
583 chemical species (metal ions, viruses, proteins etc) and as nanocarriers (gene carriers for non-viral gene
584 delivery, antibodies conjugated carriers for specific binding to malignant cells and in vivo targeting of
585 breast tumours) [166, 167]. Unfortunately little is known to date regarding the potential toxicity of this
586 type of nanomaterial.

587 As for the other HARNs, size, surface charge and surface coating are important parameters in deter-
588 mining how NWs uptake occurs in mammalian cells. The cellular uptake of NWs can occur through one of
589 the following cell-dependent pathways: phagocytosis, receptor-mediated endocytosis and pinocytosis
590 [168]. Macrophages are specialized cells able to perform phagocytosis of NWs. To date, the only available
591 study on phagocytosis of NWs was performed by Muller et al. [169]. They observed that ZnO NWs from 4
592 to 10 μm in length, with at high tendency to form aggregates, are easily phagocytosed by human monocyte
593 macrophages. Internalization via receptor-mediated endocytosis was proposed by some authors [170,
594 171]. Chou [171] also observed that NWs with length longer than the diameter of cells are internalized by
595 a single cell if in bundles and by multiple adjacent cells if well dispersed and in straight form.

596 Finally, Song and co-workers observed that short Fe NWs ($< 2 \mu\text{m}$), with positive surface charge, in-
597 troduced into the cell culture medium, migrate to the cell surface under electrostatic attraction [172] and
598 are internalized via a pinocytosis process. Instead, long Fe NWs (5 μm) are internalized only if perpendicu-
599 lar to the cell membrane. The authors speculated that the long NWs were similar to nanoneedles, which
600 could perforate and diffuse through the lipid bilayer of cell membrane without inducing cell death. This
601 kind of uptake process has been observed for cellular uptake of carbon nanotubes [173].

Some studies examining different NWs indicate a low cytotoxic potential and high biocompatibility [174-177]. Exposure of human and bovine epithelial cells to SiO₂ NWs at low concentrations (40 µg/ml) resulted in no cytotoxicity [174], which is quite relevant considering that most silicas are indeed cytotoxic [11, 178]. High concentration (>100 µg/ml) of SiO₂ NWs only modestly reduced cell viability in different cell types [175-177]. Examination of the mechanisms responsible for SiO₂ NW-induced cytotoxicity indicates that apoptotic pathways are not activated and that cytotoxicity appears to be primarily due to increased necrosis [176, 177]. However, even at the highest concentration tested SiO₂ NWs revealed a lower cytotoxicity than amorphous SiO₂ NPs ad hoc synthesized in the same lab [176]. These results indicate that structural differences between silica nanomaterials can have dramatic effects on interaction of these nanomaterials with cells.

Structurally a NW surface differs from the surface of a isometric NP mainly for the presence of a large number of edges induced by the few nanometre small curvature radius. The poorly bound atoms at the edge are a primary source of lattice defects, which are usually reported to enhances surface reactivity.[17] If compared to planar native oxides, SiO₂ NWs are capable of much larger surface hydroxylation when exposed to aqueous media. The high hydroxyl group concentration on the surface makes NWs more hydrophilic and less prone to aggregation than SiO₂ nanoparticles [179]. Differences in the aggregation may also contribute to the observed differences in cytotoxicity.

Low cytotoxicity have been observed also on several metal NWs. Iron NWs (average diameter and length 50 nm and 2-5 µm) have no significant effect on cell proliferation of human epithelial cells from cervical carcinoma. Nickel NWs (20 µm long and 200 nm in diameter) do not affect the viability of human monocytic leukaemia cells [180], nor of osteoblast and osteosarcoma cells [170]. The authors suggest that a critical factor for the high survival rate may be the presence, in both cases, of the 3–4 nm oxide layers. The oxide layer reduces metal ions release in the cells that may be responsible for the toxic effects elicited [181].

ZnO NWs were found to be toxic to human monocyte macrophages [169]. However, ZnO NWs dissolved very rapidly in a simulated body fluid at lysosomal pH, whereas they were comparatively stable at extracellular pH. NWs dissolution was observed also after phagocytosis, triggered by the acidic pH within the phagolysosome. The authors indicated Zn^{2+} release as responsible for ZnO NWs cytotoxicity. Conversely, no toxicity - measured as cell viability and morphological changes - was observed in human cervical epithelial cells and in cell from subcutaneous connective tissue cultured with ZnO NWs (average diameter and length 1 μm and 200 μm) [182] where the pH is expected to be close to neutral. Therefore, the ZnO NWs toxicity is clearly linked to their solubility, which is in turn pH-dependent, making the toxicity of this material strictly related to the biological environment.

The effect of surface charge on cytotoxicity to fibroblasts and neoplastic tissue cells has been examined for several gold NWs of few micrometer in length. NWs have been functionalized by a monolayer of thiols with amino, alkyl, or carboxyl end groups, or coated with serum. Amino-modified NWs exhibit positive zeta potential, whereas a negatively charged surface is obtained for the mercapto-acid-modified NWs. Mercapto-acid modified NWs, which exhibit the more negative zeta potential, have been found to be the most toxic ones [183] on both fibroblast cells and HeLa cell. Several aspects could account for this surface charge dependent cytotoxicity, e.g. a better dispersion in culture media, a more specific interaction with cell membranes. However, contradictory data are still reported in the literature and an ultimate reason has not yet been found.

Similar results have been obtained with 5 μm long silver NWs with different coatings. At low concentration, the higher cytotoxicity was observed for negatively charged surfaces. At the higher concentrations, all NWs were cytotoxic [183]. Finally, mercapto-acid modified gold NWs with length from 0.5 to 9 μm and aspect ratios from 1:2, 1:10, 1:25, and 1:50 exhibited the same degree of cytotoxicity [184].

5 Conclusions

The mere fibrous form is not sufficient to establish the toxicity of a given type of HARNs. The chemical nature of HARNs varies remarkably from one to the other materials and covers all types of chemical bond-

ing, from covalent to metallic and ionic. The most relevant characteristics of the materials described are illustrated and compared in Table 2. Many of them may be prepared in different forms and modified in their surface properties, which further expands the chemical varieties. Length, flexibility and surface modifications appear to modify the potential toxicity of many of the substances examined in the present review.

Carbon nanotubes, both MWCNTs and SWCNTs are hazardous in most of the forms examined. Moreover several studies agree on a large number of similarities between CNTs and asbestos, in spite of relevant chemical differences which have been here highlighted.

With metal and metal oxide materials the potential to release metal ions in the biological environment is one property of concern, with the only exception of gold and likely of other noble metals which might be considered in the future. As a whole the oxide layer protects from cytotoxicity and the elongated form does not appear to enhance toxicity.

We are proceeding but still far from finding a clue to disclose what makes a nano fibre toxic, which will be the first step to establish the requirements for a design of new safer materials. In the meanwhile each new material will need to be tested for toxicity before being produced and used.

6 Future Perspectives

As not all what is nano is dangerous, with the large number of studies appearing on nanomaterials and their potential toxicity the list of hazardous materials and of the physico-chemical properties involved in the adverse biological responses will be progressively implemented. On the basis of such data possible associations between given physico-chemical properties and toxic effects may be sorted out. Finally by preparing and testing a large number of given HARN – e.g. MWCNTs -differing one from the other in one single physical chemical characteristic, it will be possible to disclose what may make such material dangerous and how to prepare safe ones of similar kind. Appropriate positive and negative controls will also be required in such procedures.

675 More studies on CNT toxicity are needed considering the industrial interest in their usage and the fear
676 associated to their health effects. Common protocols (sample preparation, endpoint, markers) and full
677 physical-chemical characterization will be required for any future toxicological study. New in vitro and ex
678 vivo studies on tailored CNTs will shed more light on their toxicity and potential carcinogenicity. Eventual-
679 ly in vivo studies where CNTs will be administered to experimental animals with different and reliable pro-
680 cedures will allow establishing or ruling out CNTs carcinogenicity and confirming damage to lung func-
681 tions. Hopefully we will not need epidemiology to establish toxicity. Under such circumstances it will be
682 possible to verify which of the large kind of CNTs, if any, are carcinogenic to animals and possible human
683 carcinogens.

684 Tailored chemical modification of the exposed surface may be found to convert potentially hazardous
685 HARNs in non toxic entities. However such modifications will need to be persistent over long periods of
686 time in biological environments. Therefore the research will be addressed more on irreversible chemical
687 modifications than on any sort of coatings.

688 Considering the vast chemical nature of HARNs so far synthesized, any new one will need to be tested
689 for toxicity before being produced and used. However once toxicity tests will have been performed for
690 such a large variety of materials, it might be possible to draw general hypothesis on the chemical charac-
691 teristics to avoid and those which yield safe products

692 **7 *Executive summary***

693 ➤ **High Aspect Ratio Nanomaterials**

- 694 ▪ HARNs are a large variety of materials with different chemical composition and shape.
- 695 ▪ Concerns about their safety are mainly related to their fibrous form and high biopersistence,
- 696 but their chemical nature may also play an additional role.

697 ➤ **Carbon nanotubes**

698 ▪ SWCNT and MWCNT are both covalent solids which may retain some metals in a variable oxi-
699 dation state as a residue of the catalysts used in their synthesis.

700 ▪ Overall, a clear indication of toxicity came out of studies on currently available CNTs. Caution
701 in handling is therefore necessary.

702 ▪ New investigations aimed to identify the physico-chemical determinants of toxicity should be
703 carried out considering that the variability in the toxic responses elicited stems from the dif-
704 ferences in physico-chemical features.

705 ➤ **CNT modifications**

706 ▪ Due to the nature of the carbon-carbon bonds CNTs may relatively easily oxidized and func-
707 tionalized with a large variety of molecules, giving rise to very different entities.

708 ▪ surface modifications may modulate the biological responses elicited

709 ➤ **Asbestos vs. CNTs**

710 ▪ The similarity between asbestos and CNTs concerns not only some physical features but also
711 several cellular responses and in vivo damages.

712 ▪ Their chemical nature is however remarkably different as far as free radical release / quench-
713 ing or hydrophilicity is concerned.

714 ▪ Evidence for the development of mesothelioma following CNTs exposure is still weak and
715 needs to be assessed with different administration routes and long term animal experiments.

716 ➤ **Nanorods and nanowires**

717 ▪ Gold nanorods are by far the most studied and widespread. The biological responses elicited
718 much depends upon their coating.

719 ▪ A large variety of oxides and metal are available as nanowires. Metals have few oxide layers at
720 their surface. Their toxicity appears not to exceed what found with isometric nanoparticles of
721 the same composition. In the case of silica a nanowire was even less cytotoxic than isometric
722 silica nanoparticles.

723

724

Bibliography

- 726 1. Oberdorster G, Stone V, Donaldson K: Toxicology of nanoparticles: A historical perspective. *Nano-*
727 *toxicology* 1(1), 2-25 (2007).
- 728 2. Oberdorster G, Maynard A, Donaldson K *et al.*: Principles for characterizing the potential human
729 health effects from exposure to nanomaterials: elements of a screening strategy. *Particel and Fi-*
730 *bre Toxicology* 2, 8 (2005).
- 731 3. Oberdorster G, Oberdorster E, Oberdorster J: Nanotoxicology: An emerging discipline evolving
732 from studies of ultrafine particles. *Environmental Health Perspectives* 113(7), 823-839 (2005).
- 733 4. Nel A, Xia T, Madler L, Li N: Toxic potential of materials at the nanolevel. *Science* 311(5761), 622-
734 627 (2006).
- 735 5. Maynard A, Rejeski D: Too small to overlook. *Nature* 460(7252), 174-174 (2009).
- 736 6. Hong SY, Tobias G, Al-Jamal KT *et al.*: Filled and glycosylated carbon nanotubes for in vivo radioe-
737 mitter localization and imaging. *Nature Materials* 9(6), 485-490 (2010).
- 738 7. Fubini B: Surface reactivity in the pathogenic response to particulates. *Environmental Health Per-*
739 *spectives* 105, 1013-1020 (1997).
- 740 8. Fubini B, Fenoglio I: Toxic potential of mineral dusts. *Elements* 3(6), 407-414 (2007).
- 741 9. Donaldson K, Murphy F, Schinwald A, Duffin R, Poland CA: Identifying the pulmonary hazard of
742 high aspect ratio nanoparticles to enable their safety-by-design. *Nanomedicine* 6(1), 143-156
743 (2011).
- 744 ** The latest and the most extensive review on the role of length and bioperisistance in determining the
745 toxic response to HARNs
- 746
- 747 10. Tomatis M, Turci F, Ceschino R *et al.*: High aspect ratio materials: role of surface chemistry vs.
748 length in the historical "long and short amosite asbestos fibers". *Inhalation Toxicology* 22(12),
749 984-998 (2010).
- 750 11. Ghiazza M, Polimeni M, Fenoglio I, Gazzano E, Ghigo D, Fubini B: Does Vitreous Silica Contradict
751 the Toxicity of the Crystalline Silica Paradigm? *Chemical Research in Toxicology* 23(3), 620-629
752 (2010).
- 753 12. Warheit DB, Webb TR, Colvin VL, Reed KL, Sayes CR: Pulmonary bioassay studies with nanoscale
754 and fine-quartz particles in rats: Toxicity is not dependent upon particle size but on surface char-
755 acteristics. *Toxicological Sciences* 95(1), 270-280 (2007).
- 756 13. Warheit DB, Reed KL, Sayes CM: A role for nanoparticle surface reactivity in facilitating pulmonary
757 toxicity and development of a base set of hazard assays as a component of nanoparticle risk man-
758 agement. *Inhalation Toxicology* 21 Suppl 1, 61-67 (2009).
- 759 14. Maxim LD, Mcconnell EE: A review of the toxicology and epidemiology of wollastonite. *Inhalation*
760 *Toxicology* 17(9), 451-466 (2005).
- 761 15. Who: Workshop on Mechanisms of Fibre Carcinogenesis and Assessment of Chrysotile Asbestos
762 Substitutes - Consensus report. (2005).
- 763 16. Bonelli B, Bottero I, Ballarini N, Passeri S, Cavani F, Garrone E: IR spectroscopic and catalytic char-
764 acterization of the acidity of imogolite-based systems. *Journal of Catalysis* 264(1), 15-30 (2009).
- 765 17. Fubini B, Ghiazza M, Fenoglio I: Physico-chemical features of engineered nanoparticles relevant to
766 their toxicity. *Nanotoxicology* 4(4), 347-363 (2010).
- 767 18. Bussolati O, Rotoli BM, Zanello PP *et al.*: Nanotubes of the Aluminosilicate Imogolite exhibit mild
768 Toxicity for Macrophages and Airway Epithelial Cells. *Particle and Fibre Toxicology*, (submitted).
- 769 19. Iijima S: HELICAL MICROTUBULES OF GRAPHITIC CARBON. *Nature* 354(6348), 56-58 (1991).
- 770 20. Galano A, Francisco-Marquez M, Martinez A: Influence of Point Defects on the Free-Radical Scav-
771 enging Capability of Single-Walled Carbon Nanotubes. *Journal of Physical Chemistry C* 114(18),
772 8302-8308 (2010).
- 773 21. Endo M, Strano MS, Ajayan PM: Potential applications of carbon nanotubes. *Carbon Nanotubes*
774 111, 13-61 (2008).

22. Hirsch A, Vostrowsky O: *Functionalization of carbon nanotubes*. In: *Functional Molecular Nanostructures*, (Ed.^(Eds). Springer-Verlag Berlin, Berlin 193-237 (2005).
23. Banerjee S, Hemraj-Benny T, Wong SS: Covalent surface chemistry of single-walled carbon nanotubes. *Advanced Materials* 17(1), 17-29 (2005).
24. Lacerda L, Bianco A, Prato M, Kostarelos K: Carbon nanotubes as nanomedicines: From toxicology to pharmacology. *Advanced Drug Delivery Reviews* 58(14), 1460-1470 (2006).
25. Liu CH, Zhang HL: Chemical approaches towards single-species single-walled carbon nanotubes. *Nanoscale* 2(10), 1901-1918 (2010).
26. Zhang YN, Zheng LX: Towards chirality-pure carbon nanotubes. *Nanoscale* 2(10), 1919-1929 (2010).
27. Kostarelos K: The emergence of nanomedicine: a field in the making. *Nanomedicine* 1(1), 1-3 (2006).
28. Raffa V, Ciofani G, Vittorio O, Riggio C, Cuschieri A: Physicochemical properties affecting cellular uptake of carbon nanotubes. *Nanomedicine (Lond)* 5(1), 89-97 (2010).
29. Cheung W, Pontoriero F, Taratula O, Chen AM, He H: DNA and carbon nanotubes as medicine. *Advanced Drug Delivery Reviews* 62(6), 633-649 (2010).
30. Sato Y, Shibata K, Kataoka H *et al.*: Strict preparation and evaluation of water-soluble hatstacked carbon nanofibers for biomedical application and their high biocompatibility: influence of nanofiber-surface functional groups on cytotoxicity. *Molecular Biosystems* 1(2), 142-145 (2005).
31. Zanello LP, Zhao B, Hu H, Haddon RC: Bone cell proliferation on carbon nanotubes. *Nano Letters* 6(3), 562-567 (2006).
32. Koyama S, Haniu H, Osaka K *et al.*: Medical application of carbon-nanotube-fitted nanocomposites: The microcatheter. *Small* 2(12), 1406-1411 (2006).
33. Hu H, Ni YC, Montana V, Haddon RC, Parpura V: Chemically functionalized carbon nanotubes as substrates for neuronal growth. *Nano Letters* 4(3), 507-511 (2004).
34. Roach P, Parker T, Gadegaard N, Alexander MR: Surface strategies for control of neuronal cell adhesion: A review. *Surface Science Reports* 65(6), 145-173 (2010).
35. Donaldson K, Aitken R, Tran L *et al.*: Carbon nanotubes: a review of their properties in relation to pulmonary toxicology and workplace safety. *Toxicol.Sci.* 92(1), 5-22 (2006).
36. Kane AB, Hurt RH: Nanotoxicology: The asbestos analogy revisited. *Nature Nanotechnology* 3(7), 378-379 (2008).
- ** Injection of long MWCNT into the abdominal cavity of mice produces asbestos-like pathogenic behaviour. A thorough discussion about analogies and differences between asbestos and CNTs is reported
37. Kostarelos K: The long and short of carbon nanotube toxicity. *Nature Biotechnology* 26(7), 774-776 (2008).
38. Shvedova AA, Kisin ER, Porter D *et al.*: Mechanisms of pulmonary toxicity and medical applications of carbon nanotubes: Two faces of Janus? *Pharmacology & Therapeutics* 121(2), 192-204 (2009).
- * The first paper specifically devoted to the discussion of positive and detrimental aspects of CNTs
39. Pacurari M, Castranova V, Vallyathan V: Single- and multi-wall carbon nanotubes versus asbestos: are the carbon nanotubes a new health risk to humans? *J Toxicol Environ Health A* 73(5), 378-395 (2010).
40. Lison D, Muller J: Untitled. *Toxicological Sciences* 101(1), 179-180 (2008).
41. Muller J, Huaux F, Moreau N *et al.*: Respiratory toxicity of multi-wall carbon nanotubes. *Toxicology and Applied Pharmacology* 207(3), 221-231 (2005).
42. Kagan VE, Tyurina YY, Tyurin VA *et al.*: Direct and indirect effects of single walled carbon nanotubes on RAW 264.7 macrophages: role of iron. *Toxicol Lett* 165(1), 88-100 (2006).
43. Ma-Hock L, Treumann S, Strauss V *et al.*: Inhalation Toxicity of Multiwall Carbon Nanotubes in Rats Exposed for 3 Months. *Toxicological Sciences* 112(2), 468-481 (2009).
44. Elgrabli D, Floriani M, Abella-Gallart S *et al.*: Biodistribution and clearance of instilled carbon nanotubes in rat lung. *Particle and Fibre Toxicology* 5, (2008).

45. Takagi A, Hirose A, Nishimura T *et al.*: Induction of mesothelioma in p53+/- mouse by intraperitoneal application of multi-wall carbon nanotube. *J Toxicol Sci* 33(1), 105-116 (2008).
46. Sakamoto Y, Nakae D, Fukumori N *et al.*: Induction of mesothelioma by a single intrascrotal administration of multi-wall carbon nanotube in intact male fischer 344 rats. *J Toxicol Sci* 34, 65-76 (2009).
47. Poland CA, Duffin R, Kinloch I *et al.*: Carbon nanotubes introduced into the abdominal cavity of mice show asbestos-like pathogenicity in a pilot study. *Nature Nanotechnology* 3(7), 423-428 (2008).
48. Kolosnjaj-Tabi J, Hartman KB, Boudjemaa S *et al.*: In Vivo Behavior of Large Doses of Ultrashort and Full-Length Single-Walled Carbon Nanotubes after Oral and Intraperitoneal Administration to Swiss Mice. *Acs Nano* 4(3), 1481-1492 (2010).
49. Vittorio O, Raffa V, Cuschieri A: Influence of purity and surface oxidation on cytotoxicity of multi-walled carbon nanotubes with human neuroblastoma cells. *Nanomedicine-Nanotechnology Biology and Medicine* 5(4), 424-431 (2009).
50. Muller J, Huaux F, Fonseca A *et al.*: Structural defects play a major role in the acute lung toxicity of multiwall carbon nanotubes: Toxicological aspects. *Chem Res Toxicol* 21, 1698-1705 (2008).
- * The authors show that varying one properties at the time on MWCNTs is possible to single out the ultimate feature involved in pulmonary toxicity: the occurrence of structural defects.
51. Fenoglio I, Greco G, Tomatis M *et al.*: Structural defects play a major role in the acute lung toxicity of multiwall carbon nanotubes: Physicochemical aspects. *Chem Res Toxicol* 21, 1690-1697 (2008).
52. Wang X, Jia G, Wang H *et al.*: Diameter Effects on Cytotoxicity of Multi-Walled Carbon Nanotubes. *Journal of Nanoscience and Nanotechnology* 9(5), 3025-3033 (2009).
53. Yamashita K, Yoshioka Y, Higashisaka K *et al.*: Carbon Nanotubes Elicit DNA Damage and Inflammatory Response Relative to Their Size and Shape. *Inflammation* 33(4), 276-280 (2010).
54. Johnston HJ, Hutchison GR, Christensen FM *et al.*: A critical review of the biological mechanisms underlying the in vivo and in vitro toxicity of carbon nanotubes: The contribution of physicochemical characteristics. *Nanotoxicology* 4(2), 207-246 (2010).
55. Muller J, Delos M, Panin N, Rabolli V, Huaux F, Lison D: Absence of Carcinogenic Response to Multiwall Carbon Nanotubes in a 2-Year Bioassay in the Peritoneal Cavity of the Rat. *Toxicological Sciences* 110(2), 442-448 (2009).
56. Falini G, Foresti E, Gazzano M *et al.*: Tubular-shaped stoichiometric chrysotile nanocrystals. *Chemistry-A European Journal* 10(12), 3043-3049 (2004).
57. Foresti E, Fornero E, Lesci IG, Rinaudo C, Zuccheri T, Roveri N: Asbestos health hazard: a spectroscopic study of synthetic geoinspired Fe-doped chrysotile. *J Hazard.Mater* 167(1-3), 1070-1079 (2009).
58. Gazzano E, Foresti E, Lesci IG *et al.*: Different cellular responses evoked by natural and stoichiometric synthetic chrysotile asbestos. *Toxicol.Appl.Pharmacol.* 206(3), 356-364 (2005).
59. Gazzano E, Turci F, Foresti E *et al.*: Iron-loaded synthetic chrysotile: A new model solid for studying the role of iron in asbestos toxicity. *Chemical Research in Toxicology* 20(3), 380-387 (2007).
60. Foresti E, Hochella MF, Kornishi H *et al.*: Morphological and chemical/physical characterization of Fe-doped synthetic chrysotile nanotubes. *Adv Funct Mater* 15(6), 1009-1016 (2005).
61. Turci F, Tomatis M, Lesci IG, Roveri N, Fubini B: The Iron-Related Molecular Toxicity Mechanism of Synthetic Asbestos Nanofibres: A Model Study for High-Aspect-Ratio Nanoparticles. *Chemistry-a European Journal* 17(1), 350-358 (2011).
- * The first direct experimental evidence of the role of isolated iron ions in the asbestos cellular toxicity.
62. Service RF: Nanotubes:the next asbestos? *Science* 281(5379), 941-942 (1998).
63. Jaurand M-CF, Renier A, Daubriac J: Mesothelioma: Do asbestos and carbon nanotubes pose the same health risk? *Particle and Fibre Toxicology* 6, (2009).
- ** An extensive review of asbestos carcinogenic mechanisms in relation to their similarities and differences with CNTs.

- 881 64. Sanchez VC, Pietruska JR, Miselis NR, Hurt RH, Kane AB: Biopersistence and potential adverse
882 health impacts of fibrous nanomaterials: what have we learned from asbestos? *Wiley Interdisci-*
883 *plinary Reviews-Nanomedicine and Nanobiotechnology* 1(5), 511-529 (2009).
- 884 65. Nagai H, Toyokuni S: Biopersistent fiber-induced inflammation and carcinogenesis: lessons
885 learned from asbestos toward safety of fibrous nanomaterials. *Arch Biochem Biophys* 502(1), 1-7
886 (2010).
- 887 66. Veblen DR, Wylie AG: Mineralogy of Amphiboles and 1/1 Layer Silicates. *Rev Mineral* 28, 61-137
888 (1993).
- 889 67. Warheit DB: What is currently known about the health risks related to carbon nanotube expo-
890 sures? *Carbon* 44(6), 1064-1069 (2006).
- 891 68. Timbrell V, Gibson JC, Webster I: UICC standard reference samples of asbestos. *Int.J.Cancer* 3(3),
892 406-408 (1968).
- 893 69. Fubini B, Bolis V, Cavenago A, Garrone E, Ugliengo P: STRUCTURAL AND INDUCED HETEROGENEI-
894 TY AT THE SURFACE OF SOME SIO₂ POLYMORPHS FROM THE ENTHALPY OF ADSORPTION OF VAR-
895 IOUS MOLECULES. *Langmuir* 9(10), 2712-2720 (1993).
- 896 70. Girifalco LA, Hodak M, Lee RS: Carbon nanotubes, buckyballs, ropes, and a universal graphitic po-
897 tential. *Physical Review B* 62(19), 13104-13110 (2000).
- 898 71. Peigney A, Laurent C, Flahaut E, Bacsá RR, Rousset A: Specific surface area of carbon nanotubes
899 and bundles of carbon nanotubes. *Carbon* 39(4), 507-514 (2001).
- 900 72. Wick P, Manser P, Limbach LK *et al.*: The degree and kind of agglomeration affect carbon nano-
901 tube cytotoxicity. *Toxicol Lett* 168(2), 121-131 (2007).
- 902 73. Liu XY, Hurt RH, Kane AB: Biodurability of single-walled carbon nanotubes depends on surface
903 functionalization. *Carbon* 48(7), 1961-1969 (2010).
- 904 74. Choi HS, Frangioni JV: Nanoparticles for Biomedical Imaging: Fundamentals of Clinical Translation.
905 *Molecular Imaging* 9(6), 291-310 (2010).
- 906 75. Fenoglio I, Fubini B, Ghibaudi E, Turci F: Multiple aspects of the interaction of biomacromolecules
907 with inorganic surfaces. *Adv. Drug Deliv. Rev.*, (submitted).
- 908 76. Aust AE, Lund LG, Chao CC, Park SH, Fang RH: Role of iron in the cellular effects of asbestos. *Inha-*
909 *lation Toxicology* 12, 75-80 (2000).
- 910 77. Aust AE: Role of iron in the biological effects of asbestos. *Abstracts of Papers of the American*
911 *Chemical Society* 224, U732-U732 (2002).
- 912 78. Guo L, Morris DG, Liu X, Vaslet C, Hurt RH, Kane AB: Iron bioavailability and redox activity in di-
913 verse carbon nanotube samples. *Chemistry of Materials* 19(14), 3472-3478 (2007).
- 914 79. Kim H, Sigmund W: Iron particles in carbon nanotubes. *Carbon* 43(8), 1743-1748 (2005).
- 915 80. Zalma R, Guignard J, Copin E, Pezerat H: Studies on surface properties of asbestos. IV. Catalytic
916 role of asbestos in fluorene oxidation. *Environmental Research* 41(1), 296-301 (1986).
- 917 81. Pezerat H, Zalma R, Guignard J, Jaurand MC: Production of oxygen radicals by the reduction of ox-
918 ygen arising from the surface activity of mineral fibres. *IARC scientific publications* (90), 100-111
919 (1989).
- 920 82. Kamp DW, Weitzman SA: The molecular basis of asbestos induced lung injury. *Thorax* 54(7), 638-
921 652 (1999).
- 922 83. Hardy JA, Aust AE: Iron in asbestos chemistry and carcinogenicity. *Chemical Reviews* 95(1), 97-118
923 (1995).
- 924 84. Shukla A, Gulumian M, Hei TK, Kamp D, Rahman Q, Mossman BT: Multiple roles of oxidants in the
925 pathogenesis of asbestos-induced diseases. *Free Radical Biology and Medicine* 34(9), 1117-1129
926 (2003).
- 927 85. Fubini B, Mollo L: Role of iron in the reactivity of mineral fibers. *Toxicology Letters* 82-3, 951-960
928 (1995).
- 929 86. Martra G, Tomatis M, Fenoglio I, Coluccia S, Fubini B: Ascorbic acid modifies the surface of asbes-
930 tos: Possible implications in the molecular mechanisms of toxicity. *Chemical Research in Toxicolo-*
931 *gy* 16(3), 328-335 (2003).
- 932 87. Turci F, Favero-Longo SE, Tomatis M *et al.*: A biomimetic approach to the chemical inactivation of
933 chrysotile fibres by lichen metabolites. *Chemistry-a European Journal* 13(14), 4081-4093 (2007).

- 934 88. Hardy JA, Aust AE: The effect of iron-binding on the ability of crocidolite asbestos to catalyze DNA
935 single-strand breaks. *Carcinogenesis* 16(2), 319-325 (1995).
- 936 89. Liu SW, Tang XH, Mastai Y, Felner I, Gedanken A: Preparation and characterization of iron-
937 encapsulating carbon nanotubes and nanoparticles. *Journal of Materials Chemistry* 10(11), 2502-
938 2506 (2000).
- 939 90. Pulskamp K, Diabate S, Krug HF: Carbon nanotubes show no sign of acute toxicity but induce in-
940 tracellular reactive oxygen species in dependence on contaminants. *Toxicology Letters* 168(1), 58-
941 74 (2007).
- 942 91. Jacobsen NR, Pojana G, White P *et al.*: Genotoxicity, cytotoxicity, and reactive oxygen species in-
943 duced by single-walled carbon nanotubes and C(60) fullerenes in the FE1-Mutatrade markMouse
944 lung epithelial cells. *Environ Mol Mutagen* 49(6), 476-487 (2008).
- 945 92. Folkmann JK, Risom L, Jacobsen NR, Wallin H, Loft S, Moller P: Oxidatively damaged DNA in rats
946 exposed by oral gavage to C60 fullerenes and single-walled carbon nanotubes. *Environ Health Per-
947 spect* 117(5), 703-708 (2009).
- 948 93. Porter DW, Hubbs AF, Mercer RR *et al.*: Mouse pulmonary dose- and time course-responses in-
949 duced by exposure to multi-walled carbon nanotubes. *Toxicology* 269(2-3), 136-147 (2010).
- 950 94. Crouzier D, Follet S, Gentilhomme E *et al.*: Carbon nanotubes induce inflammation but decrease
951 the production of reactive oxygen species in lung. *Toxicology* 272(1-3), 39-45 (2010).
- 952 95. Vallyathan V, Mega JF, Shi XL, Dalal NS: Enhanced generation of free-radicals from phagocytes in-
953 duced by mineral dusts. *American Journal of Respiratory Cell and Molecular Biology* 6(4), 404-413
954 (1992).
- 955 96. Mossman BT, Kamp DW, Weitzman SA: Mechanisms of carcinogenesis and clinical features of as-
956 bestos-associated cancers. *Cancer Investigation* 14(5), 466-480 (1996).
- 957 97. Manning CB, Vallyathan V, Mossman BT: Diseases caused by asbestos: mechanisms of injury and
958 disease development. *Int.Immunopharmacol.* 2(2-3), 191-200 (2002).
- 959 98. Manna SK, Sarkar S, Barr J *et al.*: Single-walled carbon nanotube induces oxidative stress and acti-
960 vates nuclear transcription factor-kappa B in human keratinocytes. *Nano Letters* 5(9), 1676-1684
961 (2005).
- 962 99. Monteiro-Riviere NA, Inman AO, Wang YY, Nemanich RJ: Surfactant effects on carbon nanotube
963 interactions with human keratinocytes. *Nanomedicine* 1(4), 293-299 (2005).
- 964 100. Pacurari M, Yin XJ, Zhao J *et al.*: Raw single-wall carbon nanotubes induce oxidative stress and ac-
965 tivate MAPKs, AP-1, NF-kappa B, and Akt in normal and malignant human mesothelial cells. *Envi-
966 ronmental Health Perspectives* 116(9), 1211-1217 (2008).
- 967 101. Sharma CS, Sarkar S, Periyakaruppan A *et al.*: Single-walled carbon nanotubes induces oxidative
968 stress in rat lung epithelial cells. *Journal of Nanoscience and Nanotechnology* 7(7), 2466-2472
969 (2007).
- 970 102. Shvedova AA, Castranova V, Kisin ER *et al.*: Exposure to carbon nanotube material: Assessment of
971 nanotube cytotoxicity using human keratinocyte cells. *Journal of Toxicology and Environmental
972 Health-Part A* 66(20), 1909-1926 (2003).
- 973 103. Brown DM, Kinloch IA, Bangert U *et al.*: An in vitro study of the potential of carbon nanotubes and
974 nanofibres to induce inflammatory mediators and frustrated phagocytosis. *Carbon* 45(9), 1743-
975 1756 (2007).
- 976 104. Watts PCP, Fearon PK, Hsu WK, Billingham NC, Kroto HW, Walton DRM: Carbon nanotubes as pol-
977 ymer antioxidants. *Journal of Materials Chemistry* 13(3), 491-495 (2003).
- 978 105. Fenoglio I, Tomatis M, Lison D *et al.*: Reactivity of carbon nanotubes: Free radical generation or
979 scavenging activity? *Free Radical Biology and Medicine* 40(7), 1227-1233 (2006).
- 980 106. Lucente-Schultz RM, Moore VC, Leonard AD *et al.*: Antioxidant Single-Walled Carbon Nanotubes.
981 *Journal of the American Chemical Society* 131(11), 3934-3941 (2009).
- 982 107. Gilmore JL, Yi X, Quan L, Kabanov AV: Novel nanomaterials for clinical neuroscience. *Journal of
983 Neuroimmune Pharmacology* 3(2), 83-94 (2008).
- 984 108. Galano A: Influence of Diameter, Length, and Chirality of Single-Walled Carbon Nanotubes on
985 Their Free Radical Scavenging Capability. *Journal of Physical Chemistry C* 113(43), 18487-18491
986 (2009).

987 109. Martinez A, Galano A: Free Radical Scavenging Activity of Ultrashort Single-Walled Carbon Nano-
988 tubes with Different Structures through Electron Transfer Reactions. *Journal of Physical Chemistry*
989 *C* 114(18), 8184-8191 (2010).

990 110. Shukla PK, Mishra PC: Effects of diameter, length, chirality and defects on the scavenging action of
991 single-walled carbon nanotubes for OH radicals: A quantum computational study. *Chemical Phys-*
992 *ics* 369(2-3), 101-107 (2010).

993 111. Finkel T, Holbrook NJ: Oxidants, oxidative stress and the biology of ageing. *Nature* 408(6809), 239-
994 247 (2000).

995 112. Churg A, Wright JL: Persistence of natural mineral fibers in human lungs: an overview. *Envi-*
996 *ron.Health Perspect.* 102 Suppl 5, 229-233 (1994).

997 113. Churg A, Wright JL, Gilks B, Depaoli L: RAPID SHORT-TERM CLEARANCE OF CHRYSOTILE COM-
998 PARED WITH AMOSITE ASBESTOS IN THE GUINEA-PIG. *American Review of Respiratory Disease*
999 139(4), 885-890 (1989).

1000 114. Churg A: Deposition and clearance of chrysotile asbestos. *Ann.Occup.Hyg.* 38(4), 625-625 (1994).

1001 115. Coin PG, Roggli VL, Brody AR: Deposition, clearance, and translocation of chrysotile asbestos from
1002 peripheral and central regions of the rat lung. *Environmental Research* 58(1), 97-116 (1992).

1003 116. Berry G: Models for mesothelioma incidence following exposure to fibers in terms of timing and
1004 duration of exposure and the biopersistence of the fibers. *Inhalation Toxicology* 11(2), 111-130
1005 (1999).

1006 117. Deng X, Jia G, Wang H *et al.*: Translocation and fate of multi-walled carbon nanotubes in vivo.
1007 *Carbon* 45(7), 1419-1424 (2007).

1008 118. Lam CW, James JT, McCluskey R, Hunter RL: Pulmonary toxicity of single-wall carbon nanotubes in
1009 mice 7 and 90 days after intratracheal instillation. *Toxicol Sci* 77(1), 126-134 (2004).

1010 119. Kagan VE, Konduru NV, Feng WH *et al.*: Carbon nanotubes degraded by neutrophil myeloperoxi-
1011 dase induce less pulmonary inflammation. *Nature Nanotechnology* 5(5), 354-359 (2010).

1012 120. Liu X, Guo L, Morris D, Kane AB, Hurt RH: Targeted removal of bioavailable metal as a detoxifica-
1013 tion strategy for carbon nanotubes. *Carbon* 46(3), 489-500 (2008).

1014 121. Forrest GA, Alexander AJ: A model for the dependence of carbon nanotube length on acid oxida-
1015 tion time. *Journal of Physical Chemistry C* 111(29), 10792-10798 (2007).

1016 122. Oberdorster G, Morrow PE, Spurny K: Size dependent lymphatic short term clearance of amosite
1017 fibers in the lung. *Ann Occup Hyg* 32, 149-156 (1988).

1018 123. Dodson RF, Williams MG, Jr., Corn CJ, Brollo A, Bianchi C: Asbestos content of lung tissue, lymph
1019 nodes, and pleural plaques from former shipyard workers. *Am.Rev Respir.Dis.* 142(4), 843-847
1020 (1990).

1021 124. Dodson RF, Atkinson MA, Levin JL: Asbestos fiber length as related to potential pathogenicity: a
1022 critical review. *Am.J.Ind.Med.* 44(3), 291-297 (2003).

1023 125. Shvedova AA, Kisin E, Murray AR *et al.*: Inhalation vs. aspiration of single-walled carbon nanotubes
1024 in C57BL/6 mice: inflammation, fibrosis, oxidative stress, and mutagenesis. *American Journal of*
1025 *Physiology-Lung Cellular and Molecular Physiology* 295(4), L552-L565 (2008).

1026 126. Li JG, Li WX, Xu JY *et al.*: Comparative study of pathological lesions induced by multiwalled carbon
1027 nanotubes in lungs of mice by intratracheal instillation and inhalation. *Environ Toxicol* 22(4), 415-
1028 421 (2007).

1029 127. Warheit DB: Long-term Inhalation Toxicity Studies with Multiwalled Carbon Nanotubes: Closing
1030 the Gaps or Initiating the Debate? *Toxicological Sciences* 112(2), 273-275 (2009).

1031 128. Ryman-Rasmussen JP, Cesta MF, Brody AR *et al.*: Inhaled carbon nanotubes reach the subpleural
1032 tissue in mice. *Nat Nanotechnol* 4(11), 747-751 (2009).

1033 129. Mercer RR, Scabilloni J, Wang L *et al.*: Alteration of deposition pattern and pulmonary response as
1034 a result of improved dispersion of aspirated single-walled carbon nanotubes in a mouse model.
1035 *Am J Physiol Lung Cell Mol Physiol* 294(1), L87-L97 (2008).

1036 130. Kane AB, Macdonald JL, Moalli PA: Acute injury and regeneration of mesothelial cells produced by
1037 crocidolite asbestos fibers. *American Review of Respiratory Disease* 133(4), A198-A198 (1986).

1038 131. Moalli PA, Macdonald JL, Goodglick LA, Kane AB: Acute injury and regeneration of the mesotheli-
1039 um in response to asbestos fibers. *American Journal of Pathology* 128(3), 426-445 (1987).

- 1040 132. Donaldson K, Murphy F, Duffin R, Poland CA: Asbestos, carbon nanotubes and the pleural meso-
1041 thelium: a review of the hypothesis regarding the role of long fibre retention in the parietal pleu-
1042 ra, inflammation and mesothelioma. *Part Fibre Toxicol* 7, 5-22 (2010).
- 1043 133. Endo M, Kim YA, Hayashi T *et al.*: Structural characterization of cup-stacked-type nanofibers with
1044 an entirely hollow core. *Applied Physics Letters* 80(7), 1267-1269 (2002).
- 1045 134. Rodriguez NM, Chambers A, Baker RTK: Catalytic engineering of carbon nanostructures. *Langmuir*
1046 11(10), 3862-3866 (1995).
- 1047 135. De Jong KP, Geus JW: Carbon nanofibers: Catalytic synthesis and applications. *Catalysis Reviews-*
1048 *Science and Engineering* 42(4), 481-510 (2000).
- 1049 136. Tran PA, Zhang LJ, Webster TJ: Carbon nanofibers and carbon nanotubes in regenerative medi-
1050 cine. *Advanced Drug Delivery Reviews* 61(12), 1097-1114 (2009).
- 1051 137. Helland A, Wick P, Koehler A, Schmid K, Som C: Reviewing the environmental and human health
1052 knowledge base of carbon nanotubes. *Environmental Health Perspectives* 115(8), 1125-1131
1053 (2007).
- 1054 138. Methner M, Hodson L, Dames A, Geraci C: Nanoparticle Emission Assessment Technique (NEAT)
1055 for the Identification and Measurement of Potential Inhalation Exposure to Engineered Nano-
1056 materials-Part B: Results from 12 Field Studies. *J Occup Environ Hyg* 7(3), 163-176 (2010).
- 1057 139. Eedy DJ: Carbon-fibre-induced airborne irritant contact dermatitis. *Contact Dermatitis* 35(6), 362-
1058 363 (1996).
- 1059 140. Jenkinson HA: Contact dermatitis in a chimney sweep. *Contact Dermatitis* 37(1), 35 (1997).
- 1060 141. Monteiro-Riviere NA, Inman AO: Challenges for assessing carbon nanomaterial toxicity to the skin.
1061 *Carbon* 44(6), 1070-1078 (2006).
- 1062 142. Gogotsi Y: How safe are nanotubes and other nanofilaments? *Materials Research Innovations*
1063 7(4), 192-194 (2003).
- 1064 143. Yokoyama A, Sato Y, Nodasaka Y *et al.*: Biological behavior of hat-stacked carbon nanofibers in the
1065 subcutaneous tissue in rats. *Nano Letters* 5(1), 157-161 (2005).
- 1066 144. Grabinski C, Hussain S, Lafdi K, Braydich-Stolle L, Schlager J: Effect of particle dimension on bio-
1067 compatibility of carbon nanomaterials. *Carbon* 45(14), 2828-2835 (2007).
- 1068 145. Lindberg HK, Falck GCM, Suhonen S *et al.*: Genotoxicity of nanomaterials: DNA damage and mi-
1069 cronuclei induced by carbon nanotubes and graphite nanofibres in human bronchial epithelial
1070 cells in vitro. *Toxicology Letters* 186(3), 166-173 (2009).
- 1071 146. Magrez A, Kasas S, Salicio V *et al.*: Cellular toxicity of carbon-based nanomaterials. *Nano Letters*
1072 6(6), 1121-1125 (2006).
- 1073 147. Vamvakaki V, Tsagaraki K, Chaniotakis N: Carbon nanofiber-based glucose biosensor. *Analytical*
1074 *Chemistry* 78(15), 5538-5542 (2006).
- 1075 148. Kisin ER, Murray AR, Sargent L *et al.*: Genotoxicity of carbon nanofibers: Are they potentially more
1076 or less dangerous than carbon nanotubes or asbestos? *Toxicology and Applied Pharmacology*
1077 252(1), 1-10 (2011).
- 1078 149. Huang WH, Ferris JP: One-step, regioselective synthesis of up to 50-mers of RNA oligomers by
1079 montmorillonite catalysis. *Journal of the American Chemical Society* 128(27), 8914-8919 (2006).
- 1080 150. Lee KS, El-Sayed MA: Dependence of the enhanced optical scattering efficiency relative to that of
1081 absorption for gold metal nanorods on aspect ratio, size, end-cap shape, and medium refractive
1082 index. *Journal of Physical Chemistry B* 109(43), 20331-20338 (2005).
- 1083 151. Jana NR, Gearheart L, Murphy CJ: Wet chemical synthesis of high aspect ratio cylindrical gold na-
1084 norods. *Journal of Physical Chemistry B* 105(19), 4065-4067 (2001).
- 1085 152. Sau TK, Murphy CJ: Seeded high yield synthesis of short Au nanorods in aqueous solution. *Lang-*
1086 *muir* 20(15), 6414-6420 (2004).
- 1087 153. Murphy CJ, San TK, Gole AM *et al.*: Anisotropic metal nanoparticles: Synthesis, assembly, and op-
1088 tical applications. *Journal of Physical Chemistry B* 109(29), 13857-13870 (2005).
- 1089 154. Qiu Y, Liu Y, Wang L *et al.*: Surface chemistry and aspect ratio mediated cellular uptake of Au na-
1090 norods. *Biomaterials* 31(30), 7606-7619 (2010).
- 1091 155. Parab HJ, Chen HM, Lai TC *et al.*: Biosensing, Cytotoxicity, and Cellular Uptake Studies of Surface-
1092 Modified Gold Nanorods. *Journal of Physical Chemistry C* 113(18), 7574-7578 (2009).

1093 156. Leonov AP, Zheng J, Clogston JD, Stern ST, Patri AK, Wei A: Detoxification of Gold Nanorods by
1094 Treatment with Polystyrenesulfonate. *Acs Nano* 2(12), 2481-2488 (2008).

1095 157. Alkilany AM, Nagaria PK, Hexel CR, Shaw TJ, Murphy CJ, Wyatt MD: Cellular Uptake and Cytotoxi-
1096 city of Gold Nanorods: Molecular Origin of Cytotoxicity and Surface Effects. *Small* 5(6), 701-708
1097 (2009).

1098 158. Connor EE, Mwamuka J, Gole A, Murphy CJ, Wyatt MD: Gold nanoparticles are taken up by human
1099 cells but do not cause acute cytotoxicity. *Small* 1(3), 325-327 (2005).

1100 159. Murphy CJ, Thompson LB, Alkilany AM *et al.*: The Many Faces of Gold Nanorods. *Journal of Physi-
1101 cal Chemistry Letters* 1(19), 2867-2875 (2010).

1102 160. Chithrani BD, Ghazani AA, Chan WCW: Determining the size and shape dependence of gold nano-
1103 particle uptake into mammalian cells. *Nano Letters* 6(4), 662-668 (2006).

1104 161. Conner SD, Schmid SL: Regulated portals of entry into the cell. *Nature* 422(6927), 37-44 (2003).

1105 162. Walczyk D, Bombelli FB, Monopoli MP, Lynch I, Dawson KA: What the Cell "Sees" in Bionanosci-
1106 ence. *Journal of the American Chemical Society* 132(16), 5761-5768 (2010).

1107 163. Turci F, Ghibaudi E, Colonna M, Boscolo B, Fenoglio I, Fubini B: An Integrated Approach to the
1108 Study of the Interaction between Proteins and Nanoparticles. *Langmuir* 26(11), 8336-8346 (2010).

1109 164. Hauck TS, Ghazani AA, Chan WCW: Assessing the effect of surface chemistry on gold nanorod up-
1110 take, toxicity, and gene expression in mammalian cells. *Small* 4(1), 153-159 (2008).

1111 165. Weizmann Y, Lim J, Chenoweth DM, Swager TM: Regiospecific Synthesis of Au-
1112 Nanorod/SWCNT/Au-Nanorod Heterojunctions. *Nano Letters* 10(7), 2466-2469 (2010).

1113 166. Patolsky F, Zheng G, Lieber CM: Nanowire-Based Biosensors. *Analytical Chemistry* 78(13), 4260-
1114 4269 (2006).

1115 167. Wang J: Biomolecule-functionalized nanowires: from nanosensors to nanocarriers. *Chem-
1116 physchem* 10(11), 1748-1755 (2009).

1117 168. Lorenz MR, Holzapfel V, Musyanovych A *et al.*: Uptake of functionalized, fluorescent-labeled pol-
1118 ymeric particles in different cell lines and stem cells. *Biomaterials* 27(14), 2820-2828 (2006).

1119 169. Muller KH, Kulkarni J, Motskin M *et al.*: pH-dependent toxicity of high aspect ratio ZnO nanowires
1120 in macrophages due to intracellular dissolution. *ACS Nano* 4(11), 6767-6779 (2010).

1121 170. Prina-Mello A, Diao Z, Coey J: Internalization of ferromagnetic nanowires by different living cells.
1122 *Journal of Nanobiotechnology* 4(1), 9 (2006).

1123 171. Choi D, Fung A, Moon H *et al.*: Transport of living cells with magnetically assembled nanowires.
1124 *Biomedical Microdevices* 9(2), 143-148 (2007).

1125 172. Song MM, Song WJ, Bi H *et al.*: Cytotoxicity and cellular uptake of iron nanowires. *Biomaterials*
1126 31(7), 1509-1517 (2010).

1127 173. Kostarelos K, Lacerda L, Pastorin G *et al.*: Cellular uptake of functionalized carbon nanotubes is in-
1128 dependent of functional group and cell type. *Nature Nanotechnology* 2(2), 108-113 (2007).

1129 174. Kwon NH, Beaux MF, Ebert C *et al.*: Nanowire-based delivery of Escherichia coli O157 shiga toxin 1
1130 A subunit into human and bovine cells. *Nano Lett* 7(9), 2718-2723 (2007).

1131 175. Qi SJ, Yi CQ, Chen WW, Fong CC, Lee ST, Yang MS: Effects of silicon nanowires on HepG2 cell ad-
1132 hesion and spreading. *Chembiochem* 8(10), 1115-1118 (2007).

1133 176. Adili A, Crowe S, Beaux MF *et al.*: Differential cytotoxicity exhibited by silica nanowires and nano-
1134 particles. *Nanotoxicology* 2(1), 1-8 (2008).

1135 177. Julien DC, Richardson CC, Beaux MF, Mcilroy DN, Hill RA: In vitro proliferating cell models to study
1136 cytotoxicity of silica nanowires. *Nanomedicine-Nanotechnology Biology and Medicine* 6(1), 84-92
1137 (2010).

1138 178. Napierska D, Thomassen LCJ, Lison D, Martens JA, Hoet PH: The nanosilica hazard: another varia-
1139 ble entity. *Particle and Fibre Toxicology* 7, (2010).

1140 179. Beaux MF, Bridges NJ, Dehart M, Bitterwolf TE, Mcilroy DN: X-ray photoelectron spectroscopic
1141 analysis of the surface chemistry of silica nanowires. *Applied Surface Science* 257(13), 5766-5771
1142 (2011).

1143 180. Byrne F, Prina-Mello A, Whelan A *et al.*: High content analysis of the biocompatibility of nickel
1144 nanowires. *Journal of Magnetism and Magnetic Materials* 321(10), 1341-1345 (2009).

- 1145 181. Kasprzak KS, Sunderman FW, Jr., Salnikow K: Nickel carcinogenesis. *Mutation Research* 533(1-2),
1146 67-97 (2003).
- 1147 182. Li Z, Yang RS, Yu M, Bai F, Li C, Wang ZL: Cellular Level Biocompatibility and Biosafety of ZnO Nan-
1148 owires. *Journal of Physical Chemistry C* 112(51), 20114-20117 (2008).
- 1149 183. Kuo C-W, Shiu J-Y, Kung Hwa W, Peilen C: Functionalized Silver Nanowires for Live Cell Study.
1150 *Chemistry Letters* 37(6), 610-611 (2008).
- 1151 184. Kuo C-W, Lai J-J, Kung Hwa W, Peilen C: Surface modified gold nanowires for mammalian cell
1152 transfection. *Nanotechnology* 19(2), 025103 (2008).


1153

1154

1155

FIGURES, CAPTIONS and TABLE

FIGURE 1. Scheme of the expected events in the alveoli upon inhalation of fibrous particles. Frustrated phagocytosis mainly occurs with long fibers, but is determined not only by fiber length but also by the chemical composition of the fibers. Short fibers which do not react deleting the phagolysosomal membrane are phagocitized and cleared by macrophages. Conversely long fibers and those reacting within the phagolysome activate and ultimately kill the cells and are released again in the medium.



1165 **FIGURE 2. Magazine advertisings from different asbestos product manufacturers in the beginning of**
1166 **20th century.**

1167 Asbestos is the typical example of a versatile material with exceptional properties which turned out to be
1168 one of the largest occupational tragedies. With appropriate studies on the new HARNs we have the possi-
1169 bility to develop safe material design and manufacturing strategies before a large scale commercialization
1170 takes place. Media source: 1) Turner Brothers Asbestos Company, Manchester, UK, 1918; 2) Keasbey &
1171 Mattison Company, Ambler, PA, 1928; 3) L. W. Kerney, Chicago, IL, 1905; 4) Johns-Manville Company,
1172 New York, NY 1925; 5) Industrial Gloves Company, Danville, IL, 1946.




1173


1174

1175 **FIGURE 3. Scheme of the structure of most common HARNs.**

1176 Schematic representation of the structures of A) carbon nanofibers with different arrangement of the
1177 graphene layers: (from left to right) platelets stacked perpendicularly to the fiber axis (platelet CNF);
1178 platelets angled to the axis (herringbone CNF); carbon nanotubes; stacked cups CNF; stacked cones CNF.
1179 B) nanowires: (from left to right) single segment or single crystal NW, two components radial or core shell
1180 NW, two components multisegment axial NW, two components axial or two segment NW; C) asbestos:
1181 (from left to right) serpentine and amphibole; D) nanorods: (from top to bottom) single metal NR, bi-
1182 component NR (e.g., Au-Pt), coated NR.



1185 **FIGURE 4. A dimensional view of the HARNs whose structure is depicted in Fig 3.**




1186

1187

FIGURE 5. Carbon-nanotubes: hype or hope?

A) Schematic structure of the carbon-carbon bonds and a scanning microscopy image of carbon nanotubes. B) The rate of growth of publications on carbon nanotubes (red) compared to those devoted to their toxicity (pale blue). Clearly studies on the synthesis and application of CNTs pay more than those devoted to the hazard associated to their production and use.



1195

1196 **TABLE 1. CNT vs. Asbestos.**

1197 A comparison of the chemical properties of CNTs and asbestos which are - or may be - implied in their toxicity. The chemical nature of the two materials, at
1198 least in their “native” form, are quite different.

| Carbon nanotubes | | Asbestos | |
|--------------------------------------|---|--|--------------------------------------|
| | | <i>Amphiboles</i> | <i>Chrysotile</i> |
| bio-available metals | highly variable (Co, Ni, Fe – metallic or ionic) | stoichiometric Fe ²⁺ and Fe ³⁺ ions in crystal structure | substitutional Fe ²⁺ ions |
| hydrophilicity hydrophobicity | highly hydrophobic if not functionalized | highly hydrophilic | |
| surface charge (physiological pH) | very low, negative if not functionalized | high, negative | high, positive |
| free radicals | free radicals and ROS scavenging | free radicals and ROS generation | |
| dissolution/degradation | enzymatic degradation in neutrophils (SWCNT) and degradation in phagolysosomal fluid (carboxylated SWCNT) | selective leaching of iron ions only in presence of strong chelators | |

1199

1200

| Carbon nanotubes | | Carbon nanofibers | Nanowires | Nanorods | Asbestos | |
|----------------------------------|--|---|--|--|--|---|
| Structure | single (SWCNT) or multi (MWCNT) graphene layered rolled sheets | graphene layers arranged as stacked cones, cups or plates, aligned perpendicularly (platelet); parallel (tubular) or angled (herringbone) to the fiber axis | single segment (single-crystal) or multi segment (at least two different single-crystal) with radial (core-shell) or axial alignment | single metal, bi-component, coated NR | <u>amphiboles</u> : octahedrally coordinated cations layers sandwiched between tetrahedral silicate layers <u>chrysotile</u> : multi-layered brucitic layers intercalated with silicate rolled sheets | |
| Defects | amount | yes, variable depending upon synthesis procedures | high | yes, variable depending upon size | variable, low | largely variable in natural minerals |
| | kind | ring shapes other than hexagon, sp ³ hybridized C, dangling bonds at the lattice defects and at end caps | dangling bonds at the edges of the grapheme layers; defects similar to CNT ones | stacking faults and twins in the core shell, incomplete bond at the edges, presence of oxide layer on metal NW surface | faceting, twinning, vacancies | defects in the framework, absence or substitution of metal ions |
| Chemical composition | carbon | carbon | metals (Ni, Pt, Au), semiconductor (Si, GaN, etc.) and oxides (SiO ₂ , TiO ₂) | metal (Au, Ag), oxide (TiO ₂) | silicate sheet (SiO ₂) including Mg ²⁺ , Fe ^{2+/3+} , Na ⁺ Ca ²⁺ as structural or substitution ions | |
| Nature of the chemical bond | covalent | covalent | covalent polar ionic metallic | covalent polar metallic | mixed: covalent polar + ionic | |
| Presence of metals or metal ions | highly variable (Co, Ni, Fe). Clusters in different redox states | highly variable. Clusters in different redox states | | always | Fe, higher from amosite and crocidolite | |
| Hydrophilicity / hydrophobicity | hydrophobic | hydrophobic | variable, mostly hydrophilic depending upon composition | variable, depending upon coating | fully hydrophilic | |
| Aggregation / agglomeration | yes | yes | variable, depending upon composition | variable, depending upon coating | naturally in bundles | |
| Durability | high | high | variable, depending upon solubility of the metal/oxide constituting the wire | variable, depending upon the coating dissolution | <u>amphiboles</u> : high in all media <u>chrysotile</u> : generally high, low stability in acidic media | |

