



http://pubs.acs.org/journal/acsodf Article

# Syntheses of Thiophene and Thiazole-Based Building Blocks and Their Utilization in the Syntheses of A-D-A Type Organic Semiconducting Materials with Dithienosilolo Central Unit

Tomi A. O. Parviainen, Petri M. Salmela, Roosa J. Sippola, and Juha P. Heiskanen\*



Cite This: ACS Omega 2022, 7, 26328–26335




**ACCESS** I

Metrics & More

Article Recommendations

s Supporting Information

**ABSTRACT:** Dithienosilole moiety is an electron donating unit, and it has been applied, for example, as a part of small molecular and polymeric electron donors in high performance organic photovoltaic cells. Herein, we report efficient synthetic routes to two symmetrical, dithienosilolo-central-unit-based A-D-A type organic semiconducting materials  $DTS(Th_2FBTTh)_2$  and  $DTS(ThFBTTh)_2$ . Fine-tuned conditions in Suzuki—Miyaura couplings were tested and utilized. The effect of inserting additional hexylthiophene structures symmetrically into the material backbone was investigated, and it was noted that contrary to commonly accepted fact, the distance between electron donor and acceptor seems to play a bigger role in lowering the  $E_{\rm gap}$  value of the molecule than just extending the length of the conjugated backbone. We searched for precedent cases from the literature, and these are compared to our findings. The optical properties of the materials were



characterized with UV—vis spectroscopy. Majority of the intermediate compounds along the way to final products were produced with excellent yields. Our results offer highly efficient routes to many heterocyclic structures but also give new insights into the design of organic semiconducting materials.

## ■ INTRODUCTION

In the syntheses of conjugated organic semiconductor materials, the utilization of different types of coupling reactions is of paramount importance, as constructing the chain-like conjugated structures using alternative synthetic strategies would turn out to be an extremely laborious task. It can be safely stated that coupling reactions like Suzuki—Miyaura have laid the foundation for these types of organic molecules to the extent that can be seen today. In addition, Suzuki—Miyaura cross-coupling is an established and widely used tool of organic synthetic chemistry, especially in organic materials chemistry and medicinal chemistry. Akira Suzuki, the original developer of the Suzuki coupling, was one of the three scientists awarded with Nobel prize in chemistry in 2010 "for palladium-catalyzed cross couplings in organic synthesis".<sup>2</sup>

Organic semiconductors have been successfully applied in organic light emitting diode (OLED) technology, <sup>3</sup> organic biosensors, <sup>4</sup> and organic field-effect transistors (OFET), <sup>5</sup> as well as in organic photovoltaics (OPV), a topic that has drawn considerable research interest in recent times. This could be attributed to the many attractive properties of OPVs, e.g., ease of processing (inkjet printing, roll-to-roll processing) and the possibility to produce lightweight and flexible devices. Most of the aforementioned properties are common also with other organic semiconductor applications.

Ability to fine-tune the electronic and optical properties of materials is one of the greatest strengths of organic semiconductors. Alternating the donor—acceptor sequence in organic semiconductors has had a beneficial impact on HOMO—LUMO levels of the material and promoting, e.g., charge carrier properties. For example, in small molecular OPV active layers, the most successful composition has been acceptor—donor—acceptor, where the central part of the molecule was an electron donating moiety and end groups work as electron acceptors (also known as push—pull structure).

Benzothiadiazole (BT) is an abundantly present building block among organic semiconductors. In addition, several structural modifications of benzothiadiazole in organic semiconductor applications can be found from the literature. For example, fluorination of benzothiadiazole (fluorobenzothiadiazole, FBT) fragment has been shown to be an effective way to lower HOMO and LUMO energy levels of the molecule. Another highly important moiety is thiophene which has

Received: April 8, 2022 Accepted: July 7, 2022 Published: July 21, 2022





extensively been used as a building block in organic semiconductors. In fact, thiophene can be found, as a separate fragment or part in a fused ring system, from most of the recently reported active layers of the high-performance OPVs. The first thiophene-containing semiconducting polymer to gain widespread popularity was P3HT (poly(3-hexylthiophene). On the other hand, the other pentacyclic heteroaromatic compound, thiazole (Tz), is far less utilized in organic semiconducting materials, even though it is present in many natural products, and it has found various uses in the fields of material and medicinal chemistry. Our previous studies showed that the thiazole unit had a major role in the regioselectivity of bromination reactions which could be affected by pH control. 10

The utilization of the alkylated dithienosilole (DTS) moiety in OPV application dates to 2006 to the work of Usta et al. <sup>11</sup> Even though the number of publications concerning dithienosilole as a central unit has been recently decreasing, dithienosilole moiety is still a valid building block when developing high-performance electron donors in OPV applications. <sup>12</sup>

In this paper, we report a synthetic route for two novel organic A-D-A type semiconductor materials, DTS-(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub>. These molecules differ in structure so that DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> contains two additional, symmetrically placed *n*-hexylthiophene moieties. UV—vis spectroscopy was used to characterize the optical properties of the compounds. Differential scanning calorimetry was utilized to determine melting points and the thermal stability of the materials. Most of the intermediates along the synthetic routes could be produced with good to excellent yields. The developed procedures can be applied in fine-tuning the properties of small molecular semiconductors, as well as with their polymeric counterparts from the viewpoint of monomer synthesis strategies.

# **EXPERIMENTAL SECTION**

Commercial reagents were used as received. Compounds 2, 8, and 17 were synthesized as presented in our previous work. 10,13 All molecules were characterized using Bruker 400 MHz NMR spectrometer, and samples were prepared using deuterated chloroform as a solvent, with TMS as an internal standard. All coupling constants are reported in Hz. ESI+ TOF MS characterizations were performed using Thermo Scientific QExactive mass spectrometer. All reactions were monitored with thin-layer chromatography using silica gel-coated aluminum sheets. UV-vis absorption spectra of compounds DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub> in chloroform (concentrations 7.5  $\mu$ M) were measured in quartz glass cuvettes with Shimadzu UV-1800 spectrophotometer. A Mettler Toledo DSC (DSC 821e) was used to evaluate the melting temperatures of DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS-(ThFBTTh)<sub>2</sub>. Experiments were run under inert gas flow  $(50 \text{ cm}^3/\text{min N}_2)$  at a temperature range of 25–280 °C. The heat flow rate was 10 °C/min. Samples (ca. 1.6-3 mg) were weighed into 40 µL aluminum crucibles, which were closed with a pierced lid.

## SYNTHESES

Synthesis of 5-Fluoro-7-(5-hexylthiophen-2-yl)-4-(thiophen-2-yl)-2,1,3-benzothiadiazole (3). A mixture of toluene (3.0 mL), DMA (3.0 mL), distilled water (0.6 mL),

and 2-thiopheneboronic acid pinacol ester (1.22 equiv, 87.0 mg, 0.41 mmol) were deoxygenated with argon gas for 20 min in a reaction tube with a magnetic stirring bar. Compound 2 (135.1 mg, 0.34 mmol), Cs<sub>2</sub>CO<sub>3</sub> (2.61 equiv, 288.2 mg, 0.88 mmol),  $(t-Bu)_3P\cdot HBF_4$  (13 mol %, 12.4 mg, 42  $\mu$ mol), and  $Pd_2(dba)_3$  (4 mol %, 11.6 mg, 12.7  $\mu$ mol) were added to the mixture. The sealed tube was evacuated and backfilled with argon five times. The reaction mixture was stirred and heated in an oil bath (100 °C) for 6 h. The reaction mixture was filtered through a thin pad of silica gel rinsing with toluene and evaporated under reduced pressure. The product was purified by using flash chromatography (SiO<sub>2</sub>, toluene 1:1 *n*-hexane). The isolated 3 was collected as a red solid (134.5 mg) in 99% yield.  ${}^{1}$ H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.88–0.94 (m, 3 H), 1.32-1.47 (m, 6 H), 1.77 (quin, J = 7.6 Hz, 2 H), 2.91 (t, J= 7.6 Hz, 2 H), 6.90 (d, J = 3.7 Hz, 1 H), 7.24 - 7.26 (m, 1 H),7.56 (dd, J = 5.1, 1.1 Hz, 1 H), 7.71 (d, J = 13.0 Hz, 1 H), 7.99(d, J = 3.7 Hz, 1 H), 8.26 (d, J = 3.7 Hz, 1 H). HRMS (ESI+,TOF) m/z: M<sup>+</sup> Calcd for C<sub>20</sub>H<sub>19</sub>N<sub>2</sub>S<sub>3</sub>F 402.0689; Found 402.0679.

**Synthesis of 4-(5-Bromothiophen-2-yl)-5-fluoro-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole (4).** Compound 3 (104.8 mg, 0.26 mmol) was dissolved in THF (17 mL) and NBS (1.1 equiv, 51.0 mg, 0.29 mmol) was added. The reaction mixture was stirred at room temperature for 20 h. The solvent was evaporated, and the crude product was subjected to flash chromatography (SiO<sub>2</sub>, toluene 1:2 *n*-heptane). Pure 4 was isolated as a red solid (104.2 mg) in 83% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>) δ ppm 0.88–0.95 (m, 3 H), 1.33–1.47 (m, 6 H), 1.76 (quin, J = 7.5 Hz, 2 H), 2.89 (t, J = 7.6 Hz, 2 H), 6.89 (d, J = 3.7 Hz, 1 H), 7.18 (d, J = 4.0 Hz, 1 H), 7.65 (d, J = 13.1 Hz, 1 H), 7.96 (d, J = 3.7 Hz, 1 H), 7.98 (d, J = 4.2 Hz, 1 H). HMRS (ESI+, TOF) m/z: M<sup>+</sup> Calcd for C<sub>20</sub>H<sub>18</sub>BrFN<sub>2</sub>S<sub>3</sub> 479.9794; Found 479.9786.

Synthesis of 5-Fluoro-4-(3'-hexyl[2,2'-bithiophen]-5yl)-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole (5). A mixture of toluene (3.0 mL), ethanol (3.0 mL), distilled water (0.6 mL), and 3-hexyl-2-thiopheneboronic acid pinacol ester (1.1 equiv, 69.2 mg 0.24 mmol) was deoxygenated with argon gas for 15 min in a reaction tube with a magnetic stirring bar. Compound 4 (100.5 mg, 0.21 mmol), K<sub>3</sub>PO<sub>4</sub> (3.0 equiv, 132.6 mg, 0.62 mmol), Xantphos (5 mol %, 6.2 mg, 10.7  $\mu$ mol), and Pd(OAc)<sub>2</sub> (5 mol %, 2.5 mg, 11.1  $\mu$ mol) were added to the mixture. The sealed tube was evacuated and backfilled with argon five times. The reaction mixture was stirred and heated in an oil bath (100 °C) for 3 h. The reaction mixture was filtered through a thin pad of silica gel rinsing with toluene and evaporated under reduced pressure. The product was purified by using flash chromatography (SiO<sub>2</sub>, toluene 1:2 n-heptane). The isolated 5 was collected as a deep red solid (115.1 mg) in 97% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.87-0.94 (m, 6 H), 1.31-1.46 (m, 12 H), 1.66-1.73 (m, 2 H), 1.73-1.81 (m, 2 H), 2.84-2.88 (m, 2 H), 2.91 (t, J = 7.7Hz, 2 H), 6.90 (d, J = 3.7 Hz, 1 H), 6.99 (d, J = 5.1 Hz, 1 H), 7.23 (d, J = 5.3 Hz, 1 H), 7.25 (dd, J = 4.0, 1.3 Hz, 1 H), 7.71 (d, J = 13.1 Hz, 1 H), 7.98 (d, J = 3.7 Hz, 1 H), 8.24 (d, J = 4.0)Hz, 1 H). HRMS (ESI+, TOF) m/z:  $M^+$  Calcd for C<sub>30</sub>H<sub>33</sub>N<sub>2</sub>S<sub>4</sub>F 568.1505; Found 568.1492.

Synthesis of 4-(5'-Bromo-3'-hexyl[2,2'-bithiophen]-5-yl)-5-fluoro-7-(5-hexylthiophen-2-yl)-2,1,3-benzothia-diazole (6). Compound 5 (52.3 mg, 91.9  $\mu$ mol) was dissolved in THF (6.2 mL), and NBS (1.09 equiv, 18.3 mg, 0.10 mmol) was added. The reaction mixture was stirred at rt for 22 h. The

solvent was evaporated, and the crude product was subjected to flash chromatography (SiO<sub>2</sub>, toluene 1:2 *n*-heptane). Pure 6 was isolated as a deep red solid (53.4 mg) in 90% yield.  $^1\mathrm{H}$  NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.90 (m, 6 H), 1.25–1.49 (m, 12 H), 1.64 (m, 2 H), 1.70–1.79 (m, 2 H), 2.71–2.81 (m, 2 H), 2.87 (t, J=7.6 Hz, 2 H), 6.86 (d, J=3.8 Hz, 1 H), 6.91 (s, 1 H), 7.13 (dd, J=4.0, 1.3 Hz, 1 H), 7.62 (d, J=13.2 Hz, 1 H), 7.93 (d, J=3.7 Hz, 1 H), 8.16 (d, J=3.9 Hz, 1 H). HRMS (ESI+, TOF) m/z: [M + H]+ Calcd for  $\mathrm{C_{30}H_{32}N_2S_4BrF}$  646.0610; Found 646.0595.

Synthesis of 2,2'-[4,4-Bis(2-ethylhexyl)-4H-silolo[3,2b:4,5-b']bisthiene-2,6-diyl]bis(4,4,5,5-tetramethyl-1,3,2dioxaborolane) (7). Magnesium chips (2.5 equiv, 36.5 mg, 1.50 mmol) and an iodine crystal were added in a reaction tube with a magnetic stirring bar. The sealed reaction system was heated until iodine sublimed. The reaction system was allowed to cool to 25 °C after which the system was purged with argon for 5 min. 2,6-Dibromo-4,4-bis(2-ethylhexyl)-4H-silolo[3,2b:4,5-b'] bisthiophene (350.0 mg, 0.61 mmol) was dissolved in dry THF (2.1 mL) and added through the septum in the reaction system. Under constant stirring, pinacolborane (2.2) equiv, 0.19 mL, 1.34 mmol) was added dropwise through the septum. The reaction mixture was stirred at 25 °C ca. 2 days (until the reaction solution turned from light green into dark brown). The reaction mixture was cooled with an ice bath and toluene (5 mL) was added. 2 M aqueous HCl (2 mL) was added dropwise, and the mixture was stirred for 10 min. During that period, the released H<sub>2</sub> gas escaped from the reaction system through the open needle. The reaction mixture was extracted with toluene  $(2 \times 5 \text{ mL})$ . The combined organic layers were dried with Na2SO4, filtered, and evaporated to dryness. The product was isolated by using flash chromatography (SiO<sub>2</sub>, toluene/n-heptane 1:1). Evaporation afforded product 7 as a viscous oil (345.2 mg) in 85% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.76 (t, J = 7.4 Hz, 6H), 0.81 (t, J =6.6 Hz, 6H), 0.92 (dd, I = 6.9, 2.3 Hz, 4H), 1.06–1.28 (m, 18H), 1.36 (s, 24H), 7.58 (s, 2H).

Synthesis of 2,5-Bis(3-hexylthiophen-2-yl)-1,3-thiazole (10). Toluene (7.5 mL), EtOH (2.5 mL), distilled water (2.5 mL), and 2-(5-hexyl-2-thienyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane (2.15 equiv, 650.8 mg, 2.21 mmol) was deoxygenated for 15 min in a reaction tube with a magnetic stirring bar. 2,5-Dibromothiatzole (250.2 mg, 1.03 mmol), K<sub>3</sub>PO<sub>4</sub> (4.8 equiv., 1.06 g, 4.99 mmol), Xantphos (2.5 mol %, 14.9 mg, 25.8  $\mu$ mol), and Pd(OAc)<sub>2</sub> (2.4 mol %, 5.6 mg, 24.9  $\mu$ mol) were added to a reaction tube which was sealed, evacuated, and refilled with argon gas five times. The reaction mixture was stirred in an oil bath (100 °C) for 4 h. Crude product was filtered through a thin pad of silica gel rinsing with toluene and evaporated under reduced pressure. The product was purified by using flash chromatography (SiO<sub>2</sub>, toluene/nheptane 3:2). Pure 10 was isolated as a yellow viscous liquid (414.1 mg) in 96% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm: 0.85-0.91 (m, 6H), 1.28-1.38 (m, 10H), 1.40-1.47 (m, 2H), 1.59-1.66 (m, 2H), 1.67-1.74 (m, 2H), 2.73 (t, I = 7.7 Hz, 2H), 2.93 (t, J = 7.8 Hz, 2H), 6.95 (dd, J = 5.1, 1.2 Hz, 2H), 7.22 (d, J = 5.1 Hz, 1H), 7.28 (d, J = 5.1 Hz, 1H), 7.76 (s, 1H).  $^{13}$ C NMR (100.6 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 14.0, 14.1, 22.6, 29.2, 29.3, 29.3, 29.9, 30.0, 30.7, 31.6, 124.8, 126.2, 126.5, 130.0, 130.3, 130.5, 131.6, 140.3, 141.2, 142.2, 160.4. HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>23</sub>H<sub>32</sub>NS<sub>3</sub> 418.1697; Found 418.1696.

Synthesis of 5-(5-Bromo-3-hexylthiophen-2-yl)-2-(3hexylthiophen-2-yl)-1,3-thiazole (11a) and 2,5-Bis(5bromo-3-hexylthiophen-2-yl)-1,3-thiazole (11b). Compound 10 (423.1 mg, 1.01 mmol) was dissolved in CHCl<sub>3</sub> (16 mL), and NBS (1.07 equiv., 193.1 mg, 1.08 mmol) was added. Reaction mixture was placed in a sonicator for 4 h. Crude product was purified by flash chromatography (Si<sub>2</sub>O, toluene/ *n*-heptane 3:2). Pure 11a was isolated as a brownish viscous liquid (461.1 mg) in 92% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>) δ ppm: 0.85-0.91 (m, 6H), 1.27-1.36 (m, 10H), 1.39-1.46 (m, 2H), 1.59 (quin, J = 7.5 Hz, 2H), 1.70 (quin, J = 7.6 Hz, 2H), 2.66 (t, J = 7.7 Hz, 2H), 2.92 (t, J = 7.8 Hz, 2H), 6.92 (s, 1H), 6.96 (d, J = 5.1 Hz, 1H), 7.30 (d, J = 5.1 Hz, 1H), 7.71 (s, 1 H).  $^{13}$ C NMR (100.6 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 14.0, 14.1, 22.6, 22.6, 29.1, 29.3, 29.3, 29.9, 30.1, 30.5, 31.6, 31.6, 111.6, 126.7, 127.7, 128.9, 130.5, 131.4, 132.6, 140.7, 141.9, 142.5, 160.8. HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>23</sub>H<sub>31</sub>NS<sub>3</sub>Br 496.0802; Found 496.0791. A small amount of 11b was isolated for analytical purposes. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm: 0.87–0.92 (m, 6H), 1.27–1.45 (m, 12H), 1.56-1.72 (m, 4H), 2.66 (t, J = 8.0 Hz, 2H), 2.85 (t, J = 8.0Hz, 2H), 6.94 (s, 1H), 6.94 (s, 1H), 7.69 (s, 1H). HRMS (ESI +, TOF) m/z: [M + H]<sup>+</sup> Calcd for  $C_{23}H_{30}NS_3Br_2$  573.9901; Found 573.9922.

Synthesis of 5-[3-Hexyl-5-(4,4,5,5-tetramethyl-1,3,2dioxaborolan-2-yl)thiophen-2-yl]-2-(3-hexylthiophen-**2-yl)-1,3-thiazole (12).** Magnesium chips (1.3 equiv, 35.3 mg, 1.45 mmol) and an iodine crystal were added in a reaction tube with a magnetic stirring bar. The sealed reaction system was heated until iodine sublimed. The reaction system was allowed to cool to 25 °C which after the system was purged with argon for 5 min. Compound 11a (491.9 mg, 0.99 mmol) was dissolved in dry THF (2.8 mL) and added through the septum in the reaction system. Under constant stirring, pinacolborane (1.1 equiv, 0.16 mL, 1.10 mmol) was added dropwise through the septum. The reaction mixture was stirred at 25 °C overnight. The reaction mixture was cooled with ice bath, 2 M aqueous HCl (3 mL) was added dropwise, and the mixture was stirred for 10 min. During that period, the released H<sub>2</sub> gas escaped from the reaction system through the open needle. The reaction mixture was extracted with toluene (3  $\times$ 10 mL). The combined organic layers were dried with Na<sub>2</sub>SO<sub>4</sub>, filtered, and evaporated to dryness. The product was isolated by using flash chromatography (SiO<sub>2</sub>). The column was eluated with toluene until the impurities run out. In the second stage, the column was eluated with acetone to isolate the desired product. Finally, evaporation gave compound 12 as a viscous oil (405.3 mg) in 75% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.86–0.91 (m, 6H), 1.30–1.45 (m, 24H), 1.62-1.74 (m, 4H), 2.76 (t, J = 7.8 Hz, 2H), 2.92 (t, J = 7.6Hz, 2H), 6.95 (d, I = 5.1 Hz, 1H), 7.29 (d, I = 5.1 Hz, 1H), 7.49 (s, 1H), 7.84 (s, 1H).  $^{13}$ C NMR (100.6 MHz, CDCl<sub>3</sub>)  $\delta$ ppm 14.0, 22.5, 22.5, 24.6, 29.1, 29.2, 29.8, 30.0, 30.5, 31.5, 31.5, 84.1, 126.5, 128.1, 130.3, 130.4, 131.4, 133.4, 139.9, 140.2, 142.0, 142.2, 160.4. HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>29</sub>H<sub>43</sub>NO<sub>2</sub>S<sub>3</sub>B 544.2549; Found 544.2536.

Synthesis of 5-Fluoro-4-(4-hexylthiophen-2-yl)-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole (13). Compound 13 was synthesized from 2, following the synthetic procedure for 3. The specific amounts of chemicals were as follows: compound 2 (103.9 mg, 0.26 mmol), 2-(4-hexylthiophen-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane (1.2 equiv, 90.5 mg, 0.31 mmol), Cs<sub>2</sub>CO<sub>3</sub> (2.5 equiv, 210.7

#### Scheme 1

"Reagents and conditions: (a) Pd(OAc)<sub>2</sub>, Xantphos, Cs<sub>2</sub>CO<sub>3</sub>, toluene, DMA, H<sub>2</sub>O, 60 °C, and 3 h; (b) Pd<sub>2</sub>(dba)<sub>3</sub>, (t-Bu)<sub>3</sub>P·HBF<sub>4</sub>, Cs<sub>2</sub>CO<sub>3</sub>, toluene, DMA, H<sub>2</sub>O, 100 °C, and 6 h; (c) NBS, THF, rt, and 20 h; (d) Pd(OAc)<sub>2</sub>, Xantphos, K<sub>3</sub>PO<sub>4</sub>, toluene, EtOH, H<sub>2</sub>O, 100 °C, and 4 h; (e) NBS, THF, 0 °C, and 24 h; (f) Pd(OAc)<sub>2</sub>, Xantphos, Na<sub>2</sub>CO<sub>3</sub>, toluene, EtOH, H<sub>2</sub>O, 100 °C, and 24 h; (g) Mg, I<sub>2</sub>, pinacolborane, THF, 25 °C, and 2 days.

mg, 0.65 mmol),  $(t\text{-Bu})_3\text{P}\cdot\text{HBF}_4$  (12 mol %, 8.9 mg, 31  $\mu$ mol), and Pd<sub>2</sub>(dba)<sub>3</sub> (3.6 mol %, 8.5 mg, 9.3  $\mu$ mol). The method afforded **13** as a red solid (124.3 mg) in 98% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm: 0.90–0.93 (m, 6H), 1.32–1.45 (m, 12H), 1.68–1.80 (m, 4H), 2.72 (t, J = 7.7 Hz, 2H), 2.90 (t, J = 7.6 Hz, 2H), 6.89 (d, J = 3.8 Hz, 1H), 7.15 (d, J = 1.1 Hz, 1H), 7.68 (d, J = 13.1 Hz, 1H), 7.96 (d, J = 3.7 Hz, 1 H), 8.09 (d, J = 0.9 Hz, 1 H). HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>26</sub>H<sub>32</sub>N<sub>2</sub>S<sub>3</sub>F 487.1706; Found 487.1698.

Synthesis of 4-(5-Bromo-4-hexylthiophen-2-yl)-5-fluoro-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole (14). Compound 13 (164.5 mg, 0.34 mmol) was dissolved in THF (27 mL), and NBS (1.1 equiv., 67.5 mg, 0.38 mmol) was added. Reaction mixture was placed in a sonicator for 50 min. The solvent was evaporated, and the crude product was purified by flash chromatography (Si<sub>2</sub>O, toluene/*n*-hexane 1:5). Pure 14 was isolated as a red solid (181.4 mg) in 95% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>) δ ppm: 0.90–0.93 (m, 6H), 1.32–1.45 (m, 12H), 1.68 (quin, J = 7.5 Hz, 2H), 1.76 (quin, J = 7.5 Hz, 2H), 2.66 (t, J = 7.6 Hz, 2H), 2.89 (t, J = 7.6 Hz, 2H), 6.89 (d, J = 3.8 Hz, 1H), 7.64 (d, J = 13.2 Hz, 1H), 7.93 (s, 1 H), 7.96 (d, J = 3.7 Hz, 1 H). HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>26</sub>H<sub>31</sub>N<sub>2</sub>S<sub>3</sub>FBr 565.0811; Found 565.0805.

Synthesis of 5-Fluoro-4-{4-hexyl-5-[2-(3-hexylthiophen-2-yl)-1,3-thiazol-5-yl]thiophen-2-yl}-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole (15). Compound 15 was synthesized from 14, following the synthetic procedure for 3. The specific amounts of chemicals were as follows: compound 14 (152.8 mg, 0.27 mmol), 2-(3-hexylthiophen-2yl)-5-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-1,3-thiazole (1.1 equiv, 108.6 mg, 0.29 mmol), Cs<sub>2</sub>CO<sub>3</sub> (2.5 equiv, 218.3 mg, 0.67 mmol),  $(t\text{-Bu})_3 P \cdot HBF_4$  (12 mol %, 9.5 mg, 33  $\mu$ mol), and  $Pd_2(dba)_3$  (4.8 mol %, 12.3 mg, 13  $\mu$ mol). The method afforded 15 as a deep red solid (163.0 mg) in 82% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.89–0.93 (m, 9H), 1.32– 1.49 (m, 18H), 1.69–1.80 (m, 6H), 2.84 (t, J = 8.1 Hz, 2H), 2.89 (t, J = 7.6 Hz, 2H), 2.97 (t, J = 7.8 Hz, 2H), 6.89 (d, J =3.8 Hz, 1H), 6.99 (d, J = 5.1 Hz, 1H), 7.33 (d, J = 5.1 Hz, 1H), 7.67 (d, I = 13.2 Hz, 1H), 7.90 (s, 1H), 7.98 (d, I = 3.7 Hz,

1H), 8.11 (s, 1H). HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for  $C_{39}H_{47}N_3S_5F$  736.2352; Found 736.2332.

Synthesis of 4-{5-[2-(5-Bromo-3-hexylthiophen-2-yl)-1,3-thiazol-5-yl]-4-hexylthiophen-2-yl}-5-fluoro-7-(5hexylthiophen-2-yl)-2,1,3-benzothiadiazole (16). Compound 15 (114.1 mg, 0.16 mmol) was dissolved in THF (9.7 mL), and NBS (1.06 equiv, 30.9 mg, 0.17 mmol) was added. The stirring of the reaction mixture was initiated at 0 °C and the temperature was allowed to rise to room temperature over the next 24 h. The solvent was evaporated, and the crude product was subjected to flash chromatography (SiO<sub>2</sub>, toluene 2:1 n-hexane). Pure 16 was isolated as a deep red solid (70.6 mg) in 56% yield. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.89– 0.93 (m, 9H), 1.32-1.47 (m, 18H), 1.67-1.80 (m, 6H), 2.82-2.92 (m, 6H), 6.90 (d, J = 3.7 Hz, 1H), 6.96 (s, 1H), 7.70 (d, J = 13.2 Hz, 1H), 7.88 (s, 1H), 7.99 (d, J = 3.8 Hz, 1H), 8.12 (s, 1H). HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for C<sub>39</sub>H<sub>46</sub>N<sub>3</sub>S<sub>5</sub>FBr 814.1457; Found 814.1450.

Synthesis of 4,4'-{[4,4-Bis(2-ethylhexyl)-4H-silolo[3,2b:4,5-b']bis-thiene-2,6-diyl]bis[(3'-hexyl[2,2'-bithiophene]-5',5-diyl)]}bis[5-fluoro-7-(5-hexylthiophen-2yl)-2,1,3-benzothiadiazole] (DTS(Th<sub>2</sub>FBTTh)<sub>2</sub>). Compound 7 (13.6 mg, 20  $\mu$ mol) was added into a reaction tube with a magnetic stirring bar, along with ethanol (0.15 mL), distilled water (0.1 mL), and toluene-Pd(OAc)<sub>2</sub> solution (0.85 mL, corresponding to 10 mol %, 400  $\mu$ g, 2  $\mu$ mol of Pd(OAc)<sub>2</sub>). The solution was deoxygenated with argon for 15 min. Compound 6 (2.0 equiv, 25.9 mg, 40  $\mu$ mol), Na<sub>2</sub>CO<sub>3</sub> (5.5 equiv, 11.7 mg, 0.11 mmol), and Xantphos (10 mol %, 1.2 mg, 2  $\mu$ mol) were added in the reaction system. The sealed tube was evacuated and backfilled with argon five times. The reaction mixture was stirred and heated in an oil bath (80 °C) for 4 h. The reaction mixture was filtered through a thin pad of silica gel rinsing with toluene and evaporated under reduced pressure. The crude product was purified by using flash chromatography (SiO<sub>2</sub>, toluene 1:5 n-hexane) and washed with  $4 \times 5$  mL methanol,  $3 \times 5$  mL acetone, and  $2 \times 5$  mL methanol. The isolated DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> was collected as a dark purple solid (18.2 mg) in 59% yield. Mp 133 °C. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.81–1.06 (m, 28H), 1.21– 1.48 (m, 42H), 1.71–1.80 (m, 8H), 2.84–2.92 (m, 8H), 6.90

#### Scheme 2

"Reagents and conditions: (a) Pd(OAc)<sub>2</sub>, Xantphos, K<sub>3</sub>PO<sub>4</sub>, toluene, EtOH, H<sub>2</sub>O, 100 °C, and 4 h; (b) NBS, CHCl<sub>3</sub>, ultrasonic bath, and 4 h; (c) Mg, I<sub>2</sub>, pinacolborane, THF, 25 °C, and overnight; (d) Pd<sub>2</sub>(dba)<sub>3</sub>, (t-Bu)<sub>3</sub>P·HBF<sub>4</sub>, Cs<sub>2</sub>CO<sub>3</sub>, toluene, DMA, H<sub>2</sub>O, 100 °C, and 6 h; (e) NBS, THF, ultrasonic bath, and 50 min; (f) NBS, THF, 0 °C to rt, and 24 h.

(d, J = 3.7 Hz, 2H), 7.03 (s, 2H), 7.16 (s, 2H), 7.26 (s, 2H), 7.71 (d, J = 13.1 Hz, 2H), 7.98 (d, J = 3.7 Hz, 2H), 8.25 (d, J = 3.9 Hz, 2H). HRMS (ESI+, TOF) m/z: [M + H]<sup>+</sup> Calcd for  $C_{84}H_{101}N_4S_{10}F_2Si$  1551.4915; Found 1551.4923.

Synthesis of 4,4'-{[4,4-Bis(2-ethylhexyl)-4H-silolo[3,2b:4,5-b']bisthiene-2,6-diyl]di(thiene-5,2-diyl)}bis[5-fluoro-7-(5-hexylthiophen-2-yl)-2,1,3-benzothiadiazole] (DTS(ThFBTTh)<sub>2</sub>). DTS(ThFBTTh)<sub>2</sub> was synthesized from 4, following the synthetic procedure for DTS(Th2FBTTh)2. The specific amounts of chemicals were as follows: compound 7 (14.3 mg, 21  $\mu$ mol), ethanol (0.15 mL), distilled water (0.1 mL) and toluene-Pd(OAc)<sub>2</sub> -solution (0.85 mL, corresponding to 8 mol %, 400  $\mu$ g, 2  $\mu$ mol of Pd(OAc)<sub>2</sub>), compound 4 (2.1 equiv, 21.7 mg, 45 μmol), Na<sub>2</sub>CO<sub>3</sub> (6.2 equiv, 13.4 mg, 0.13 mmol), and Xantphos (17 mol %, 2.0 mg, 3.5  $\mu$ mol). The crude product was purified by using flash chromatography (SiO<sub>2</sub>, dichloromethane 2:5 n-hexane) and washed with total volume of 30 mL of methanol and 70 mL of acetone. The isolated DTS(ThFBTTh)2 was collected as a dark purple solid (12.1 mg) in 47% yield. Mp 164 °C. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  ppm 0.82-0.94 (m, 18H), 0.98-1.09 (m, 4H), 1.22-1.45 (m, 30 H), 1.77 (quin, J = 7.6 Hz 4H), 2.90 (t, J =7.6 Hz, 4H), 6.89 (d, J = 3.7 Hz, 2H), 7.26 (dd, J = 1.1 Hz, 2H), 7.30 (s, 2H), 7.69 (d, J = 13.2 Hz, 2H), 7.97 (d, J = 3.7Hz, 2H), 8.19 (d, J = 4.0 Hz, 2H). HRMS (ESI+, TOF) m/z: M<sup>+</sup> Calcd for C<sub>64</sub>H<sub>72</sub>N<sub>4</sub>S<sub>8</sub>F<sub>2</sub>Si 1218.3254; Found 1218.3232.

#### RESULTS AND DISCUSSION

**Syntheses.** Compound **2** (Scheme 1) was received from 4,7-dibromo-5-fluoro-2,1,3-benzothiadiazole (1) using a selective Suzuki—Miyaura cross-coupling procedure developed by our group. The method relies on an efficient Pd(OAc)<sub>2</sub> and Xantphos catalyst system. By contrast, the same catalyst system gave **3** only in 50% conversion in 22 h in the consequent reaction step where compound **2** was utilized as a starting material. After short optimizations, compound **3** was synthesized in nearly quantitative yield (99%) from **2** using Pd<sub>2</sub>(dba)<sub>3</sub> and (t-Bu)<sub>3</sub>P·HBF<sub>4</sub> as a catalyst system of Suzuki—Miyaura cross-coupling. Bromination of **3** with NBS in THF gave **4** in good yield (83%) which underwent Suzuki—Miyaura

cross-coupling affording 5 in high yield (97%) in the presence of Pd(OAc)<sub>2</sub>/Xantphos catalyst system. A consequential reaction with NBS gave 6 in high yield (90%).

Compound 7 (Scheme 1) has previously been synthesized in 65% yield utilizing n-BuLi and 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane (IPTMDOB).14 The method developed by Singaram et al., 15 which our group showed to be a reliable method to synthesize 2-(3-hexylthiophen-2-yl)-5-(4,4,5,5tetramethyl-1,3,2-dioxaborolan-2-yl)-1,3-thiazole<sup>10</sup> (compound 17, Scheme 2), gave 7 in highly improved yield (85%). However, the utilization of 7 as a building block proved to be troublesome. Three different catalyst systems Pd(OAc)<sub>2</sub>/ Xantphos,  $Pd_2(dba)_3/(t-Bu)_3P\cdot HBF_4$ , and a special catalyst for sensitive boronic acids, XPhosPdG2, with aqueous Cs<sub>2</sub>CO<sub>3</sub> in toluene/DMA not only catalyzed the desired Suzuki-Miyaura cross-coupling between 6 and 7 but also led to simultaneous hydrolysis of dithienosilole unit. The possible lability of dithienosilole in the presence of an aqueous base has previously been reported by Nguyen et al. 16 Compound 6 did not show any conversion in the presence of Pd(OAc)<sub>2</sub>/ Xantphos in dioxane/H<sub>2</sub>O. In toluene/DMA (anhydrous conditions), the same catalyst system showed formation of multiple byproducts. Previously, Pd(PPh<sub>3</sub>)<sub>4</sub> along with aqueous Na<sub>2</sub>CO<sub>3</sub> in dimethoxyethane (DME) has shown relatively good catalytic activity with compound 7 and its derivatives during polymer syntheses. 14,17 In toluene/ethanol, Pd(PPh<sub>3</sub>)<sub>4</sub> along with aqueous Na<sub>2</sub>CO<sub>3</sub> showed only minor catalytic activity in the Suzuki-Miyaura cross-coupling between 6 and 7. However, signs from hydrolysis of dithienosilole unit could not be observed anymore. The desired compound DTS(Th2FBTTh)2 was finally received in 59% yield using Pd(OAc)<sub>2</sub>/Xantphos with aqueous Na<sub>2</sub>CO<sub>3</sub> in toluene/ethanol. The same reaction system gave compound DTS(ThFBTTh)<sub>2</sub> in 47% yield in the reaction between 7 and 4. However, the method was inefficient for Suzuki-Miyaura cross-coupling between compounds 7 and 8, and the target product DTS(ThTzFBTTh), could not be separated from the crude reaction mixture that also contained unreacted 8 and debrominated form of compound 8. Compound 8 has previously shown efficient reactivity in Suzuki-Miayura crosscouplings in the presence of  $Pd(OAc)_2/X$ antphos with aqueous  $Cs_2CO_3$  in toluene/DMA. The cross-coupling experiments carried out here underline the importance of delicate fine-tuning of reaction conditions. The results here and our previous results show that in most cases  $Pd(OAc)_2/X$ antphos is an extremely efficient catalyst system in Suzuki–Miyaura to construct C–C bonds between thiophene, thiazole, benzothiadiazole, and carbazole units. For unreactive C–Br bonds such as in compound 2,  $Pd_2(dba)_3/(t-Bu)_3P\cdot HBF_4$  catalyst system can be the right choice.

Compound DTS(ThTzThFBTTh)<sub>2</sub> (Scheme 2) was selected for the next target after facing problems with the synthesis of compound DTS(ThTzFBTTh)<sub>2</sub> (Scheme 1). To achieve the target, needed building blocks had to be designed and synthesized. Suzuki-Miyaura cross-coupling between 9 and 2-(3-hexylthiophen-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane gave 10 in high yield (96%). The bromination of 10 with NBS in an ultrasonic bath gave selectively monobrominated product 11a in high yield (92%). The chemical structure of 11a was confirmed by <sup>1</sup>H, <sup>13</sup>C, and 2D NMR measurements (see Supporting Information) to verify the site of bromination. A small amount of dibrominated byproduct 11b along with the unreacted starting material 10 could be separated from the product mixture. The borylation method applied for the synthesis of 7 was also efficient for 11a affording 12 in good yield (75%). Unfortunately, several attempted Suzuki-Miyaura cross-couplings between 12 and 2 were unsuccessful, and the desired product 15 could not be separated. Based on TLC and NMR analyses, the major problem seems to be unwanted deborylation of 12 in the presence of Pd<sub>2</sub>(dba)<sub>3</sub> and (t-Bu)<sub>3</sub>P·HBF<sub>4</sub> or Xantphos. XPhosPdG2, which has previously been shown to act as an efficient catalyst for labile pinacol esters, showed only low conversion of 2 into product 15 at 30 °C. Increasing temperature up to 60 °C was shown to facilitate deborylation

The successful route to 15 was developed starting with cross-coupling between 2 and 2-(4-hexylthiophen-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane that afforded 13 in high yield (98%). Consequent ultrasonic supported bromination and Suzuki-Miyaura reactions afforded 14 and 15 in 95 and 82% yields, respectively. Next, bromination of 15 and flash-chromatographic separation gave monobrominated 16 in medium yield (56%). TLC analysis implied that compound 15 has a strong tendency to give several different bromination products which are challenging to separate. Finally, 16 showed complete unreactivity with 7 under Suzuki-Miyaura reaction conditions with  $Pd(OAc)_2$  or  $Pd_2(dba)_3$  and  $(t-Bu)_3P\cdot HBF_4$  or Xantphos as a catalyst system with aqueous Na<sub>2</sub>CO<sub>3</sub> or  $Cs_2CO_3$  in toluene/EtOH. In the presence of  $Pd(OAc)_2$  with either Xantphos or (t-Bu)<sub>3</sub>P·HBF<sub>4</sub>, the cross-coupling reaction did not proceed at all, and with Pd<sub>2</sub>(dba)<sub>3</sub> and (t-Bu)<sub>3</sub>P·HBF<sub>4</sub> catalyst system complete debromination of 16 was observed in few hours. Thus, compound DTS(ThTzThFBTTh)<sub>2</sub> remained as an unachieved target.

Differential Scanning Calorimetry. To determine the melting temperatures and heat stability of DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub>, DSC measurements were performed for the materials. DSC curves of the materials can be found in Supporting Information (S53 and S54). DTS(ThFBTTh)<sub>2</sub> showed a higher melting temperature of 164 °C compared to the melting temperature of DTS(Th<sub>2</sub>FBTTh)<sub>2</sub>, which was

measured to be 133 °C. This result can be rationalized by the lack of two *n*-hexyl chains in DTS(ThFBTTh)<sub>2</sub>, which could be responsible for better intermolecular  $\pi-\pi$  -interactions of the material.

After the DSC measurements, <sup>1</sup>H NMR spectra from both material samples were recorded, and it was noted that heating under an inert atmosphere to 280 °C had no effect on the integrity of the materials. Thus, the materials can withstand temporary heating to 280 °C under an inert atmosphere without degradation, far exceeding the temperatures encountered in, e.g., typical OPV applications.

**UV**—**vis Measurements.** In order to study the effect of structural variation on electrical and spectral properties, UV—vis absorption spectra of DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS-(ThFBTTh)<sub>2</sub> were measured with a spectrophotometer. The normalized absorption spectra of the compounds in CHCl<sub>3</sub> solution are presented in Figure 1. DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> shows an absorption maximum at 510 nm, whereas the absorption maximum of DTS(ThFBTTh)<sub>2</sub> is red-shifted 30 nm located at 540 nm.




Figure 1. Normalized absorption spectra of compounds DTS-(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub> in CHCl<sub>3</sub>.

Optical band gaps  $(E_{gap})$  were determined from the absorption edges of the lowest energy absorption band. 18 The calculated values were 2.00 and 1.93 eV for compounds DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub>, respectively. In Table 1, the results are compared with the previous studies found in the literature. The observed  $E_{\rm gap}$  values are higher compared to the value of  $DTS(FBTTh_2)_2$  (1.85 eV). By comparing the results of DTS(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS- $(ThFBTTh)_2$  to the results of DTS(FBTTh<sub>2</sub>)<sub>2</sub> (entries 1-3), it can be observed, in addition, that both absorption maxima and edges are blue-shifted with the increasing distance of DTS and FBT units which results in simultaneous increase of  $E_{\rm gap}$  values. On the other hand,  $E_{\rm gap}$  can be decreased by increasing the number of thiophene (Th) end units as demonstrated in the series of DTS(PTTh)2, DTS(PTTh2)2, and DTS(PTTh<sub>3</sub>)<sub>2</sub> (entries 4-6). The series of DTGe-(FBTTh<sub>2</sub>)<sub>2</sub>, DTGe(FBTTh<sub>3</sub>)<sub>2</sub>, and DTGe(ThFBTTh<sub>2</sub>)<sub>2</sub> (entries 7–9) show also that  $E_{\rm gap}$  can be decreased by increasing the Th end units and decreasing the distance between central donor unit (DTGe) and electron accepting FBT units, even

Table 1. Comparison of Optical Properties of Presented and Literature-Reported A-D-A Type Organic Semiconductors<sup>a</sup>

|       | 71                                       | 8                      |                   |           |
|-------|--|------------------------|-------------------|-----------|
| entry | material <sup>a</sup>                    | Amax<br>Aonset<br>[nm] | $E_{ m gap}$ [eV] | ref.      |
| 1     | DTS(Th <sub>2</sub> FBTTh) <sub>2</sub>  | 510<br>621             | 2.00              | this work |
| 2     | DTS(ThFBTTh)2                            | 540<br>641             | 1.93              | this work |
| 3     | DTS(FBTTh <sub>2</sub> ) <sub>2</sub>    | 590<br>670             | 1.85              | 19        |
| 4     | DTS(PTTh) <sub>2</sub>                   | 600<br>690             | 1.80              | 20        |
| 5     | DTS(PTTh <sub>2</sub> ) <sub>2</sub>     | 625<br>732             | 1.69              | 20        |
| 6     | DTS(PTTh <sub>3</sub> ) <sub>2</sub>     | 645<br>740             | 1.67              | 20        |
| 7     | DTGe(FBTTh <sub>2</sub> ) <sub>2</sub>   | -<br>775 <sup>b</sup>  | 1.65 <sup>b</sup> | 21        |
| 8     | DTGe(FBTTh <sub>3</sub> ) <sub>2</sub>   | -<br>781 <sup>b</sup>  | 1.59 <sup>b</sup> | 21        |
| 9     | DTGe(ThFBTTh <sub>2</sub> ) <sub>2</sub> | -<br>778 <sup>b</sup>  | 1.59 <sup>b</sup> | 21        |
| 10    | BDT(BTTh <sub>2</sub> ) <sub>2</sub>     | 569<br>640°            | 1.77 <sup>d</sup> | 22        |
| 11    | BDT(ThBTTh) <sub>2</sub>                 | 526<br>610°            | 1.77 <sup>d</sup> | 22        |
| 12    | SMI                                      | 507<br>600°            | 1.85 <sup>d</sup> | 23        |
| 13    | SM2                                      | 502<br>580°            | 1.98 <sup>d</sup> | 23        |
| 14    | SM3                                      | 491<br>560°            | 2.01 <sup>d</sup> | 23        |
| 15    | BDT-TT-BT                                | 483<br>550°            | 2.03 <sup>d</sup> | 24        |
| 16    | BDT-BT-TT                                | 546<br>620°            | 1.76 <sup>d</sup> | 24        |

 $^{a}$ R<sup>1</sup> = n-hexyl, R<sup>2</sup> = 2-ethylhexyl, R<sup>3</sup> = n-butyl.  $^{b}$ Determined with cyclic voltammetry.  $^{c}$ Estimated from presented UV—vis spectra.  $^{d}$ Calculated from onset of UV—vis absorption of thin-films.

though the effect is much less pronounced. For benzodithiophene (BDT) central donors (entries 10-16), this effect seems to significantly increase with smaller distances between central donor and acceptors as in the case of the DTS central unit.<sup>23,24</sup> From the results presented here and others found from literature, it can be concluded that bringing the acceptor moiety closer to the central donor unit by shortening the intermediate  $\pi$ -bridge decreases the  $E_{\rm gap}$ -value of the compound most efficiently.

#### CONCLUSIONS

In summary, two novel A-D-A type organic semiconductors were designed and synthesized. Incorporation of additional thiophene spacers into the backbone structure led to higher  $E_{\rm gap}$  value, thus decreasing the absorption onset wavelength. Lowering the optical band gap is considered beneficial in most applications, and these results suggest that a careful optimization of the moiety sequence in organic semiconductors plays a potentially larger role in decreasing the optical band gap than the overall size of the conjugated structure alone.

Even though only two out of four target compounds were eventually isolated, a significant amount of information concerning optimized synthetic procedures for novel building blocks was produced along the way. Our findings offer efficient routes to access a variety of small molecular units indispensable especially in the field of organic semiconductors.

# ASSOCIATED CONTENT

#### Supporting Information

The Supporting Information is available free of charge at https://pubs.acs.org/doi/10.1021/acsomega.2c02195.

NMR spectra of synthesized compounds with assignments and DSC curves of compounds DTS-(Th<sub>2</sub>FBTTh)<sub>2</sub> and DTS(ThFBTTh)<sub>2</sub> (PDF)

#### AUTHOR INFORMATION

#### **Corresponding Author**

Juha P. Heiskanen — Research Unit of Sustainable Chemistry, University of Oulu, FI-90014 Oulu, Finland; ocid.org/ 0000-0002-1884-1583; Email: juha.heiskanen@oulu.fi

#### **Authors**

Tomi A. O. Parviainen — Research Unit of Sustainable Chemistry, University of Oulu, FI-90014 Oulu, Finland; orcid.org/0000-0002-3402-6378

Petri M. Salmela – Research Unit of Sustainable Chemistry, University of Oulu, FI-90014 Oulu, Finland

Roosa J. Sippola – Research Unit of Sustainable Chemistry, University of Oulu, FI-90014 Oulu, Finland

Complete contact information is available at: https://pubs.acs.org/10.1021/acsomega.2c02195

#### Notes

The authors declare no competing financial interest.

#### ACKNOWLEDGMENTS

The authors thank Dr. Ulrich Bergmann (Biocenter Oulu) for HRMS data.

#### REFERENCES

- (1) Schneider, N.; Lowe, D. M.; Sayle, R. A.; Tarselli, M. A.; Landrum, G. A. Big Data from Pharmaceutical Patents: A Computational Analysis of Medicinal Chemists' Bread and Butter. J. Med. Chem. 2016, 59, 4385-4402.
- (2) https://www.nobelprize.org/prizes/lists/all-nobel-prizes-inchemistry/ (March 2022).
- (3) Bauri, J.; Choudhary, R. B.; Mandal, G. Recent advances in efficient emissive materials-based OLED applications: a review. J. Mater. Sci. 2021, 56, 18837-18866.
- (4) Hopkins, J.; Fidanovski, K.; Lauto, A.; Mawad, D. All-Organic Semiconductors for Electrochemical Biosensors: An Overview of Recent Progress in Material Design. Front. Bioeng. Biotechnol. 2019, 7,
- (5) Yuvaraja, S.; Nawaz, A.; Liu, Q.; Dubal, D.; Surya, S. G.; Salama, K. N.; Sonar, P. Organic field-effect transistor-based flexible sensors. Chem. Soc. Rev. 2020, 49, 3423-3460.
- (6) Li, Y. Molecular Design of Photovoltaic Materials for Polymer Solar Cells: Toward Suitable Electronic Energy Levels and Broad Absorption. Acc. Chem. Res. 2012, 45, 723-733.
- (7) Wan, X.; Li, C.; Zhang, M.; Chen, Y. Acceptor-donor-acceptor type molecules for high performance organic photovoltaics chemistry and mechanism. Chem. Soc. Rev. 2020, 49, 2828-2842.
- (8) Du, J.; Biewer, M. C.; Stefan, M. C. Benzothiadiazole building units in solution-processable small molecules for organic photovoltaics. J. Mater. Chem. A 2016, 4, 15771-15787.
- (9) Wang, X.; Sun, Q.; Gao, J.; Wang, J.; Xu, C.; Ma, X.; Zhang, F. Recent Progress of Organic Photovoltaics with Efficiency over 17%. Energies 2021, 14, 4200.
- (10) Heiskanen, J. P.; Vivo, P.; Saari, N. M.; Hukka, T. I.; Kastinen, T.; Kaunisto, K.; Lemmetyinen, H. J.; Hormi, O. E. O. Synthesis of Benzothiadiazole Derivatives by Applying C-C Cross-Couplings. J. Org. Chem. 2016, 81, 1535-1546.
- (11) Usta, H.; Lu, G.; Facchetti, A.; Marks, T. J. Dithienosilole- and Dibenzosilole-Thiophene Copolymers as Semiconductors for Organic Thin-Film Transistors. J. Am. Chem. Soc. 2006, 128, 9034-9035.
- (12) Chen, Z.; Song, W.; Yu, K.; Ge, J.; Zhang, J.; Xie, L.; Peng, R.; Ge, Z. Small-molecular donor guest achieves rigid 18.5% and flexible 15.9% efficiency organic photovoltaic via fine-tuning microstructure morphology. Joule 2021, 5, 2395-2407.
- (13) Sippola, R. J.; Hadipour, A.; Kastinen, T.; Vivo, P.; Hukka, T. I.; Aernouts, T.; Heiskanen, J. P. Carbazole-based small molecule electron donors: Syntheses, characterization, and material properties. Dyes Pigm. 2018, 150, 79-88.
- (14) Drozdov, F. V.; Myshkovskaya, E. N.; Susarova, D. K.; Troshin, P. A.; Fominykh, O. D.; Balakina, M. Y.; Bakirov, A. V.; Shcherbina, M. A.; Choi, J.; Tondelier, D.; Buzin, M. I.; Chvalun, S. N.; Yassar, A.; Ponomarenko, S. A. Novel Cyclopentadithiophene-Based D-A Copolymers for Organic Photovoltaic Cell Applications. Macromol. Chem. Phys. 2013, 214, 2144-2156.
- (15) Clary, J. W.; Rettenmaier, T. J.; Snelling, R.; Bryks, W.; Banwell, J.; Wipke, W. T.; Singaram, B. Hydride as a Leaving Group in the Reaction of Pinacolborane with Halides under Ambient Grignard and Barbier Conditions. One-Pot Synthesis of Alkyl, Aryl, Heteroaryl, Vinyl, and Allyl Pinacolboronic Esters. J. Org. Chem. 2011, 76, 9602-
- (16) Walker, B.; Liu, J.; Kim, C.; Welch, G. C.; Park, J. K.; Lin, J.; Zalar, P.; Proctor, C. M.; Seo, J. H.; Bazan, G. C.; Nguyen, T.-Q. Optimization of energy levels by molecular design: evaluation of bisdiketopyrrolopyrrole molecular donor materials for bulk heterojunction solar cells. Energy Environ. Sci. 2013, 6, 952-962.
- (17) Drozdov, F. V.; Surin, N. M.; Peregudova, S. M.; Trukhanov, V. A.; Dmitryakov, P. V.; Chvalun, S. N.; Parashchuk, D. Yu.; Ponomarenko, S. A. Synthesis and Properties of Alternating Copolymers Based on 4H-Cyclopenta[2,1-b:3,4-b']dithiophene and 4H-Dithieno[3,2-b:2',3'-d]silol. Polymer Science, Series B 2019, 61, 56-76.

- (18) Costa, J. C. S.; Taveira, R. J. S.; Lima, C. F. R. A. C.; Mendes, A.; Santos, L. M. N. B. F. Optical band gaps of organic semiconductor materials. Opt. Mater. 2016, 58, 51-60.
- (19) van der Poll, T. S.; Love, J. A.; Nguyen, T.-Q.; Bazan, G. C. Non-Basic High-Performance Molecules for Solution-Processed Organic Solar Cells. Adv. Mater. 2012, 24, 3646-3649.
- (20) Henson, Z. B.; Welch, G. C.; van der Poll, T.; Bazan, G. C. Pyridalthiadiazole-Based Narrow Band Gap Chromophores. J. Am. Chem. Soc. 2012, 134, 3766-3779.
- (21) Walker, B.; Han, D.; Moon, M.; Park, S. Y.; Kim, K.-H.; Kim, J. Y.; Yang, C. Effect of Heterocyclic Anchoring Sequence on the Properties of Dithienogermole-Based Solar Cells. ACS Appl. Mater. Interfaces 2017, 9, 7091-7099.
- (22) Liang, L.; Wang, J.-T.; Xiang, X.; Ling, J.; Zhaob, F.-G.; Li, W.-S. Influence of moiety sequence on the performance of small molecular photovoltaic materials. J. Mater. Chem. 2014, 2, 15396-15405.
- (23) Wang, K.; Liang, R.-Z.; Wolf, J.; Saleem, Q.; Babics, M.; Wucher, P.; Abdelsamie, M.; Amassian, A.; Hansen, M. R.; Beaujuge, P. M. Donor and Acceptor Unit Sequences Influence Material Performance in Benzo [1,2- b:4,5- b'] dithiophene-6,7- Difluoroquinoxaline Small Molecule Donors for BHJ Solar Cells. Adv. Funct. Mater. 2016, 26, 7103-7114.
- (24) Du, J.; Fortney, A.; Washington, K. E.; Bulumulla, C.; Huang, P.; Dissanayake, D.; Biewer, M. C.; Kowalewski, T.; Stefan, M. C. Systematic Investigation of Benzodithiophene-Benzothiadiazole Isomers for Organic Photovoltaics. ACS Appl. Mater. Interfaces 2016, 8, 33025-33033.

# **□** Recommended by ACS

Thiophene-Perylenediimide Bridged Dimeric Porphyrin Donors Based on the Donor-Acceptor-Donor **Structure for Organic Photovoltaics** 

Venkatesh Piradi, Shu Kong So, et al.

JUNE 13, 2022

ACS APPLIED ENERGY MATERIALS

Ladder-Type Fused Benzodithiophene Extended along the Short-Axis Direction as a New Donor Building Block for Efficient Organic Solar Cells

Ning Yang, Do-Hoon Hwang, et al.

NOVEMBER 23 2021

ACS APPLIED MATERIALS & INTERFACES

READ

Rational Design of Bay-Annulated Indigo (BAI)-Based Oligomers for Bulk Heterojunction Organic Solar Cells: A Density Functional Theory (DFT) Study

Shahnaz Ahmed, Dhruba Jyoti Kalita, et al.

APRIL 03, 2020

ACS OMEGA

READ **C** 

**Quinoidal Small Molecule Containing Ring-Extended Termini for Organic Field-Effect Transistors** 

Yoonjung Mok, Dong-Yu Kim, et al.

OCTOBER 07, 2021

ACS OMEGA

RFAD 🗹

Get More Suggestions >